

SVENSK STANDARD

SS-EN 330:2014



Fastställt/Approved: 2014-11-11
Publicerad/Published: 2014-11-13
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 71.100.50

Träskydd – Bestämning av den relativa skyddseffekten hos ett skyddsmedel för trä utomhus ovan mark – Fältprovning

Wood preservatives – Determination of the relative protective effectiveness of a wood preservative for use under a coating and exposed out-of-ground contact – Field test: L-joint method



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 330:2014 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 330:2014.

Denna standard ersätter SS-EN 330, utgåva 1.

The European Standard EN 330:2014 has the status of a Swedish Standard. This document contains the official version of EN 330:2014.

This standard supersedes the Swedish Standard SS-EN 330, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Beständighet, SIS/TK 182/AG 3.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 330

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2014

ICS 71.100.50

Supersedes EN 330:1993

English Version

Wood preservatives - Determination of the relative protective effectiveness of a wood preservative for use under a coating and exposed out-of-ground contact - Field test: L-joint method

Produits de préservation du bois - Détermination de l'efficacité protectrice d'un produit de préservation du bois pour emploi sous un revêtement et hors de contact avec le sol - Essai de champ: méthode avec un assemblage en L

Holzschutzmittel - Bestimmung der relativen Wirksamkeit eines Holzschutzmittels zur Anwendung unter einem Anstrich und ohne Erdkontakt - Freilandprüfung: L-Verbindungsmethode

This European Standard was approved by CEN on 30 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

| | |
|---|----|
| Foreword..... | 4 |
| Introduction | 5 |
| 1 Scope | 6 |
| 2 Normative references | 6 |
| 3 Terms and definitions | 6 |
| 4 Principle | 6 |
| 5 Materials | 7 |
| 5.1 End-seal compounds | 7 |
| 5.2 Reference coating | 7 |
| 5.3 Reference preservative | 7 |
| 5.4 Wood test specimens | 7 |
| 6 Apparatus and Equipment | 10 |
| 6.1 Wood working equipment | 10 |
| 6.2 Conditioning area | 10 |
| 6.3 Application equipment | 10 |
| 6.4 Balance | 10 |
| 6.5 Safety equipment and protective clothing | 10 |
| 6.6 Labels / tags | 10 |
| 6.7 Exposure site | 11 |
| 6.8 Weathering racks | 11 |
| 7 Sampling | 11 |
| 8 Treatment and handling of test L-joints | 12 |
| 8.1 General..... | 12 |
| 8.2 End-sealing..... | 12 |
| 8.3 Process | 12 |
| 8.4 Retention of preservative..... | 12 |
| 8.5 Post-treatment handling of the L-joints | 12 |
| 9 Reference L-joints..... | 13 |
| 10 Untreated test control L-joints | 14 |
| 11 Exposure test site | 14 |
| 11.1 Number of test sites | 14 |
| 11.2 Installation of the L-joints at the test site..... | 14 |
| 12 Inspections | 14 |
| 12.1 L-joints for non- destructive inspection | 14 |
| 12.2 L-joints for destructive inspection..... | 15 |
| 13 Evaluation..... | 16 |
| 13.1 General..... | 16 |
| 13.2 Assessment of decay | 16 |
| 14 Duration of the test | 17 |
| 15 Validity of the test | 17 |
| 16 Test report | 17 |

Annex A (informative) **Flow chart for the preparation and exposure of L-joints for test** 19

Annex B (informative) **Information on treatment processes, reference and alternative preservatives and materials**20

Annex C (informative) **Example of a Test Report**.....22

Annex D (informative) **Environmental, health and safety precautions within chemical / biological laboratory**24

Bibliography.....25

Foreword

This document (EN 330:2014) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2015 and conflicting national standards shall be withdrawn at the latest by May 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 330:1993.

Compared to EN 330:1993 the following changes have been made:

- The scope of the standard clarifies that the effectiveness is evaluated to a reference material;
- The grading system for the assessment of decay has been modified in Table 1;
- Modifications have been made to the duration (Clause 14) and validity (Clause 15) of the test;
- In Annex B information has been added that the reference wood preservatives stated in the document may only be used for research purposes in accordance with the Biocidal Products Regulations (Regulation (EU) No. 528/2012);
- An informative Annex D covering environmental, health and safety precautions has been added.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard describes a method of test for wood preservatives that are intended for use under a surface coating in timber to be exposed to the weather and out of contact with the ground (Use Class 3, EN 335).

The main objective of the test is to evaluate the relative effectiveness of the preservative applied to jointed samples of *Pinus sylvestris* L sapwood by a treatment technique relevant to its intended practical use.

Effectiveness is evaluated relative to a reference material.

The method is concerned with protection against attack by the complete sequence of microorganisms occurring under natural conditions, including those basidiomycete fungi that eventually cause decay. It takes into account the effects of weathering (light, rain and heat) on the effectiveness of a wood preservative under a coating.

The method does not accelerate the rate of decay (see Note), however the coating failure occurs immediately at the test start, that is even sooner than in badly designed and poorly maintained joinery exposed under the same conditions.

The method may be used, after modification, for other purposes including evaluating the effectiveness of a test preservative as follows:

- in protecting timbers of a different wood species;
- under different types of coating.

Since the L-joints are exposed to natural outdoor conditions during the test period, variations in test conditions from one location to another have to be expected. Differences in climate, especially rainfall, will influence the general rate of development of decay fungi. However, by comparing the results obtained for the test preservative with those obtained with the reference material and with those for untreated, control L-joints, the relative protective effectiveness of the preservative under test can be evaluated.

NOTE The coating is intended to make the technique relevant to the end use – albeit the test pieces are badly maintained and designed in order to accelerate the test.

1 Scope

This European Standard specifies a method for determining the relative protective effectiveness against fungal decay of a wood preservative applied to wood in combination with a subsequent surface coating, exposed to the weather and out of contact with the ground. The effectiveness is evaluated relative to a reference wood preservative.

The method is applicable to the testing of commercial or experimental preservatives applied to non-durable timbers by methods appropriate to commercial practice and subsequently coated with a specified coating system. The method is applicable to products and processes used individually or in combination to prevent the development of decay in the wood.

The method is also appropriate for factory finishing systems which include wood protection and wood preservation claims.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1001-2, *Durability of wood and wood based products - Terminology - Part 2: Vocabulary*

EN 335, *Durability of wood and wood-based products - Use classes: definitions, application to solid wood and wood-based products*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1001-2 apply.

4 Principle

Jointed samples (L-joints) are treated, assembled, coated and placed out of contact with the ground and exposed to the normal environmental and ecological factors which affect coated wood so exposed in practice. The organisms that colonize such units invade in their natural sequence of moulds, blue stain fungi, soft rot fungi and basidiomycetes. Colonization by basidiomycetes, as shown by the presence of visible decay, is assessed at least annually by visual inspection of the L-joints after they have been dismantled. In addition, periodically, sets of samples are examined after dismantling and sawing along the grain of the L-joint assemblies to reveal their internal condition. These data are compared with those generated using a reference material and untreated samples to assess relative performance.

It is recommended that the replicates for non-destructive inspection continue to be exposed beyond the minimum 5 year period, preferably until failure.

NOTE Inspection after sawing is necessary because application by processes such as double vacuum and superficial (surface) application does not result in complete penetration of the L-joint members. The untreated core of the samples, therefore, can show internal decay before it becomes visible on the surface within the joint.

5 Materials

5.1 End-seal compounds

5.1.1 Preservative resistant end-seal

A material resistant to the penetration of the reference and test preservative solutions (or separate materials for each).

5.1.2 Weatherproof end-seal

A material that prevents water entry into the test specimen and remains effective for the duration of exposure of the test specimen to the weather.

NOTE Two coats of an epoxy-resin / pitch compound have been found to be suitable.

5.2 Reference coating

Opaque high gloss, gloss or semi-gloss solvent borne alkyd paint applied in 2 or 3 coats to give a dry film build of (50 ± 5) μm or an opaque water borne acrylic paint applied in 1 or 2 coats to give a dry film build of $110 \mu\text{m} - 120 \mu\text{m}$ when measured by method 4A (microscope method) of ISO 2808.

If a particular coating system is specified by the supplier of the test preservative to be an integral part of the protection system, this shall be used in conjunction with the test preservative, instead of the reference coating.

Details of the coating system used shall be given in the test report including the number of coats and the contribution each coat makes to the coating system used, e.g. primer function.

5.3 Reference preservative

Containing hexabutyldistannoxane (bis(tri-*n*-butyltin) oxide) as the active ingredient and with the following composition:

- Hexabutyldistannoxane minimum mass fraction of 1 % (mass fraction 95 % active ingredient);
- Aliphatic neutral hydrocarbon resin mass fraction of 5 %;
- Hydrocarbon solvent mass fraction of 94 %, (distillation range 160 °C to 215 °C; aromatic content mass fraction < 17 %).

If an alternative wood preservative product is used the concentration of the product used should provide a performance equivalent to the specified concentration of the reference wood preservatives referred to in this standard. Evidence of equivalence shall be recorded in the test report.

NOTE See informative Annex B on alternative reference preservatives.

5.4 Wood test specimens

5.4.1 Wood species

Sapwood of *Pinus sylvestris* (Scots Pine, redwood) shall be used. Some heartwood is permitted in the mortise member but none in the joint area (5.4.3).