

SVENSK STANDARD

SS-EN 252:2014



Fastställt/Approved: 2014-11-11
Publicerad/Published: 2014-11-13
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 71.100.50

Träskydd – Bestämning av den relativa förebyggande skyddseffekten hos ett träskyddsmedel i markkontakt – Fältprovning

Field test method for determining the relative protective effectiveness of a wood preservative in ground contact

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-104367>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 252:2014 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 252:2014.

Denna standard ersätter SS 27222, utgåva 1.

The European Standard EN 252:2014 has the status of a Swedish Standard. This document contains the official version of EN 252:2014.

This standard supersedes the Swedish Standard SS 27222, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Beständighet, SIS/TK 182/AG 3.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 252

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2014

ICS 71.100.50

Supersedes EN 252:1989

English Version

Field test method for determining the relative protective effectiveness of a wood preservative in ground contact

Essai de champ pour déterminer l'efficacité protectrice relative d'un produit de préservation du bois en contact avec le sol

Freiland-Prüfverfahren zur Bestimmung der relativen Schutzwirkung eines Holzschutzmittels im Erdkontakt

This European Standard was approved by CEN on 30 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		4
Introduction		5
1 Scope		6
2 Principle		6
3 Wood specimens		6
3.1 Wood species.....		6
3.2 Wood quality		6
3.3 Characteristics and dimension of stakes.....		6
3.4 Number of Stakes		7
3.5 Labelling of stakes.....		7
4 Sample of wood preservative		7
5 Conditioning and treatment of the stakes.....		7
5.1 Conditioning.....		7
5.2 Treating process		7
5.3 Determination of retention of wood preservative product		8
5.4 Range of preservative retention.....		8
5.5 Post treatment conditioning of stakes		8
6 Reference stakes		8
6.1 Reference preservative		8
6.2 Alternative reference preservative.....		9
7 Untreated control stakes.....		9
8 Condition of the test field		9
9 Installation of the stakes in the test field		10
10 Inspections		10
11 Evaluation.....		11
11.1 General.....		11
11.2 Attack by microorganisms.....		11
11.3 Attack by termites.....		11
11.4 Simultaneous attack by microorganisms and termites		12
12 Duration of the test.....		12
13 Conditions for the validity of the test		12
14 Test report		12
Annex A (informative) Guidance for the testing of wood or wood based products that have not been treated with a wood preservative		15
Annex B (informative) Characterization of the field test site.....		17
Annex C (informative) Example of pattern for setting up field stakes into the ground		18

Annex D (informative) Determination of strength characteristics in wood stakes through measuring Modulus of Elasticity	19
Annex E (informative) Example of a test report.....	21
Bibliography.....	24

Foreword

This document (EN 252:2014) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2015 and conflicting national standards shall be withdrawn at the latest by May 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 252:1989.

In relation to the previous version of the standard, the following main modifications have been made:

- change in the assessment criteria for fungal decay;
- minor changes in the description of termite attack;
- the addition of informative annexes concerning the determination of strength characteristics in wood stakes by measuring the modulus of elasticity; the characterization of field test sites and the setting-out of the test stakes in the field test sites.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The method is primarily concerned with protection against microbial attack. However, it is also capable of being used in areas where a termite hazard exists. It should also be noted that microbial decay may alter the resistance of a stake to termite attack and that termite attack may obliterate evidence of microbial decay.

This field method provides one criterion by which the effectiveness of a wood preservative product can be assessed in a ground contact situation (Use Class 4 according to EN 335).

The main objective of the method described is to evaluate the effectiveness of a preservative relative to a reference material.

For this reason permeable timbers are used throughout so that the protective efficacy of various retentions of wood preservative can be determined.

NOTE Informative Annex A gives guidance for testing wood or wood based products in ground contact that have or have not been treated with a wood preservative.

1 Scope

This European Standard specifies a field test method for evaluating the effectiveness of wood preservatives in a ground contact situation. Wood treated with a reference preservative is included for comparison.

The protective effect of the test preservative is assessed in relation to the effect of a reference wood preservative applied by a specified treatment.

2 Principle

Wooden stakes are treated with preservative solutions to give a range of preservative retentions. After drying and, if necessary, an appropriate fixation period, the stakes are partially buried in soil in selected test fields in the open.

The stakes are regularly inspected and their condition compared with that of untreated controls and that of a group of stakes treated with a reference preservative both of which indicate the aggressiveness of the individual field.

The different agents of attack and their respective intensities are recorded.

3 Wood specimens

3.1 Wood species

Susceptible wood species that can be completely penetrated with preservative shall be chosen as follows:

- for every test the sapwood of Scots Pine (*Pinus sylvestris* (L)), shall be used;
- it is recommended that a hardwood species of local importance is included if the preservative is expected to be used in this type of wood;
- if desired other wood species may be incorporated in the test.

3.2 Wood quality

The wood shall be straight-grained and free from knots, cracks, stain, decay, insect holes, reaction wood or other defects. Test stakes with a resinous appearance shall be avoided. The wood shall not have been water-stored, floated, chemically treated or steamed or dried at a temperature above 60 °C.

The Scots Pine sapwood shall show an average rate of growth of 2,5 to 10 annual rings per 10 mm.

If additional wood species are to be used the range in the number of annual rings per 10 mm for each species shall be mentioned in the report.

The test report shall also include the mean density and moisture content for the wood used in the preparation of the stakes.

3.3 Characteristics and dimension of stakes

The boards shall be conditioned at (20 ± 2) °C, (65 ± 5) % relative humidity.

Stakes for test shall be cut from the test wood(s) as follows:

- Each stake shall be planed to within the thickness tolerance indicated. When viewed at the cross-cut end, the rings shall be oriented tangentially to one of the 50 mm edges within the limits $(0 \pm 25)^\circ$;
- The dimensions shall be: (500 ± 2) mm x (50 ± 1) mm x $(25 \pm 0,5)$ mm when measured at a moisture content of (12 ± 2) % (mass fraction).

Each test shall be carried out with stakes of comparable density and any stakes in a test batch which have densities outside the range of 15 % of the mean density shall be rejected.

Additional stakes of different dimensions may also be included in the tests.

3.4 Number of Stakes

At least 10 stakes per field for each wood preservative and retention shall be tested.

A greater number of stakes shall be treated so that stakes with deviating retentions can be rejected (5.3).

Additional stakes may also be included for chemical analysis, to aid determination of retentions and/or penetration/distribution (see 5.3).

To assess the virulence of the field conditions a series of at least 10 untreated control stakes shall be included in each field (see Clause 7).

Include in each field at least two series of 10 standard reference stakes of Scots Pine treated according to 5.2 with a reference preservative (see Clause 6).

3.5 Labelling of stakes

Each stake shall be labelled with an inert, long-lasting label or tag.

NOTE A map of the position of each stake within the site is desirable.

4 Sample of wood preservative

The sample shall be representative of the wood preservative to be tested. It shall be stored and handled in accordance with written recommendations from the manufacturer.

It is recommended to chemically quantify the active ingredients content.

5 Conditioning and treatment of the stakes

5.1 Conditioning

The stakes should be conditioned in conditions to reach constant mass at (20 ± 2) °C and (65 ± 5) %RH.

The stakes shall be air-dried indoors, to a moisture content at which a good penetration of the wood preservative can be obtained. For vacuum / pressure processes the moisture content of the specimens shall be (12 ± 2) % (mass fraction).

5.2 Treating process

For the reference stakes and unless otherwise specified for the test stakes a full-cell process is to be used. A typical full-cell process has an initial vacuum which shall be less than 10 kPa (0,10 bar) and maintained for at