

# SVENSK STANDARD

## SS-EN 10293:2015



Fastställt/Approved: 2015-02-06  
Publicerad/Published: 2015-02-10  
Utgåva/Edition: 2  
Språk/Language: engelska/English  
ICS: 77.140.80

---

### **Stålgjutgods för konstruktions- och allmänna ändamål**

### **Steel castings – Steel castings for general engineering uses**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-105484>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 10293:2015 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10293:2015.

Denna standard ersätter SS-EN 10293:2005, utgåva 1 och SS-EN 10293:2005/AC:2008, utgåva 1.

The European Standard EN 10293:2015 has the status of a Swedish Standard. This document contains the official version of EN 10293:2015.

This standard supersedes the Swedish Standard SS-EN 10293:2005, edition 1 and SS-EN 10293:2005/AC:2008, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Gjutet järn och stål, SIS/TK 130.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

**EN 10293**

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2015

ICS 77.140.80

Supersedes EN 10293:2005

English Version

## Steel castings - Steel castings for general engineering uses

Aciers moulés - Aciers moulés d'usage général

Stahlguss - Stahlguss für allgemeine Anwendungen

This European Standard was approved by CEN on 5 December 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
Foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
■ 3 Terms and definitions .....	5
• 4 Information to be supplied by the purchaser .....	5
5 Designation .....	5
6 Manufacture.....	5
6.1 Manufacturing process .....	5
■ 6.1.1 Melting .....	5
6.1.2 Heat treatment.....	5
6.2 Welding operations.....	6
■ 6.2.1 General.....	6
6.2.2 Production welding.....	6
■ 6.3 Further processing .....	6
7 Requirements .....	6
■ 7.1 General.....	6
7.2 Material .....	6
7.2.1 Chemical composition .....	6
7.2.2 Mechanical properties.....	9
•• 7.2.3 Other properties (magnetic properties).....	15
7.3 Casting.....	15
■ 7.3.1 Chemical composition .....	15
7.3.2 Mechanical properties.....	15
■ 7.3.3 Non-destructive testing.....	15
■ 7.3.4 Conditions of the casting.....	15
■ 7.3.5 Mass of the casting.....	15
■ 7.3.6 Additional requirements regarding the condition of the casting .....	15
8 Inspection .....	15
■ 8.1 General.....	15
■ 8.2 Type of inspection document and type of inspection .....	15
■ 8.3 Test unit .....	15
■ 8.4 Samples .....	15
8.5 Test procedures .....	16
■ 8.6 Invalidation of test results .....	16
■ 8.7 Retests .....	16
■ 8.8 Sorting and reprocessing .....	16
■ 9 Marking .....	16
■ 10 Packaging and surface protection .....	16
■ 11 Complaints .....	16
Annex A (informative) Guidance data for welding .....	17
Bibliography .....	19

## Foreword

This document (EN 10293:2015) has been prepared by Technical Committee ECISS/TC 111 "Steel castings and forgings", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2015 and conflicting national standards shall be withdrawn at the latest by July 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10293:2005.

In comparison with EN 10293:2005, the following significant technical changes were made:

- Alignment with the structure of EN 1559-1:2011, "*Founding - Technical conditions of delivery - Part 1: General*" and EN 1559-2:2014 "*Founding - Technical conditions of delivery - Part 2: Additional requirements for steel castings*";
- New grades (GE270, GE320 and GE360) added.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This document retains the same format for clauses as EN 1559-1:2011 and EN 1559-2:2014. It should be used in conjunction with these standards. Where no text is given under a paragraph heading, the corresponding paragraph of EN 1559-1:2011 and EN 1559-2:2014 applies.

The structure of this document is as follows:

- clauses and subclauses preceded by ■ indicates no additional conditions to EN 1559-1<sup>1)</sup> and EN 1559-2<sup>1)</sup>;
- clauses and subclauses marked with a single dot • indicate that the conditions shall be agreed at the time of enquiry and order;
- subclauses marked with two dots •• indicate that conditions may be agreed at the time of enquiry and order (optional);
- subclauses without dot marking are mandatory.

---

1) When a complementary information is given in a clause or subclause of this document (versus the same clause or subclause of EN 1559-1:2011 or EN 1559-2:2014) it is preceded by “in addition to EN 1559-2:2014”.



## 1 Scope

This European Standard applies to steel castings:

- for general engineering uses. Its uses include machinery (mechanical, electrical...), automotive industries, railroad, armament, agricultural equipment, mining, etc.

In cases where castings are joined by welding by the founder, this document applies.

In cases where castings are welded:

- to wrought products (plates, tubes, forgings...), or
- by non-founders,

this document does not apply.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1559-2:2014, *Founding — Technical conditions of delivery — Part 2: Additional requirements for steel castings*

## ■ 3 Terms and definitions

### • 4 Information to be supplied by the purchaser

In cases of grades with different mechanical properties relating to heat treatment conditions the purchaser shall specify the heat treatment symbol (see Clause 5).

## 5 Designation

In addition to EN 1559-2:2014:

- for a steel grade which can be delivered to different strength levels, according to the heat treatment, a suffix shall be added in accordance with Table 3. For example: G26CrMo4 +QT1.

## 6 Manufacture

### 6.1 Manufacturing process

#### ■ 6.1.1 Melting

#### 6.1.2 Heat treatment

Unless otherwise agreed, the type of heat treatment shall comply with Table 3.

## **6.2 Welding operations**

### **■ 6.2.1 General**

### **6.2.2 Production welding**

In addition to EN 1559-2:2014:

- information on preheat and interpass temperatures as well as on postweld heat-treatment and the corresponding welding groups as defined in EN ISO 11970 is given in Annex A.

### **■ 6.3 Further processing**

## **7 Requirements**

### **■ 7.1 General**

### **7.2 Material**

#### **7.2.1 Chemical composition**

In addition to EN 1559-2:2014:

- the chemical composition determined by a cast analysis shall conform to the values given in Table 1;
- elements unspecified in Table 1 of this document shall not be intentionally added without agreement of the purchaser other than for the purpose of finishing the heat. If not otherwise agreed the maximum values in % (by mass) given in Table 2 shall be applicable;
- permissible deviations between the specified cast analysis and the product analysis are indicated in Table 1 of EN 1559-2:2014.

Table 1 — Chemical composition (cast analysis), (% by mass)

Designation		C		Si	Mn		P	S	Cr		Mo		Ni		V		W
Name	Number	min.	max.	max.	min.	max.	max.	max.	min.	max.	min.	max.	min.	max.	min.	max.	max.
GE200	1.0420	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
GS200	1.0449	-	0,18	0,60	-	1,20	0,030	0,025	-	-	-	-	-	-	-	-	-
GE240	1.0446	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
GS240	1.0455	-	0,23	0,60	-	1,20	0,030	0,025	-	-	-	-	-	-	-	-	-
GE270	1.0454	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
GE300	1.0558	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
GE320	1.0591	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
GE360	1.0597	-	-	-	-	-	0,035	0,030	-	-	-	-	-	-	-	-	-
G17Mn5	1.1131	0,15	0,20	0,60	1,00	1,60	0,020 <sup>a</sup>	0,020 <sup>b</sup>	--	-	-	-	-	-	-	-	-
G20Mn5	1.6220	0,17	0,23	0,60	1,00	1,60	0,020 <sup>a</sup>	0,020 <sup>b</sup>	-	-	-	-	-	0,80	-	-	-
G24Mn6	1.1118	0,20	0,25	0,60	1,50	1,80	0,020 <sup>a</sup>	0,015	-	-	-	-	-	-	-	-	-
G28Mn6	1.1165	0,25	0,32	0,60	1,20	1,80	0,035	0,030	-	-	-	-	-	-	-	-	-
G20Mo5	1.5419	0,15	0,23	0,60	0,50	1,00	0,025	0,020 <sup>b</sup>	-	-	0,40	0,60	-	-	-	-	-
G10MnMoV6-3	1.5410	-	0,12	0,60	1,20	1,80	0,025	0,020	-	-	0,20	0,40	-	-	0,05	0,10	-
G15CrMoV6-9	1.7710	0,12	0,18	0,60	0,60	1,00	0,025	0,020 <sup>b</sup>	1,30	1,80	0,80	1,00	-	-	0,15	0,25	-
G17CrMo5-5	1.7357	0,15	0,20	0,60	0,50	1,00	0,025	0,020 <sup>b</sup>	1,00	1,50	0,45	0,65	-	-	-	-	-
G17CrMo9-10	1.7379	0,13	0,20	0,60	0,50	0,90	0,025	0,020 <sup>b</sup>	2,00	2,50	0,90	1,20	-	-	-	-	-
G26CrMo4	1.7221	0,22	0,29	0,60	0,50	0,80	0,025	0,020 <sup>b</sup>	0,80	1,20	0,15	0,30	-	-	-	-	-
G34CrMo4	1.7230	0,30	0,37	0,60	0,50	0,80	0,025	0,020 <sup>b</sup>	0,80	1,20	0,15	0,30	-	-	-	-	-
G42CrMo4	1.7231	0,38	0,45	0,60	0,60	1,00	0,025	0,020 <sup>b</sup>	0,80	1,20	0,15	0,30	-	-	-	-	-
G30CrMoV6-4	1.7725	0,27	0,34	0,60	0,60	1,00	0,025	0,020 <sup>b</sup>	1,30	1,70	0,30	0,50	-	-	0,05	0,15	-
G35CrNiMo6-6	1.6579	0,32	0,38	0,60	0,60	1,00	0,025	0,020 <sup>b</sup>	1,40	1,70	0,15	0,35	1,40	1,70	-	-	-