

SVENSK STANDARD


SS-EN ISO 10545-11



Fastställt/Approved: 1997-03-27
Publicerad/Published: 1997-03-27
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 91.100.25

Keramiska plattor – Del 11: Bestämning av beständighet mot krackelering hos glaserade plattor (ISO 10545-11:1994)

Ceramic tiles – Part 11: Determination of crazingresistance for glazed tiles (ISO 10545-11:1994)



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN ISO 10545-11:1996 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 10545-11:1996.

Denna standard ersätter SS-EN 105, utgåva 1.

The European Standard EN ISO 10545-11:1996 has the status of a Swedish Standard. This document contains the official English version of EN ISO 10545-11:1996.

This standard supersedes the Swedish Standard SS-EN 105, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN ISO 10545-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1996

ICS 91.100.20

Supersedes EN 105:1991

Descriptors: ceramics, enamelled ceramic, tiles, tests, cracking tests, determination, crazing resistance

English version

Ceramic tiles - Part 11: Determination of crazing resistance for glazed tiles (ISO 10545-11:1994)

Carreaux et dalles céramiques - Partie 11:
Détermination de la résistance au tressailage
pour les carreaux émaillés (ISO 10545-11:1994)

Keramische Fliesen und Platten - Teil 11:
Bestimmung der Widerstandsfähigkeit gegen
Glasurrisse glasierter Fliesen und Platten
(ISO 10545-11:1994)

This European Standard was approved by CEN on 1996-01-14. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard from Technical Committee ISO/TC 189 "Ceramic tiles" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 67 "Ceramic tiles", the secretariat of which is held by UNI.

This European Standard replaces EN 105:1991.

ISO 10545 consists of the following parts, under the general title "Ceramic tiles":

- Part 1: Sampling and basis for acceptance
- Part 2: Determination of dimensions and surface quality
- Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density
- Part 4: Determination of modulus of rupture and breaking strength
- Part 5: Determination of impact resistance by measurement of coefficient of restitution
- Part 6: Determination of resistance to deep abrasion for unglazed tiles
- Part 7: Determination of resistance to surface abrasion for glazed tiles
- Part 8: Determination of linear thermal expansion
- Part 9: Determination of resistance to thermal shock
- Part 10: Determination of moisture expansion
- Part 11: Determination of crazing resistance for glazed tiles
- Part 12: Determination of frost resistance
- Part 13: Determination of chemical resistance
- Part 14: Determination of resistance to stains
- Part 15: Extraction of lead and cadmium from glazed tiles
- Part 16: Determination of colour differences
- Part 17: Determination of coefficient of friction

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1997, and conflicting national standards shall be withdrawn at the latest by February 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 10545-11:1994 has been approved by CEN as a European Standard without any modification.

Ceramic tiles —

Part 11:

Determination of crazing resistance for glazed tiles

1 Scope

This part of ISO 10545 defines a test method for determining the crazing resistance of all glazed ceramic tiles except when the crazing is an inherent decorative feature of the product.

NOTE 1 ISO 13006:—, *Ceramic tiles — Definitions, classification, characteristics and marking* (to be published), provides property requirements for tiles and other useful information on these products.

2 Definition

For the purposes of this part of ISO 10545, the following definition applies.

2.1 craze: Crack, showing as a fine hairline, limited to the glazed surface of a tile.

3 Principle

Determination of the resistance to the formation of crazes by subjecting whole tiles to steam at high pressure in an autoclave, then examination of the tiles for crazes after applying a stain to the glazed faces.

4 Apparatus

4.1 Autoclave, of sufficient internal volume to accommodate five tiles with adequate separation. Ideally, the steam is fed from an external source in order to maintain a pressure of (500 ± 20) kPa, that is, a steam temperature of (159 ± 1) °C for 2 h.

Alternatively, a directly heated autoclave may be used.

5 Test specimens

5.1 A minimum of five whole tiles shall be tested.

5.2 Exceptionally large tiles may be cut into pieces for enclosure in the autoclave, but all pieces shall be tested. The cut pieces shall be as large as possible.

6 Procedure

6.1 First examine the tiles for visible defects by viewing them with the naked eye (or with the aid of spectacles if usually worn) from a distance of 25 cm to 30 cm under an illumination of approximately 300 lx. All test specimens shall be free from crazing at the commencement of the test. The methylene blue solution described in 6.3 may be used to detect pretest crazing. Except in the case of freshly fired tiles being tested as part of a routine in-house quality assurance programme, the tile shall be prepared by re-heating to (500 ± 15) °C at a rate not greater than 150 °C/h and with a soak of not less than 2 h.

6.2 Place the test specimens in the autoclave (4.1) in such a way that there is air space between them. Raise the pressure in the autoclave gradually for a period of 1 h until it reaches (500 ± 20) kPa, (159 ± 1) °C, and maintain this pressure for 2 h. Then turn off the steam source (or the heat supply in the case of directly heated autoclaves), allow the pressure to fall as rapidly as possible to atmospheric and cool the test specimens in the autoclave for 0,5 h. Bring the test specimens into the laboratory atmosphere,

SS-EN ISO 10545-11 (E)

place them singly on a flat surface and allow them to cool for a further period of 0,5 h.

6.3 Brush a suitable stain, such as a 1 % aqueous solution of methylene blue containing a small quantity of wetting agent, on to the glazed surfaces of the test specimens. After 1 min, wipe off the stain with a damp cloth.

6.4 Examine the test specimens for crazes, taking care to avoid confusing crazes with scratches and ignoring cracks.

7 Test report

The test report shall include the following information:

- a) reference to this part of ISO 10545;
- b) a description of the tiles;
- c) the number of test specimens;
- d) the number of test specimens showing crazing;
- e) a description of the crazing (written text, drawing or photograph).