

Fastställt	Utgåva	Sida
2001-07-27	1	1 (1+6)

© Copyright SIS. Reproduction in any form without permission is prohibited.

Aerospace series – Nickel base alloy NI-B31001 (NiCr19Si10) – Filler metal for brazing – Powder or paste

The European Standard EN 3930:2001 has the status of a Swedish Standard. This document contains the official English version of EN 3930:2001.

Swedish Standards corresponding to documents referred to in this Standard are listed in "Catalogue of Swedish Standards", issued by SIS. The Catalogue lists, with reference number and year of Swedish approval, International and European Standards approved as Swedish Standards as well as other Swedish Standards.

Europastandarden EN 3930:2001 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 3930:2001.

Motsvarigheten och aktualiteten i svensk standard till de publikationer som omnämns i denna standard framgår av "Katalog över svensk standard", som ges ut av SIS. I katalogen redovisas internationella och europeiska standarder som fastställts som svenska standarder och övriga gällande svenska standarder.

ICS 49.025.15

Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.
Postadress: SIS Förlag AB, 118 80 STOCKHOLM
Telefon: 08 - 555 523 00. Telefax: 08 - 555 523 11
E-post: sis.sales@sis.se. Internet: www.sisforlag.se

Upplysningar om **sakinnehållet** i standarden lämnas av SIS.
Telefon: 08 - 555 520 00. Telefax: 08 - 555 520 01

Tryckt i september 2001

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 3930

June 2001

ICS 49.025.15

English version

**Aerospace series - Nickel base alloy NI-B31001 (NiCr19Si10) -
Filler metal for brazing - Powder or paste**

Série aérospatiale - Alliage base nickel NI-B31001
(NiCr19Si10) - Métal d'apport de brasage - Poudre ou pâte

Luft- und Raumfahrt - Nickelbasislegierung NI-B31001
(NiCr19Si10) - Hartlot in Form von Pulver oder Paste

This European Standard was approved by CEN on 19 April 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2001, and conflicting national standards shall be withdrawn at the latest by December 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organisation of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-6.

1 Scope

This standard specifies the requirements relating to:

Nickel base alloy NI-B31001 (NiCr19Si10)
Filler metal for brazing
Powder or paste

for aerospace applications.

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 2043	Aerospace series - Metallic materials - General requirements for semi-finished product qualification (excluding forgings and castings) ¹⁾
EN 3875	Aerospace series - Metallic materials - Filler metal for brazing - Technical specification ¹⁾
EN 4258	Aerospace series - Metallic materials - General organization of standardization - Links between types of EN standards and their use
EN 4500-6	Aerospace series - Metallic materials - Rules for drafting and presentation of material standards - Part 6: Specific rules for filler metals for brazing ¹⁾

¹⁾ Published as AECMA Prestandard at the date of publication of this standard

1	Material designation		Nickel base braze alloy NI-B31001 (NiCr19Si10)												
2	Chemical composition ^a %	Element	C	Si	P	S	Cr	Al	B	Co	Se	Ti	Zr	Others	Ni
														Total	
		min.	-	9,75	-	-	18,5	-	-	-	-	-	-	-	-
max.	0,06	10,5	0,02	0,02	19,5	0,05	0,03	0,10	50 *)	0,05	0,05	0,05			
3	Method of melting		Air or inert gas or vacuum melted												
4.1	Form		Powder						Paste						
4.2	Method of production		Water or inert gas atomised and sieved						Water or inert gas atomised and sieved and mixed with a binder						
4.3	Limit dimension(s)	mm	-						-						
5	Technical specification		EN 3875												

6.1	Delivery condition	As manufactured	As manufactured
	Heat treatment	-	-
6.2	Delivery condition code	U	U
7	Use condition	Delivery condition or mixed with a binder	Delivery condition
	Heat treatment	-	-

Characteristics

8.1	Test sample(s)		-
8.2	Test piece(s)		-
8.3	Heat treatment		-
9	Dimensions concerned	mm	-
10	Thickness of cladding on each face	%	-
11	Direction of test piece		-
12	Temperature	θ	°C
13	Proof stress	$R_{p0,2}$	MPa
14	T Strength	R_m	MPa
15	Elongation	A	%
16	Reduction of area	Z	%
17	Hardness		-
18	Shear strength	R_c	MPa
19	Bending	k	-
20	Impact strength		-
21	Temperature	θ	°C
22	Time		h
23	Stress	σ_a	MPa
24	Elongation	a	%
25	Rupture stress	σ_R	MPa
26	Elongation at rupture	A	%
27	Notes (see line 98)		*) ^a