



SWEDISH  
STANDARDS  
INSTITUTE

**SVENSK STANDARD**  
**SS-EN 10059**

Fastställd 2003-11-14

Utgåva 1

**Varmvalsad fyrkantstång av stål – Dimensioner  
och toleranser för form och dimensioner**

**Hot rolled square steel bars for general  
purposes – Dimensions and tolerances on shape  
and dimensions**

ICS 77.140.60

Språk: engelska

Publicerad: januari 2004

Europastandarden EN 10059:2003 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10059:2003.

Denna standard tillsammans med SS-EN 10058, utgåva 1, SS-EN 10060, utgåva 1 och SS-EN 10061, utgåva 1 ersätter SMS 267, utgåva 2.

Denna standard ersätter även SS 21 23 25, utgåva 3.

The European Standard EN 10059:2003 has the status of a Swedish Standard. This document contains the official English version of EN 10059:2003.

This standard together with SS-EN 10058, edition 1, SS-EN 10060, edition 1 and SS-EN 10061, edition 1, supersedes the Swedish Standard SMS 267, edition 2.

This standard supersedes the Swedish Standard SS 21 23 25, edition 3.

Dokumentet består av 11 sidor.

Upplysningar om **sakinnehållet** i standarden lämnas av SIS, Swedish Standards Institute, tel 08 - 555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar **allmänna upplysningar** om svensk och utländsk standard.

*Postadress:* SIS Förlag AB, 118 80 STOCKHOLM  
*Telefon:* 08 - 555 523 10. *Telefax:* 08 - 555 523 11  
*E-post:* [sis.sales@sis.se](mailto:sis.sales@sis.se). *Internet:* [www.sis.se](http://www.sis.se)

EUROPEAN STANDARD

**EN 10059**

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2003

---

ICS 77.140.60

English version

## Hot rolled square steel bars for general purposes - Dimensions and tolerances on shape and dimensions

Carrés en acier laminés à chaud pour usages généraux -  
Dimensions et tolérances sur la forme et les dimensions

Warmgewalzte Vierkantstäbe aus Stahl für allgemeine  
Verwendung - Maße, Formtoleranzen und Grenzabmaße

This European Standard was approved by CEN on 18 September 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

<b>Contents</b>		<b>page</b>
Foreword .....		3
1	Scope.....	4
2	Normative references.....	4
3	Terms and definitions .....	4
4	Designation .....	4
5	Dimensions .....	4
6	Tolerances on dimensions and shape .....	6
6.1	Size ( <i>a</i> ).....	6
6.2	Length ( <i>L</i> ).....	6
6.3	Corner radius ( <i>r</i> ).....	6
6.4	Straightness ( <i>q</i> ).....	6
6.5	Twist .....	6
6.6	Out-of-squareness ( <i>u</i> ).....	6
7	Measurement .....	8
7.1	Size .....	8
7.2	Length .....	8
7.3	Corner radius.....	8
7.4	Straightness.....	8
7.5	Twist .....	8
7.6	Out-of-squareness .....	8

## **Foreword**

This document (EN 10059:2003) has been prepared by Technical Committee ECISS/TC 11 “Structural steel sections and hot rolled steel bars for engineering use — Dimensions and tolerances”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2004, and conflicting national standards shall be withdrawn at the latest by April 2004.

This European Standard replaces:

EURONORM 59-78 *Hot rolled square bars for general purposes.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

## EN 10059:2003 (E)

### 1 Scope

This European Standard specifies the nominal dimensions and the tolerances on dimensions and shape of hot-rolled finished square steel bars for general purposes.

### 2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10079:1992, *Definition of steel products*.

EN 10088-1, *Stainless steels — Part 1: List of stainless steels*.

### 3 Terms and definitions

For the purposes of this European Standard the terms and definitions given in EN 10079:1992 apply.

### 4 Designation

The designation of hot-rolled square steel bars shall comprise:

- the term "square bar";
- the number of this European Standard (EN 10059);
- the dimensions in mm (size x length (M, F or E, see Table 3));
- the number of the quality standard and the steel name or steel number of the ordered steel.

#### EXAMPLE

Square bar EN 10059 - 60x6000M

steel EN 10025 - S235JR

### 5 Dimensions

Hot rolled square bars for general purposes complying with this European Standard shall be delivered with the specified dimensions range given in Table 1 and illustrated in Figure 1. The preferred dimensions are presented in Table 1.