

Träbaserade skivor – Formaldehydemission –
Del 1: Provning enligt kammarmetod

Wood-based panels – Determination of
formaldehyde release –
Part 1: Formaldehyde emission by the chamber
method

Europastandarden EN 717-1:2004 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 717-1:2004. Det finns för närvarande inga planer på att översätta standarden till svenska.

Nationellt förord

SS-EN 717-1 skiljer sig från SS 27 02 36 Byggskivor – Bestämning av formaldehydavgivning vad gäller kammarstorlek, konditionering och preparering av proverna, provningstid, antal luftprover, relativ luftfuktighet i kammaren och tolkningen av slutkoncentrationen ("steady state") i kammaren.

Metoderna uppvisar en god korrelation och ger normalt ungefär lika resultat.

SS 27 02 36 kommer tills vidare inte att upphävas, bland annat eftersom den är både snabbare och billigare än SS-EN 717-1. Vilken av de två metoderna som skall eller bör användas beror på i vilket sammanhang som provningen aktualiseras.

Upplysningar om **sakinnehållet** i standarden lämnas av SIS, Swedish Standards Institute, telefon 08 - 555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar **allmänna upplysningar** om svensk och utländsk standard.

Postadress: SIS Förlag AB, 118 80 STOCKHOLM
Telefon: 08 - 555 523 10. *Telefax:* 08 - 555 523 11
E-post: sis.sales@sis.se. *Internet:* www.sis.se

EUROPEAN STANDARD

EN 717-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2004

ICS 79.060.01

Supersedes ENV 717-1:1998

English version

Wood-based panels - Determination of formaldehyde release - Part 1: Formaldehyde emission by the chamber method

Panneaux à base de bois - Détermination du dégagement
de formaldéhyde - Partie 1 : Emission de for-maldéhyde
par la méthode à la chambre

Holzwerkstoffe - Bestimmung der Formaldehydabgabe -
Teil 1: Formaldehydabgabe nach der Prüfkammer-Methode

This European Standard was approved by CEN on 16 August 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	6
5 Reagents	6
5.1 General.....	6
5.2 Acetylacetone solution	6
5.3 Ammonium acetate solution.....	6
5.4 Formaldehyde standard solution	6
6 Apparatus	7
6.1 Test chamber.....	7
6.2 Air sampling system.....	8
6.3 Equipment for chemical analysis.....	8
6.4 Equipment for verification of air exchange rate	9
7 Test pieces	9
8 Procedure	9
8.1 Test conditions	9
8.2 Verification of test conditions	9
8.3 Chamber preparation	10
8.4 Preparation of test pieces	11
8.5 Loading and starting procedure.....	11
8.6 Air sampling and analysis	11
8.7 Test duration	12
9 Determination of formaldehyde emission	12
9.1 General.....	12
9.2 Principle.....	12
9.3 Procedure	12
9.4 Calibration curve.....	12
9.5 Calculation of the amount of absorbed formaldehyde	13
9.6 Calculation of the formaldehyde emission	14
10 Determination of test result	14
11 Expression of results	14
12 Test report	14
Annex A (normative) Test chambers	17
Annex B (normative) Determination of air exchange rate	24
Annex C (normative) Determination of the steady-state emission value	26
Annex D (informative) Analytical procedure for the fluorimetric determination of formaldehyde content	29
Bibliography	31

Foreword

This document (EN 717-1:2004) has been prepared by Technical Committee CEN/TC 112 “Wood-based panels”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2005, and conflicting national standards shall be withdrawn at the latest by April 2005.

This document supersedes ENV 717-1:1998.

Compared to ENV 717-1:1998 the following modifications have been made.

- a) Conditions for a reduced test period have been specified in Clause 10.
- b) The requirements for the air-tightness of the test chamber in 8.2.2 have been changed.

This European Standard is one of a series, which specifies methods for determining formaldehyde potential in or formaldehyde release from wood-based panels. The other standards of this series are:

EN 120, *Wood based panels — Determination of formaldehyde content — Extraction method called the perforator method.*

EN 717-2, *Wood-based panels — Determination of formaldehyde release — Part 2: Formaldehyde release by the gas analysis method.*

EN 717-3, *Wood-based panels — Determination of formaldehyde release — Part 3: Formaldehyde release by the flask method.*

This European Standard is based on CEN report CR 213 “Particleboards — Determination of Formaldehyde Emission under Specified Conditions” and COST Project 613: Indoor Air Quality and its Impact on Man, Report No. 2: “Formaldehyde emission from wood-based materials: Guideline for the determination of steady state concentrations in test chambers”.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Each testing institute is responsible for the quality of the test procedure. To ensure the reproducibility of the test results, it is recommended to participate in a round-robin test for calibration at least once a year.

1 Scope

This European Standard specifies a chamber method with three options of test chambers for the determination of the formaldehyde emission from wood-based panels in terms of the steady-state concentration in a climate chamber under defined conditions, which relate to typical conditions in real-life. This chamber method can also be applied to the estimation of formaldehyde concentrations under various conditions in practice, by the use of mathematical models.

This standard can also be used for the testing of formaldehyde emissions of products other than wood-based panels.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 326-1, *Wood-based panels — Sampling, cutting and inspection — Part 1: Sampling and cutting of test pieces and expression of test results*.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

volume of the chamber

total air volume of the unloaded chamber, including recirculating ventilation ducts, expressed in cubic metres (m^3)

3.2

loading factor

ratio of the total surface area of the test piece, excluding the area of the edges, to the volume of the chamber, expressed in square metres per cubic metre (m^2/m^3)

3.3

air exchange rate

quotient of air volume passing through the chamber per hour (m^3/h) and the chamber volume (m^3)

3.4

air velocity

velocity of the air near the surface of test pieces in the chamber in metres per second (m/s)

3.5

steady-state

state when the formaldehyde emission of the wood-based panels is quasi constant under the test conditions, this means that the formaldehyde concentration in the chamber remains constant

NOTE In practice, a true steady-state is not achievable because formaldehyde is emitted irreversibly. This standard defines a steady-state condition for the purpose of the test (see Clause 10).

EN 717-1:2004 (E)

3.6 emission value
the steady-state formaldehyde concentration in the chamber, obtained under constant temperature, relative humidity, loading factor and air exchange rate, expressed by mass to volume in milligrams formaldehyde per cubic metre air (mg/m^3)

NOTE At 23 °C and 1 013 hPa, the following relationship exists for formaldehyde:
1 ppm (parts per million) = 1,24 mg/m^3
1 mg/m^3 = 0,81 ppm (parts per million)

4 Principle

Test pieces of known surface area, are placed in a chamber, in which the temperature, relative humidity, air velocity and exchange rate are controlled at defined values. Formaldehyde emitted from the test pieces mixes with the air in the chamber. The air in the chamber is sampled periodically. The formaldehyde concentration is determined by drawing air from the chamber through gas washing bottles containing water, which absorbs the formaldehyde. The formaldehyde concentration in the water is determined. The concentration of formaldehyde in the chamber atmosphere is calculated from the concentration in the water in the gas washing bottles and the volume of the sampled air. It is expressed in milligrams per cubic metre (mg/m^3). Sampling is periodically continued until the formaldehyde concentration in the chamber has reached a steady-state.

NOTE The influences of temperature, relative humidity, loading factor and air exchange rate on the formaldehyde concentration in the chamber atmosphere can be described by formulas (e.g. Andersen formula). An interrelation between the structure of the test pieces, especially of their surfaces and the air velocity is also apparent but cannot be exactly described by a formula.

5 Reagents**5.1 General**

Reagents and water of recognised analytical purity shall be used for the analysis.

5.2 Acetylacetone solution

4 ml acetylacetone are added to a 1 000 ml volumetric flask and made up to the mark with water.

5.3 Ammonium acetate solution

200 g ammonium acetate are dissolved in water in a 1 000 ml volumetric flask and made up to the mark.

NOTE Commercially prepared solutions may be used.

5.4 Formaldehyde standard solution

Standard iodine solution $c(\text{I}_2) = 0,05 \text{ mol/l}$

Standard sodium thiosulphate solution $c(\text{Na}_2\text{S}_2\text{O}_3) = 0,1 \text{ mol/l}$

Standard sodium hydroxide solution $c(\text{NaOH}) = 1 \text{ mol/l}$

Standard sulphuric acid solution $c(\text{H}_2\text{SO}_4) = 1 \text{ mol/l}$

6 Apparatus

6.1 Test chamber

6.1.1 General

This standard applies to different test chambers for formaldehyde emission testing which are described in Annex A.

General specifications and requirements which apply to all types of test chambers included in this standard are given in 6.1.2 to 6.1.8.

6.1.2 Test chamber materials

Materials used for the inner walls and ducts of test chambers shall have a smooth surface, which, prior to testing, can be effectively cleaned with water. The surface shall be as inert and non-absorptive as possible to formaldehyde.

NOTE Proven materials are stainless steel or aluminium (sandblasted or polished), glass and some types of plastics (PVC, PMMA).

6.1.3 Air-tightness of the chamber

The test chamber shall be air-tight in order to avoid uncontrolled air exchange.

The criteria of air-tightness are given in 8.2.2.

6.1.4 Air circulation in the test chamber

The test chamber shall contain facilities (such as fan systems) capable of maintaining:

- intensive air mixing in the chamber;
- an air velocity of 0,1 m/s to 0,3 m/s at the surface of the test pieces (see 8.2.5).

6.1.5 Air exchange facilities

The test chamber shall contain air inlet and/or outlet facilities capable of regulating the air flow and thus the rate of air exchange (replacement of chamber air by clean, conditioned air) with an error limit of 5 % at an air exchange rate of 1/h.

Precautions shall be taken to ensure that the clean air inlet and the air circulation system are adequately placed to ensure sufficient mixing and that ambient air cannot enter into the air outlet, even during sampling.

6.1.6 Clean air supply of the test chamber

Equipment capable of providing clean air with a maximum formaldehyde content of 0,006 mg/m³ (0,005 ppm).

EN 717-1:2004 (E)**6.1.7 Temperature and relative humidity regulating systems**

Equipment capable of maintaining the temperature and the relative humidity in the test chamber within the following limits:

- Temperature: $(23 \pm 0,5) ^\circ\text{C}$
- Relative humidity: $(45 \pm 3) \%$

6.1.8 Equipment for monitoring of test conditions

Measuring equipment and recording facilities capable of continuous or frequent monitoring of the specified test conditions with an error limit as follows:

- Temperature: $0,1 ^\circ\text{C}$
- Relative humidity: 1 %
- Air exchange rate: 0,03/h
- Air velocity: 0,05 m/s

6.2 Air sampling system**6.2.1 General**

Figure 1 shows the principle of a sampling system for the determination of the formaldehyde concentration in the chamber air. The sampling tube shall be placed either in the air outlet, or inside the chamber, close to the air outlet.

NOTE Other sampling systems may be used, provided it can be shown that they give equivalent results.

6.2.2 Equipment**6.2.2.1 General**

The air sampling system consists of the following components which are given in Figure 1. The numbers in brackets refer to the numbers in Figure 1:

- 6.2.2.2** Sampling tube (1)
- 6.2.2.3** Two 100 ml gas washing bottles, containing water, for absorption and subsequent determination of formaldehyde (2)
- 6.2.2.4** Silica absorber for drying the air (3)
- 6.2.2.5** Gas flow valve (4)
- 6.2.2.6** Gas sampling pump (5)
- 6.2.2.7** Gas flow meter (6)
- 6.2.2.8** Gas meter (including a thermometer) for measuring the volume of air (7)
- 6.2.2.9** Air pressure meter (8)

6.3 Equipment for chemical analysis

6.3.1 Spectrophotometer, suitable for use with cells with a path-length of at least 50 mm and capable of measuring absorbance at 412 nm

- 6.3.2 Water bath, capable of maintaining a temperature of $(40 \pm 1) ^\circ\text{C}$
- 6.3.3 Six volumetric flasks, 100 ml (calibrated at $20 ^\circ\text{C}$)
- 6.3.4 Two volumetric flasks, 1 000 ml (calibrated at $20 ^\circ\text{C}$)
- 6.3.5 Bulb pipettes, 5 ml, 10 ml, 15 ml, 20 ml, 25 ml, 50 ml, and 100 ml (calibrated at $20 ^\circ\text{C}$)
- 6.3.6 Microburette
- 6.3.7 At least three flasks, 50 ml, with stoppers
- 6.3.8 Balance, scale interval 0,001 g

6.4 Equipment for verification of air exchange rate

- 6.4.1 Compressed-gas cylinder with tracer-gas
- 6.4.2 Detector for continuous monitoring of tracer-gas
- 6.4.3 Recorder

NOTE Dinitrogen monoxide (N_2O) with infrared (IR) detection has proved to be suitable.

7 Test pieces

Sample the test pieces according to the general principles of EN 326-1 and cut them to a size which corresponds to a total loading rate of $1 \text{ m}^2/\text{m}^3$ (see Annex A). Wrap the test pieces hermetically immediately after cutting and leave them wrapped until the start of the test.

8 Procedure

8.1 Test conditions

The following conditions shall be maintained in the chamber throughout the test:

- Temperature $(23 \pm 0,5) ^\circ\text{C}$;
- Relative humidity $(45 \pm 3) \%$;
- Loading factor $(1,0 \pm 0,02) \text{ m}^2/\text{m}^3$;
- Air exchange rate $(1,0 \pm 0,05)/\text{h}$;
- Air velocity at the surface of the test pieces (see 8.2.5) $(0,1 \text{ to } 0,3) \text{ m/s}$.

8.2 Verification of test conditions

8.2.1 Clean air supply of the test chamber

When determined in accordance with Clause 9, the formaldehyde content of the air supplied to the chamber shall not exceed $0,006 \text{ mg}/\text{m}^3$ (0,005 ppm).

8.2.2 Air-tightness of the test chamber

In order to avoid uncontrolled air exchange by intrusion of ambient air, the test chamber shall be operated at a slight over-pressure.