

**Konstruktionskeramer – Provningsmetoder för
keramiska pulver –**

Del 3: Bestämning av syrehalt i icke-oxider genom
termisk extraktion med bärgas

**Advanced technical ceramics – Methods of test
for ceramic powders –**

Part 3: Determination of the oxygen content of non-
oxides by thermal extraction with a carrier gas

Europastandarden EN 725-3:2007 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 725-3:2007.

Denna standard ersätter SS-EN 725-3, utgåva 1.

The European Standard EN 725-3:2007 has the status of a Swedish Standard. This document contains the official English version of EN 725-3:2007.

This standard supersedes the Swedish Standard SS-EN 725-3, edition 1.

Upplysningar om **sakinnehållet** i standarden lämnas av SIS, Swedish Standards Institute, telefon 08 - 555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar **allmänna upplysningar** om svensk och utländsk standard.

Postadress: SIS Förlag AB, 118 80 STOCKHOLM
Telefon: 08 - 555 523 10. *Telefax:* 08 - 555 523 11
E-post: sis.sales@sis.se. *Internet:* www.sis.se

EUROPEAN STANDARD

EN 725-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2007

ICS 81.060.30

Supersedes EN 725-3:1994

English Version

**Advanced technical ceramics - Methods of test for ceramic
powders - Part 3: Determination of the oxygen content of non-
oxides by thermal extraction with a carrier gas**

Céramiques techniques avancées - Méthodes d'essais
pour poudres céramiques - Partie 3: Détermination de la
teneur en oxygène de poudres non-oxydes par extraction à
chaud sous gaz porteur

Hochleistungskeramik - Prüfverfahren für keramische
Pulver - Teil 3: Bestimmung des Sauerstoffgehaltes in
Nichtoxid-Pulvern mittels Trägergasheißextraktion

This European Standard was approved by CEN on 2 December 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Principle.....	4
4	Apparatus	4
5	Sample preparation	5
6	Calibration	5
7	Blank determination	5
8	Procedure	5
9	Test report	6
Annex A (informative) Guidance in the selection of test conditions		7

Foreword

This document (EN 725-3:2007) has been prepared by Technical Committee CEN/TC 184 “Advanced technical ceramics”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2007, and conflicting national standards shall be withdrawn at the latest by July 2007.

This document supersedes EN 725-3:1994.

EN 725 *Advanced technical ceramics — Methods of test for ceramic powders* was prepared in Parts as follows:

Part 1: *Determination of impurities in alumina*

Part 2: *Determination of impurities in barium titanate*

Part 3: *Determination of the oxygen content of non-oxides by thermal extraction with a carrier gas*

Part 4: *Determination of oxygen content in aluminium nitride by XRF analysis*

Part 5: *Determination of particle size distribution*

Part 6: *Determination of the specific surface area* [withdrawn]

Part 7: *Determination of the absolute density* [withdrawn]

Part 8: *Determination of tapped bulk density*

Part 9: *Determination of un-tapped bulk density*

Part 10: *Determination of compaction properties*

Part 11: *Determination of densification on natural sintering*

Part 12: *Chemical analysis of zirconia*

Parts 6 and 7 of the series were superseded in 2005 by EN ISO 18757 and EN ISO 18753 respectively.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 725-3:2007 (E)

1 Scope

This part of EN 725 describes a method for the determination of the oxygen content of non-oxide powders used for advanced technical ceramics, using an inert carrier gas thermal extraction method. The method described is suitable for oxygen contents of less than 3 %.

NOTE An indication of the limits of determination is usually given by the manufacturers of the gas analysis apparatus used. However, for a specific measurement procedure, such limits can be determined by experiments conducted by the user.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)*

3 Principle

A test sample is heated in a graphite crucible at a high temperature in a flow of an inert carrier gas. Oxygen in the sample is converted to oxides of carbon, which are extracted and transformed to consist entirely of either carbon monoxide or carbon dioxide. This volume is then determined by a method of gas analysis.

NOTE Guidance on the selection of test conditions is given in Annex A.

4 Apparatus

4.1 Scoop, for transferring the test sample.

4.2 Graphite crucible, which is used as a carbon source. The crucible is capable of being electrically heated by two electrodes, or by induction.

4.3 Tin or nickel capsule (optional), to contain the ceramic powder sample.

4.4 Nickel wire basket (optional), for use as a fluxing agent with certain powders such as aluminium nitride.

4.5 Gas analysis apparatus, based on one of the following techniques:

- a) volumetric analysis, for measurement of carbon monoxide gas;
- b) chromatography, for carbon monoxide;
- c) thermal conductivity, for carbon monoxide and carbon dioxide;
- d) coulometric analysis, for carbon dioxide;
- e) infrared absorption, for carbon dioxide;
- f) gravimetry, by absorption of carbon dioxide.