

**Aerospace series – Heat resisting alloy FE-  
PA2601 (X6NiCrTiMoV26-15) – Consumable  
electrode remelted – Solution and precipitation  
treated – Sheet, strip and plate –  $0,5 \text{ mm} \leq a \leq 10$   
mm**

Europastandarden EN 3638:2007 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 3638:2007.

The European Standard EN 3638:2007 has the status of a Swedish Standard. This document contains the official English version of EN 3638:2007.

---

Uppllysningar om **sakinnehållet** i standarden lämnas av SIS, Swedish Standards Institute, telefon 08 - 555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar **allmänna upplysningar** om svensk och utländsk standard.

*Postadress:* SIS Förlag AB, 118 80 STOCKHOLM  
*Telefon:* 08 - 555 523 10. *Telefax:* 08 - 555 523 11  
*E-post:* sis.sales@sis.se. *Internet:* www.sis.se

EUROPEAN STANDARD

**EN 3638**

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2007

ICS 49.025.10

English Version

**Aerospace series - Heat resisting alloy FE-PA2601  
(X6NiCrTiMoV26-15) - Consumable electrode remelted -  
Solution and precipitation treated - Sheet, strip and plate - 0,5  
mm ≤ a ≤ 10 mm**

Série aéronautique - Alliage résistant à chaud FE-PA2601  
(X6NiCrTiMoV26-15) - Elaboré par électrode consommable  
- Mis en solution et précipité - Tôles, bandes et plaques -  
0,5 mm ≤ a ≤ 10 mm

Luft- und Raumfahrt - Hochwarmfeste Legierung FE-  
PA2601 (X6NiCrTiMoV26-15) - Mit selbstverzehrender  
Elektrode umgeschmolzen - Lösungsgeglüht und  
ausgelagert - Bleche, Bänder und Platten - 0,5 mm ≤ a ≤ 10  
mm

This European Standard was approved by CEN on 5 October 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Foreword

This document (EN 3638:2007) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-3.

## 1 Scope

This standard specifies the requirements relating to:

Heat resisting alloy FE-PA2601 (X6NiCrTiMoV26-15)  
Consumable electrode remelted  
Solution and precipitation treated  
Sheet, strip and plate  
 $0,5 \text{ mm} \leq a \leq 10 \text{ mm}$

for aerospace applications.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)*. <sup>1)</sup>

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*.

EN 4050-4, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 4: Acceptance criteria*. <sup>1)</sup>

EN 4500-3, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 3: Specific rules for heat resisting alloys*. <sup>1)</sup>

EN 4700-1, *Aerospace series — Steel and heat resisting alloy — Wrought products — Technical specification — Part 1: Plate, sheet and strip*. <sup>1)</sup>

---

<sup>1)</sup> Published as ASD Prestandard at the date of publication of this standard.

**EN 3638:2007 (E)**

|     |                         |         |   |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
|-----|-------------------------|---------|---|------|------|-------|-------|------|------------------|------|------|------|------|------|-----------------|------|
| 1   | Material designation    |         | Heat resisting alloy FE-PA2601 (X6NiCrTiMoV26-15) |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
| 2   | Chemical composition %  | Element | C   | Si   | Mn   | P     | S     | Al   | B                | Cr   | Mo   | Ni   | Ti   | V    | Pb              | Fe   |
|     |                         | min.    | –   | –    | 1,00 | –     | –     | –    | 30 <sup>a</sup>  | 13,5 | 1,00 | 24,0 | 1,90 | 0,10 | –               | Base |
|     |                         | max.    | 0,080   | 1,00 | 2,00 | 0,020 | 0,015 | 0,35 | 100 <sup>a</sup> | 16,0 | 1,50 | 27,0 | 2,30 | 0,50 | 20 <sup>a</sup> |      |
| 3   | Method of melting       |         | Consumable electrode remelted                     |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
| 4.1 | Form                    |         | Sheet, strip and plate                            |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
| 4.2 | Method of production    |         | Rolled  |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
| 4.3 | Limit dimension(s)      | mm      | 0,5 ≤ a ≤ 10                                      |      |      |       |       |      |                  |      |      |      |      |      |                 |      |
| 5   | Technical specification |         | EN 4700-1   |      |      |       |       |      |                  |      |      |      |      |      |                 |      |

|     |                         |  |  |  |  |  |  |  |  |  |  |  |  |  |  |  |
|-----|-------------------------|--|--|--|--|--|--|--|--|--|--|--|--|--|--|--|
| 6.1 | Delivery condition      |  | Solution treated and descaled                          |  |  |  |  |  |  |  |  |  |  |  |  |  |
|     | Heat treatment          |  | 980 °C ± 10 °C / t ≥ 15 min / AQ                       |  |  |  |  |  |  |  |  |  |  |  |  |  |
| 6.2 | Delivery condition code |  | W  |  |  |  |  |  |  |  |  |  |  |  |  |  |
| 7   | Use condition           |  | Solution and precipitation treated                     |  |  |  |  |  |  |  |  |  |  |  |  |  |
|     | Heat treatment          |  | Delivery condition<br>+ 720 °C ± 10 °C / t = 16 h / AC |  |  |  |  |  |  |  |  |  |  |  |  |  |

Characteristics

|     |                                    |                   |                                |  |                               |  |                |  |                               |                      |  |                     |  |  |  |  |  |  |
|-----|------------------------------------|-------------------|--------------------------------|--|-------------------------------|--|----------------|--|-------------------------------|----------------------|--|---------------------|--|--|--|--|--|--|
| 8.1 | Test sample(s)                     |                   | Cut from sheet, strip or plate |  |                               |  |                |  |                               |                      |  |                     |  |  |  |  |  |  |
| 8.2 | Test piece(s)                      |                   | See EN 4700-1.                 |  |                               |  |                |  |                               |                      |  |                     |  |  |  |  |  |  |
| 8.3 | Heat treatment                     |                   | Delivery condition             |  |                               |  |                |  |                               | Use condition        |  |                     |  |  |  |  |  |  |
| 9   | Dimensions concerned               | mm                | 0,5 ≤ a ≤ 5                    |  |                               |  | 5 < a ≤ 10     |  |                               | 0,5 ≤ a ≤ 10         |  |                     |  |  |  |  |  |  |
| 10  | Thickness of cladding on each face | %                 | –                              |  |                               |  | –              |  |                               | –                    |  |                     |  |  |  |  |  |  |
| 11  | Direction of test piece            |                   | See EN 4700-1.                 |  |                               |  | See EN 4700-1. |  |                               | See EN 4700-1.       |  |                     |  |  |  |  |  |  |
| 12  | Temperature                        | θ                 | °C                             |  | Ambient                       |  |                |  | Ambient                       |                      |  | Ambient             |  |  |  |  |  |  |
| 13  | Proof stress                       | R <sub>p0,2</sub> | MPa                            |  | 200 ≤ R <sub>p0,2</sub> ≤ 390 |  |                |  | 200 ≤ R <sub>p0,2</sub> ≤ 390 |                      |  | ≥ 655               |  |  |  |  |  |  |
| 14  | T Strength                         | R <sub>m</sub>    | MPa                            |  | ≤ 665                         |  |                |  | ≤ 665                         |                      |  | ≥ 965               |  |  |  |  |  |  |
| 15  | Elongation                         | A                 | %                              |  | ≥ 35                          |  |                |  | ≥ 35                          |                      |  | ≥ 15                |  |  |  |  |  |  |
| 16  | Reduction of area                  | Z                 | %                              |  | –                             |  |                |  | –                             |                      |  | –                   |  |  |  |  |  |  |
| 17  | Hardness                           |                   | HV ≤ 195                       |  |                               |  | HB ≤ 190       |  |                               | HB ≥ 255 or HV ≥ 860 |  |                     |  |  |  |  |  |  |
| 18  | Shear strength                     | R <sub>c</sub>    | MPa                            |  | –                             |  |                |  | –                             |                      |  | –                   |  |  |  |  |  |  |
| 19  | Bending                            | k                 | –                              |  | 0,5; α = 180°                 |  |                |  | –                             |                      |  | –                   |  |  |  |  |  |  |
| 20  | Impact strength                    |                   | –                              |  |                               |  |                |  |                               |                      |  |                     |  |  |  |  |  |  |
| 21  | Temperature                        | θ                 | °C                             |  | –                             |  |                |  | –                             |                      |  | 650 <sup>b</sup>    |  |  |  |  |  |  |
| 22  | Time                               |                   | h                              |  | –                             |  |                |  | –                             |                      |  | t <sub>R</sub> ≥ 23 |  |  |  |  |  |  |
| 23  | Stress                             | σ <sub>a</sub>    | MPa                            |  | –                             |  |                |  | –                             |                      |  | –                   |  |  |  |  |  |  |
| 24  | Elongation                         | a                 | %                              |  | –                             |  |                |  | –                             |                      |  | –                   |  |  |  |  |  |  |
| 25  | Rupture stress                     | σ <sub>R</sub>    | MPa                            |  | –                             |  |                |  | –                             |                      |  | 450                 |  |  |  |  |  |  |
| 26  | Elongation at rupture              | A                 | %                              |  | –                             |  |                |  | –                             |                      |  | ≥ 2                 |  |  |  |  |  |  |
| 27  | Notes (see line 98)                |                   | a, b                           |  |                               |  |                |  |                               |                      |  |                     |  |  |  |  |  |  |