

# SVENSK STANDARD

## SS-EN 14545:2008

Fastställt/Approved: 2008-10-10

Publicerad/Published: 2008-11-03

Utgåva/Edition: 1

Språk/Language: engelska/English

ICS: 91.080.20

---

### Träkonstruktioner – Mekaniska förbindare av stål – Krav

### Timber structures – Connectors – Requirements

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-67515>

# Hitta rätt produkt och ett leveranssätt som passar dig

## Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

## Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på. På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

## Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

## Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på [sis.se](http://sis.se) och ger dig en bra bild över hur olika produkter hör ihop.

## Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

# Find the right product and the type of delivery that suits you

## Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

## Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

## Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

## Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at [sis.se](http://sis.se), provide an overview of which publications belong together.

## Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 14545:2008 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 14545:2008.

The European Standard EN 14545:2008 has the status of a Swedish Standard. This document contains the official English version of EN 14545:2008.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.  
E-mail: [sis.sales@sis.se](mailto:sis.sales@sis.se) Internet: [www.sis.se](http://www.sis.se)



EUROPEAN STANDARD

**EN 14545**

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2008

---

ICS 91.080.20

English Version

## Timber structures - Connectors - Requirements

Structures en bois - Connecteurs - Exigences

Holzbauwerke - Nicht stiftförmige Verbindungselemente -  
Anforderungen

This European Standard was approved by CEN on 9 August 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

---

<b>Contents</b>	<b>Page</b>
Foreword .....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	5
4 Symbols and abbreviations .....	5
5 Dimensions and tolerances .....	6
5.1 Method of measurement and accuracy .....	6
5.2 Length .....	6
5.3 Width .....	6
5.4 Diameter .....	6
5.5 Thickness .....	6
5.6 Other dimensions .....	7
6 Requirements .....	7
6.1 Shear plates, split ring and toothed-plate connectors .....	7
6.1.1 Materials .....	7
6.1.2 Geometry .....	7
6.1.3 Mechanical strength and stiffness .....	7
6.1.4 Corrosion protection .....	7
6.2 Punched metal plate fasteners .....	7
6.2.1 Materials .....	7
6.2.2 Geometry .....	8
6.2.3 Mechanical strength and stiffness .....	8
6.2.4 Corrosion protection .....	8
6.3 Nailing plates .....	9
6.3.1 Materials .....	9
6.3.2 Geometry .....	9
6.3.3 Mechanical strength and stiffness .....	9
6.3.4 Corrosion protection .....	9
7 Evaluation of conformity .....	10
7.1 General .....	10
7.2 Initial type testing (ITT) .....	10
7.2.1 General .....	10
7.2.2 Sampling, testing and conformity criteria .....	10
7.3 Factory production control (FPC) .....	13
7.3.1 General .....	13
7.3.2 Control .....	14
8 Marking .....	19
8.1 General .....	19
8.2 Shear plate, split ring and toothed plate connectors .....	19
8.3 Punched metal plate fasteners .....	19
8.4 Nailing plates .....	19
Annex A (normative) Expression of corrosion protection specifications .....	21
Annex B (normative) Procedures for the derivation of mechanical strength and stiffness characteristics of punched metal plate fasteners .....	22
Annex ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Directive .....	27
Bibliography .....	36

## Foreword

This document (EN 14545:2008) has been prepared by Technical Committee CEN/TC 124 “Timber Structures”, the secretariat of which is held by SFS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2009, and conflicting national standards shall be withdrawn at the latest by April 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative Annex ZA, which is an integral part of this document.

This standard also includes two normative annexes covering corrosion protection specifications for connectors covered by this standard, and procedures for the derivation of characteristic strength properties of punched metal plate fasteners.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## SS-EN 14545:2008 (E)

### 1 Scope

This European Standard specifies requirements and test methods for materials, geometry, strength, stiffness and durability aspects (i.e. corrosion protection) of connectors for use in load bearing timber structures.

Only connectors manufactured from steel are covered by this European Standard, like shear plates, split ring connectors, tooth plate connectors, punched metal plate fasteners and nailing plates. Definitions of these items are given in Clause 3.

This European Standard specifies also the evaluation of conformity procedures and includes requirements for marking of these products.

This European Standard does not cover connectors treated with fire retardants to improve their fire performance.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 912:1999, *Timber fasteners - Specifications for connectors for timber*

EN 1075:1999, *Timber structures - Test methods - Joints made with punched metal plate fasteners*

EN 1995-1-1:2004, *Eurocode 5: Design of timber structures - Part 1-1: General - Common rules and rules for buildings*

EN 10025-2, *Hot rolled products of structural steels - Part 2: Technical delivery conditions for non-alloy structural steels*

EN 10029, *Hot rolled steel plates 3 mm thick or above - Tolerances on dimensions, shape and mass*

EN 10051, *Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels - Tolerances on dimensions and shape*

EN 10088-1, *Stainless steels - Part 1: List of stainless steels.*

EN 10088-2, *Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes*

EN 10143, *Continuously hot-dip coated steel sheet and strip - Tolerances on dimensions and shape*

EN 10204, *Metallic products - Types of inspection documents*

EN 10292, *Continuously hot-dip coated strip and sheet of steels with high yield strength for cold forming - Technical delivery conditions*

EN 10326, *Continuously hot-dip coated strip and sheet of structural steels - Technical delivery conditions*

EN 10327, *Continuously hot-dip coated strip and sheet of low carbon steels for cold forming - Technical delivery conditions*

EN 13271:2001, *Timber fasteners - Characteristic load-carrying capacities and slip-moduli for connector joints*



EN 14358:2006, *Timber structures - Calculation of characteristic 5-percentile values and acceptance criteria for a sample*

EN 26891, *Timber structures - Joints made with mechanical fasteners - General principles for the determination of strength and deformation characteristics (ISO 6891:1983)*

EN 28970:1991, *Timber structures - Testing of joints made with mechanical fasteners - Requirements for wood density (ISO 8970:1989)*

EN ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461:1999)*

EN ISO 9001, *Quality management systems - Requirements (ISO 9001:2000)*

EN ISO 9445, *Continuously cold-rolled stainless steel narrow strip, wide strip, plate/sheet and cut lengths - Tolerances on dimensions and form (ISO 9445:2002)*

ISO 2081, *Metallic coatings - Electroplated coatings of zinc on iron or steel*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1995-1-1:2004 and the following apply.

#### 3.1

##### **connector**

shear plates, split ring connectors or tooth plate connectors as defined in EN 912 and punched metal plate fasteners or nailing plates as defined below

#### 3.2

##### **nailing plate**

flat rectangular metal plate containing pre-punched holes through which nails or screws are inserted

NOTE Used either on the external faces of a joint to join two or more pieces of timber of the same thickness in the same plane or on one external face of a timber member for anchoring and bracing.

#### 3.3

##### **punched metal plate fastener**

metal plate having integral projections punched out in one direction perpendicular to the base of the plate

NOTE Used to join two or more pieces of timber of the same thickness in the same plane.

#### 3.4

##### **plate thickness**

nominal steel plate thickness including the thickness of any corrosion protection coating

#### 3.5

##### **stiffness (slip modulus)**

the value of  $k_{ser}$  defined in EN 26891, calculated per fastener and per shear plane

### 4 Symbols and abbreviations

For the purposes of this standard, the symbols and abbreviations given in EN 1995-1-1:2004, EN 14358:2006, EN 13271:2001, EN 912:1999 and the following ones apply.

$A_{80}$  percentage elongation (%)  
 $d_c$  connector diameter defined in EN 13271 (mm)

## SS-EN 14545:2008 (E)

$f_{a,\alpha,\beta,k}$	characteristic punched metal plate anchorage capacity (N/mm <sup>2</sup> )
$f_{v,\alpha,k}$	characteristic punched metal plate shear capacity (N/mm)
$f_{t,k}$	characteristic punched metal plate tension capacity (N/mm)
$f_{c,k}$	characteristic punched metal plate compression capacity (N/mm)
$k_{ser}$	slip modulus per shear plane per fastener (N/mm <sup>3</sup> )
$k_s$	statistical constant defined in EN 14358
$k_1, k_2, \alpha_0$	constants used to characterise the shape of the punched metal plate anchorage capacity
$k_v, \gamma_0$	constants used to characterise the shape of the punched metal plate shear capacity
$l$	overall connector length (mm)
$t_p$	metal plate thickness (mm)
$w$	overall connector width (mm)
$\alpha$	maximum bend angle (degrees)
$\rho_k$	characteristic timber density (kg/m <sup>3</sup> )
$\rho_m$	mean timber density (kg/m <sup>3</sup> )

## 5 Dimensions and tolerances

### 5.1 Method of measurement and accuracy

Length and width of the connectors shall be measured using a device capable of achieving an accuracy of  $\pm 0,5$  mm.

Thickness and diameter shall be measured using a calibrated device capable of achieving an accuracy of  $\pm 1$  %.

### 5.2 Length

Where appropriate, the overall length of the connector shall be measured and the result declared.

When sampled in accordance with Tables 2, 3 and 4 and Tables 5, 6 and 7 and measured, the overall length shall be within  $-1$  mm/+ 2 mm or  $-1$  %/+ 2 %, whichever is the greater, of its declared value.

### 5.3 Width

Where appropriate, the overall width of the connector shall be measured and the result declared.

When sampled in accordance with Tables 2, 3 and 4 and Tables 5, 6 and 7 and measured, the overall width shall be within  $-1$  mm/+ 2 mm or  $-1$  %/+ 2 %, whichever is the greater, of its declared value.

### 5.4 Diameter

Where appropriate, the connector diameter shall be measured and the result declared.

Where tolerances on diameter are not otherwise given in EN 912, when sampled in accordance with Tables 2 and 4 and Tables 5 and 7 and measured to an accuracy of 0,01 mm, the nominal diameter shall be within  $\pm 2,5$  % of its declared value.

### 5.5 Thickness

Where appropriate, the thickness of the connector shall be measured and the result declared.

When sampled in accordance with Tables 2, 3 and 4 and Tables 5, 6 and 7 and measured, the plate thickness shall be within the tolerances specified for the parent plate material being used.

## **5.6 Other dimensions**

Where appropriate, other dimensions, e.g. tooth length, etc., shall be measured and result declared. When sampled in accordance with Tables 2 and 3 and measured these dimensions shall be within greater of  $\pm 0,75$  mm or  $\pm 2,5$  % of the specified values given.

## **6 Requirements**

### **6.1 Shear plates, split ring and toothed-plate connectors**

#### **6.1.1 Materials**

For shear plates, split ring connectors and toothed-plate connectors manufactured from steel specified in EN 912, the minimum material specifications shall be as given in that standard.

#### **6.1.2 Geometry**

For shear plates, split ring connectors and toothed-plate connectors specified in EN 912, the geometric values specified (i.e. dimensions and tolerances) shall be as given in that standard.

#### **6.1.3 Mechanical strength and stiffness**

For joints formed using shear plates, split ring connectors and toothed-plate connectors specified in EN 912, the following characteristics shall be determined according to EN 13271 for:

- a) mechanical strength: as characteristic load bearing capacity, and
- b) mechanical stiffness: as slip modulus.

NOTE The equations for the load-bearing capacity of joints made with the connectors covered by EN 912 are given in EN 1995-1-1.

#### **6.1.4 Corrosion protection**

For shear plates, split ring connectors and toothed-plate connectors covered by EN 912, the corrosion protection specifications shall be as given in that standard and shall be declared as appropriate service class according to EN 1995-1-1.

Examples of minimum corrosion protection or material specifications for different service classes are given in EN 1995-1-1.

### **6.2 Punched metal plate fasteners**

#### **6.2.1 Materials**

Punched metal plate fasteners shall be formed from the steel specifications given in Table 1 and shall have a minimum elongation ( $A_{80}$ ) of 16 %.