

SVENSK STANDARD

SS-EN 485-2:2008

Fastställt/Approved: 2008-10-27

Publicerad/Published: 2008-12-01

Utgåva/Edition: 4

Språk/Language: engelska/English

ICS: 77.120.10; 77.150.10

Aluminium och aluminiumlegeringar – Plåt och band – Del 2: Mekaniska egenskaper

Aluminium and aluminium alloys – Sheet, strip and plate – Part 2: Mechanical properties

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-67845>



SWEDISH
STANDARDS
INSTITUTE

Hitta rätt produkt och ett leveranssätt som passar dig

Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på. På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på sis.se och ger dig en bra bild över hur olika produkter hör ihop.

Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

Find the right product and the type of delivery that suits you

Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at sis.se, provide an overview of which publications belong together.

Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 485-2:2008 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 485-2:2008.

Denna standard ersätter SS-EN 485-2:2007, utgåva 3.

The European Standard EN 485-2:2008 has the status of a Swedish Standard. This document contains the official English version of EN 485-2:2008.

This standard supersedes the Swedish Standard SS-EN 485-2:2007, edition 3.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00.

Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.

E-mail: sis.sales@sis.se Internet: www.sis.se

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 485-2

October 2008

ICS 77.150.10

Supersedes EN 485-2:2007

English Version

**Aluminium and aluminium alloys - Sheet, strip and plate - Part 2:
Mechanical properties**

Aluminium et alliages d'aluminium - Tôles, bandes et tôles
épaisses - Partie 2 : Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Bänder, Bleche
und Platten - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 29 August 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Requirements	4
4	List of alloys with mechanical property limits	4
4.1	General	4
4.2	Elongation	5
4.3	List of alloys and their mechanical properties	5
Annex A (normative) Rules for rounding		83
Annex B (informative) Explanation of temper designations used in Tables 1 to 46 based on definitions of EN 515		84
Bibliography		86

Foreword

This document (EN 485-2:2008) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2009, and conflicting national standards shall be withdrawn at the latest by April 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

CEN/TC 132 affirms it is its policy that in the case when a patentee refuses to grant licences on standardised standard products under reasonable and not discriminatory conditions, then this product shall be removed from the corresponding standard.

This document supersedes EN 485-2:2007.

Within its programme of work, Technical Committee CEN/TC 132 entrusted CEN/TC 132/WG 7 "Sheets, strips and plates" to revise EN 485-2:2007.

EN 485 comprises the following parts under the general title, "Aluminium and aluminium alloys — Sheet, strip and plate":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Tolerances on dimensions and form for hot-rolled products*
- *Part 4: Tolerances on shape and dimensions for cold-rolled products*

The following changes have been made:

- In all tables, the tempers have been separated in rows.
- Table 25: Values for temper H112 have been modified.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

SS-EN 485-2:2008 (E)

1 Scope

This European Standard specifies the mechanical properties of wrought aluminium and wrought aluminium alloy sheet, strip and plate for general engineering applications.

It does not apply to semi-finished rolled products in coiled form to be subjected to further rolling (reroll stock) or to special products such as corrugated, embossed, painted, sheets and strips or to special applications such as aerospace, can stock, finstock, for which mechanical properties are specified in separate European Standards.

The chemical composition limits of the alloys are specified in EN 573-3.

Temper designations are defined in Annex B, in compliance with the provisions of EN 515.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-1, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 1: Technical conditions for inspection and delivery*

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature*

ASTM G66, *Standard Test Method for Visual Assessment of Exfoliation Corrosion Susceptibility of 5xxx Series Aluminium Alloys (ASSET test)*

ASTM G67, *Standard Test Method for Determining the Susceptibility to Intergranular Corrosion of 5xxx Series Aluminium Alloys by Mass Loss After Exposure to Nitric Acid (NAMLT test)*

3 Requirements

The mechanical properties shall be in conformity with those specified in Clause 4 or those agreed upon between purchaser and manufacturer and stated on the order document.

4 List of alloys with mechanical property limits

4.1 General

Tables 1 to 46 contain mechanical property limits values obtained by tensile testing according to EN 10002-1 after sampling and after sample preparation according to EN 485-1.

They also contain values of bend radius and hardness following sampling and test methods as described in EN 485-1. These values are for information only.

For some alloys they contain provisions related to intergranular corrosion, exfoliation corrosion or stress corrosion testing, see also EN 485-1.

4.2 Elongation

The $A_{50\text{mm}}$ value is the elongation measured over a gauge length of 50 mm and expressed in percent.

The A value for elongation is the elongation measured over a gauge length of $5,65 \sqrt{S_0}$ (where S_0 is the initial cross-sectional area of the test-piece), and expressed in percent.

4.3 List of alloys and their mechanical properties

	Page
Table 1 — Aluminium EN AW-1050A [Al 99,5]	7
Table 2 — Aluminium EN AW-1070A [Al 99,7]	9
Table 3 — Aluminium EN AW-1080A [Al 99,8(A)]	11
Table 4 — Aluminium EN AW-1200 [Al 99,0]	13
Table 5 — Alloy EN AW-2014 [Al Cu ₄ SiMg]	15
Table 6 — Alloy EN AW-2014A [Al Cu ₄ SiMg(A)]	17
Table 7 — Alloy EN AW-2017A [Al Cu ₄ MgSi(A)]	19
Table 8 — Alloy EN AW-2024 [Al Cu ₄ Mg ₁]	20
Table 9 — Alloy EN AW-2618A [Al Cu ₂ Mg _{1,5} Ni]	22
Table 10 — Alloy EN AW-3003 [Al Mn ₁ Cu]	23
Table 11 — Alloy EN AW-3004 [Al Mn ₁ Mg ₁]	25
Table 12 — Alloy EN AW-3005 [Al Mn ₁ Mg _{0,5}]	27
Table 13 — Alloy EN AW-3103 [Al Mn ₁]	29
Table 14 — Alloy EN AW-3105 [Al Mn _{0,5} Mg _{0,5}]	31
Table 15 — Alloy EN AW-4006 [Al Si ₁ Fe]	32
Table 16 — Alloy EN AW-4007 [Al Si _{1,5} Mn]	33
Table 17 — Alloy EN AW-4015 [Al Si ₂ Mn]	34
Table 18 — Alloy EN AW-5005 [Al Mg ₁ (B)], alloy EN AW-5005A [Al Mg ₁ (C)]	35
Table 19 — Alloy EN AW-5010 [AlMg 0,5Mn]	37
Table 20 — Alloy EN AW-5026 [Al Mg _{4,5} MnSiFe]	38
Table 21 — Alloy EN AW-5040 [Al Mg _{1,5} Mn]	38
Table 22 — Alloy EN AW-5049 [Al Mg ₂ Mn _{0,8}]	39
Table 23 — Alloy EN AW-5050 [Al Mg _{1,5} (C)]	41

SS-EN 485-2:2008 (E)

Table 24 — Alloy EN AW-5052 [Al Mg2,5]	43
Table 25 — Alloy EN AW-5059 [Al Mg5,5MnZnZr]	45
Table 26 — Alloy EN AW-5070 [Al Mg4MnZn]	46
Table 27 — Alloy EN AW-5083 [Al Mg4,5Mn0,7]	47
Table 28 — Alloy EN AW-5086 [Al Mg4]	50
Table 29 — Alloy EN AW-5088 [AlMg5Mn0,4]	52
Table 30 — Alloy EN AW-5154A [Al Mg3,5(A)]	53
Table 31 — Alloy EN AW-5182 [Al Mg4,5Mn0,4]	56
Table 32 — Alloy EN AW-5251 [Al Mg2Mn0,3]	57
Table 33 — Alloy EN AW-5383 [Al Mg4,5Mn0,9]	60
Table 34 — Alloy EN AW-5449 [Al Mg2Mn0,8(B)]	62
Table 35 — Alloy EN AW-5454 [Al Mg3Mn]	63
Table 36 — Alloy EN AW-5754 [Al Mg3]	66
Table 37 — Alloy EN AW-6016 [Al Si1,2Mg0,4]	68
Table 38 — Alloy EN AW-6025 [Al Mg2,5SiMnCu]	68
Table 39 — Alloy EN AW-6061 [Al Mg1SiCu]	69
Table 40 — Alloy EN AW-6082 [Al Si1MgMn]	71
Table 41 — Alloy EN AW-7010 [Al Zn6MgCu]	73
Table 42 — Alloy EN AW-7020 [Al Zn4,5Mg1]	76
Table 43 — Alloy EN AW-7021 [Al Zn5,5Mg1,5]	78
Table 44 — Alloy EN AW-7022 [Al Zn5Mg3Cu]	78
Table 45 — Alloy EN AW-7075 [Al Zn5,5MgCu]	79
Table 46 — Alloy EN AW-8011A [Al FeSi(A)]	82

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Temper	Specified thickness		Tensile strength		Yield strength		Elongation min.		Bend radius ^a		Hardness HBW ^a
	mm		R_m MPa		$R_{p0,2}$ MPa		%		180°	90°	
	over	up to	min.	max.	min.	max.	$A_{50\text{ mm}}$	A			
F ^a	≥ 2,5	150,0	60								
O	0,2	0,5	65	95	20		20		0 <i>t</i>	0 <i>t</i>	20
	0,5	1,5	65	95	20		22		0 <i>t</i>	0 <i>t</i>	20
	1,5	3,0	65	95	20		26		0 <i>t</i>	0 <i>t</i>	20
	3,0	6,0	65	95	20		29		0,5 <i>t</i>	0,5 <i>t</i>	20
	6,0	12,5	65	95	20		35		1,0 <i>t</i>	1,0 <i>t</i>	20
	12,5	80,0	65	95	20			32			20
H111	0,2	0,5	65	95	20		20		0 <i>t</i>	0 <i>t</i>	20
	0,5	1,5	65	95	20		22		0 <i>t</i>	0 <i>t</i>	20
	1,5	3,0	65	95	20		26		0 <i>t</i>	0 <i>t</i>	20
	3,0	6,0	65	95	20		29		0,5 <i>t</i>	0,5 <i>t</i>	20
	6,0	12,5	65	95	20		35		1,0 <i>t</i>	1,0 <i>t</i>	20
	12,5	80,0	65	95	20			32			20
H112	≥ 6,0	12,5	75		30		20				23
	12,5	80,0	70		25			20			22
H12	0,2	0,5	85	125	65		2		0,5 <i>t</i>	0 <i>t</i>	28
	0,5	1,5	85	125	65		4		0,5 <i>t</i>	0 <i>t</i>	28
	1,5	3,0	85	125	65		5		0,5 <i>t</i>	0,5 <i>t</i>	28
	3,0	6,0	85	125	65		7		1,0 <i>t</i>	1,0 <i>t</i>	28
	6,0	12,5	85	125	65		9			2,0 <i>t</i>	28
	12,5	40,0	85	125	65			9			28
H14	0,2	0,5	105	145	85		2		1,0 <i>t</i>	0 <i>t</i>	34
	0,5	1,5	105	145	85		2		1,0 <i>t</i>	0,5 <i>t</i>	34
	1,5	3,0	105	145	85		4		1,0 <i>t</i>	1,0 <i>t</i>	34
	3,0	6,0	105	145	85		5			1,5 <i>t</i>	34
	6,0	12,5	105	145	85		6			2,5 <i>t</i>	34
	12,5	25,0	105	145	85			6			34
H16	0,2	0,5	120	160	100		1			0,5 <i>t</i>	39
	0,5	1,5	120	160	100		2			1,0 <i>t</i>	39
	1,5	4,0	120	160	100		3			1,5 <i>t</i>	39
H18	0,2	0,5	135		120		1			1,0 <i>t</i>	42
	0,5	1,5	140		120		2			2,0 <i>t</i>	42
	1,5	3,0	140		120		2			3,0 <i>t</i>	42
H19	0,2	0,5	155		140		1				45
	0,5	1,5	150		130		1				45
	1,5	3,0	150		130		1				45