

# SVENSK STANDARD

## SS-EN 12369-3:2008

Fastställt/Approved: 2008-11-24

Publicerad/Published: 2008-12-18

Utgåva/Edition: 1

Språk/Language: engelska/English

ICS: 79.060.99

---

### **Massivträskivor – Karakteristiska värden för bärande konstruktioner – Del 3: Solida träskivor**

### **Wood-based panels – Characteristic values for structural design – Part 3: Solid-wood panels**



SWEDISH  
STANDARDS  
INSTITUTE

# Hitta rätt produkt och ett leveranssätt som passar dig

## Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

## Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på. På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

## Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

## Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på sis.se och ger dig en bra bild över hur olika produkter hör ihop.

## Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

# Find the right product and the type of delivery that suits you

## Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

## Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

## Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

## Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at sis.se, provide an overview of which publications belong together.

## Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 12369-3:2008 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 12369-3:2008.

The European Standard EN 12369-3:2008 has the status of a Swedish Standard. This document contains the official English version of EN 12369-3:2008.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.  
E-mail: [sis.sales@sis.se](mailto:sis.sales@sis.se) Internet: [www.sis.se](http://www.sis.se)



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 12369-3**

November 2008

ICS 79.060.99

English Version

## Wood-based panels - Characteristic values for structural design - Part 3: Solid-wood panels

Panneaux à base de bois - Valeurs caractéristiques pour  
conception des structures - Partie 3: Bois panneautés

Holzwerkstoffe - Charakteristische Werte für die  
Berechnung und Bemessung von Holzbauwerken - Teil 3:  
Massivholzplatten

This European Standard was approved by CEN on 12 October 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

<b>Contents</b>	<b>Page</b>
<b>Foreword</b> .....	<b>3</b>
<b>1 Scope</b> .....	<b>4</b>
<b>2 Normative references</b> .....	<b>4</b>
<b>3 Terms and definitions and symbols</b> .....	<b>4</b>
<b>3.1 Terms and definitions</b> .....	<b>4</b>
<b>3.2 Symbols</b> .....	<b>5</b>
<b>3.2.1 Main Symbols</b> .....	<b>5</b>
<b>3.2.2 Subscripts</b> .....	<b>6</b>
<b>4 General</b> .....	<b>6</b>
<b>5 Characteristic values for solid wood panels</b> .....	<b>6</b>
<b>5.1 Introduction</b> .....	<b>6</b>
<b>5.2 Load-bearing panels for use in all service classes</b> .....	<b>7</b>
<b>Annex A (informative) Presentation of characteristic values</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>10</b>

## Foreword

This document (EN 12369-3:2008) has been prepared by Technical Committee CEN/TC 112 “Wood-based panels”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2009, and conflicting national standards shall be withdrawn at the latest by May 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard is intended to be used in conjunction with EN 1995-1-1.

This European Standard is one of a series specifying characteristic values of wood-based panels for structural design. The other parts of this series are listed in the Bibliography.

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

**SS-EN 12369-3:2008 (E)****1 Scope**

This European Standard provides information on the characteristic values for use in designing structures incorporating wood-based panels. The characteristic values given are as defined in EN 1995-1-1.

This European Standard includes the characteristic values of the mechanical properties and of the raw density for solid-wood panels complying with EN 13353:2008 technical classes SWP/1 S, SWP/2 S, SWP/3 S.

**2 Normative references**

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 338, *Structural timber — Strength classes*

EN 789, *Timber structures — Test methods — Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels — Determination of characteristics values of mechanical properties and density*

EN 1995-1-1, *Eurocode 5: Design of timber structures — Part 1-1: General — Common rules and rules for buildings*

EN 13017-1, *Solid wood panels — Classification by surface appearance — Part 1: Softwood*

EN 13017-2, *Solid wood panels — Classification by surface appearance — Part 2: Hardwood*

EN 13353:2008, *Solid wood panels (SWP) — Requirements*

**3 Terms and definitions and symbols****3.1 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

**3.1.1 characteristic values****3.1.1.1 characteristic strength value**

population 5-percentile value obtained from the results of tests with a duration of 300 s at an equilibrium moisture content of the test pieces relating to a temperature of 20 °C and a relative humidity of 65 %

**3.1.1.2 characteristic stiffness value**

either the population 5-percentile or the mean value obtained of tests with a duration of 300 s at an equilibrium moisture content of the test pieces relating to a temperature of 20 °C and a relative humidity of 65 %

NOTE The stiffness values given in the Tables are mean values as these are most commonly used in design. A note in Annex A explains how to calculate the 5-percentile value.

**3.1.1.3 characteristic density**

population 5-percentile value with mass and volume corresponding to equilibrium moisture content at a temperature of 20 °C and a relative humidity of 65 %