

SVENSK STANDARD

SS-EN 12915-2:2009

Fastställt/Approved: 2009-03-19

Publicerad/Published: 2009-04-23

Utgåva/Edition: 2

Språk/Language: engelska/English

ICS: 13.060.20; 71.100.80

Produkter för beredning av dricksvatten – Aktivt kol, granulerat – Del 2: Reaktiverat granulerat aktivt kol

Products used for the treatment of water intended for human consumption – Granular activated carbon – Part 2: Reactivated granular activated carbon

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-69256>

Hitta rätt produkt och ett leveranssätt som passar dig

Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på.

På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på sis.se och ger dig en bra bild över hur olika produkter hör ihop.

Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

Find the right product and the type of delivery that suits you

Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at sis.se, provide an overview of which publications belong together.

Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 12915-2:2009 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 12915-2:2009.

Denna standard ersätter SS-EN 12915-2, utgåva 1; SS-EN 12915-2/AC:2006, utgåva 1.

The European Standard EN 12915-2:2009 has the status of a Swedish Standard. This document contains the official English version of EN 12915-2:2009.

This standard supersedes the Swedish Standard SS-EN 12915-2, edition 1; SS-EN 12915-2/AC:2006, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00.

Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.

E-mail: sis.sales@sis.se Internet: www.sis.se

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12915-2

March 2009

ICS 71.100.80

Supersedes EN 12915-2:2003

English Version

Products used for the treatment of water intended for human consumption - Granular activated carbon - Part 2: Reactivated granular activated carbon

Produits utilisés pour le traitement de l'eau destinée à la consommation humaine - Charbon actif en grains - Partie 2: Charbon actif en grains réactivé

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Granulierte Aktivkohle - Teil 2: Reaktivierte granulierte Aktivkohle

This European Standard was approved by CEN on 1 February 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Description	6
5 Physical properties.....	6
6 Chemical properties	8
7 Specific properties.....	8
8 Test methods.....	8
9 Labelling, transportation and storage	9
Annex A (informative) General information on reactivated granular activated carbon	10
Bibliography	14

Foreword

This document (EN 12915-2:2009) has been prepared by Technical Committee CEN/TC 164 "Water supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2009, and conflicting national standards shall be withdrawn at the latest by September 2009.

This document supersedes EN 12915-2:2003.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Differences between this edition and EN 12915-2:2003 are editorial to harmonize the text with other standards in this series.

The note in Clause 6 concerning the purity of the product has been reworded.

This European Standard consists of two parts, Part 1 is concerned with virgin granular activated carbon and Part 2 gives requirements for reactivated granular activated carbon.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this European Standard:

- a) this European Standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- b) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

NOTE Conformity with this European Standard does not confer or imply acceptance or approval of the product in any of the Member States of the EU or EFTA. The use of the product covered by this European Standard is subject to regulation or control by National Authorities.

1 Scope

This part of EN 12915 is applicable to reactivated granular activated carbon used for treatment of water intended for human consumption. It describes the characteristics of reactivated granular activated carbon and specifies the requirements and the corresponding test methods for reactivated granular activated carbon. It gives information on its use in water treatment.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12901:1999, *Products used for the treatment of water intended for human consumption - Inorganic supporting and filtering materials – Definitions*

EN 12902, *Products used for the treatment of water intended for human consumption - Inorganic supporting and filtering materials - Methods of test*

EN 12915-1:2009, *Products used for the treatment of water intended for human consumption – Granular activated carbon - Part 1: Virgin granular activated carbon*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12901:1999 and the following apply.

3.1

virgin activated carbon

freshly manufactured activated carbon that has not been used and has not been reactivated

[EN 12915-1:2009]

3.2

wettability

ability of granular activated carbon to be wetted when in contact with water, determined by measuring the quantity of material that sinks in water under specified conditions

[EN 12915-1:2009]

3.3

spent granular activated carbon

granular activated carbon with reduced adsorption capacity as a result of operational use

3.4

reactivation

process used to restore all or part of the adsorption capacity of spent granular activated carbon

NOTE The most common process is thermal reactivation but other methods can be used.

3.5

reactivated granular activated carbon.

spent granular activated carbon that has been subjected to reactivation

NOTE Usually, reactivated granular activated carbon is returned to the water treatment plant at which it was previously used. The delivered product can include make-up granular activated carbon and/or top-up granular activated carbon.

3.6

make-up granular activated carbon

virgin granular activated carbon, or reactivated granular activated carbon from the same water treatment plant, added to the reactivated granular activated carbon to compensate for losses during the operations of reactivation (handling, transportation and reactivation itself)

3.7

top-up granular activated carbon

virgin granular activated carbon, or reactivated granular activated carbon from the same water treatment plant, added to the reactivated granular activated carbon to compensate for losses due to operational (in-service) losses due to attrition and wash-out of granular activated carbon at the water treatment plant

4 Description

4.1 Identification

4.1.1 Chemical name(s)

Carbon.

4.1.2 Synonym or common names

Reactivated activated coal, reactivated activated charcoal, reactivated active carbon, regenerated granular activated carbon, regenerated activated coal, regenerated activated charcoal, regenerated active carbon.

4.1.3 Chemical formula

C (elementary).

4.1.4 CAS Registry Number ¹

7440-44-0.

4.1.5 EINECS reference ²

231-153-3.

4.2 Commercial forms

Granular activated carbon is a granular product; by convention not less than a mass fraction of 90 % is retained on a 180 µm aperture test sieve (see 5.3). The product can be either shaped (moulded/extruded) or irregular (non-moulded), and is available in many grades, differing in adsorption characteristics, hardness, porosity, granulometry, shape and purity.

5 Physical properties

5.1 General

The physical properties of reactivated granular activated carbon are dependent on the quality of the spent granular activated carbon as well as on the reactivation process.

¹ Chemical Abstracts Service Registry Number.

² European Inventory of Existing Commercial Chemical Substances.

5.2 Appearance

The commercial product consists of black, porous granules of irregular shape or, for moulded or extruded products, in forms such as uniform cylinders, pellets or spheres.

5.3 Particle size distribution

5.3.1 General

The particle size distribution shall be determined on samples taken at the point of reactivation. The particle size distribution shall be within the supplier's stated tolerance.

NOTE 1 Different applications can require different particle size ranges.

NOTE 2 The particle size can decrease during transportation and handling.

NOTE 3 The particle size distribution is dependent on that of the spent granular activated carbon. It can be impossible to guarantee a particular particle size distribution if the spent granular activated carbon has a substantially degraded particle size distribution.

5.3.2 Irregular product

The particle size distribution shall be described by particle size range and by mass of oversize and undersize particles according to application:

— the content of oversize plus undersize shall not exceed a mass fraction of 15 % and not more than a mass fraction of 5 % shall be undersize.

NOTE 1 Other values can be necessary for certain applications.

NOTE 2 Alternatively, particle size distribution can be described by:

— effective size: (d_{10});

— uniformity coefficient: (U);

— minimum size: (d_1).

5.3.3 Moulded/extruded product

Not more than a mass fraction of 3 % shall pass a test sieve with an aperture size as close as possible to 0,75 times the nominal particle diameter.

5.4 Wettability

The wettability shall be greater than a mass fraction of 99 %.

5.5 Bulk density packed

The bulk density packed shall be greater than or equal to 180 kg/m³.

5.6 Mechanical strength

The ball-pan hardness shall be greater than or equal to the supplier's declared value.