

SVENSK STANDARD

SS-EN 14279:2005+A1:2009

Fastställt/Approved: 2009-03-30

Publicerad/Published: 2009-05-05

Utgåva/Edition: 1

Språk/Language: engelska/English

ICS: 79.060.20; 79.080

Fanerträ (LVL) – Definitioner, klasser och specifikationer

Laminated Veneer Lumber (LVL) – Definitions, classification and specifications



SWEDISH
STANDARDS
INSTITUTE

Hitta rätt produkt och ett leveranssätt som passar dig

Standarder

Genom att följa gällande standard både effektiviserar och säkrar du ditt arbete. Många standarder ingår dessutom ofta i paket.

Tjänster

Abonnemang är tjänsten där vi uppdaterar dig med aktuella standarder när förändringar sker på dem du valt att abonnera på.

På så sätt är du säker på att du alltid arbetar efter rätt utgåva.

e-nav är vår online-tjänst som ger dig och dina kollegor tillgång till standarder ni valt att abonnera på dygnet runt. Med e-nav kan samma standard användas av flera personer samtidigt.

Leveranssätt

Du väljer hur du vill ha dina standarder levererade. Vi kan erbjuda dig dem på papper och som pdf.

Andra produkter

Vi har böcker som underlättar arbetet att följa en standard. Med våra böcker får du ökad förståelse för hur standarder ska följas och vilka fördelar den ger dig i ditt arbete. Vi tar fram många egna publikationer och fungerar även som återförsäljare. Det gör att du hos oss kan hitta över 500 unika titlar. Vi har även tekniska rapporter, specifikationer och "workshop agreement".

Matriser är en översikt på standarder och handböcker som bör läsas tillsammans. De finns på sis.se och ger dig en bra bild över hur olika produkter hör ihop.

Standardiseringsprojekt

Du kan påverka innehållet i framtida standarder genom att delta i någon av SIS ca 400 Tekniska Kommittéer.

Find the right product and the type of delivery that suits you

Standards

By complying with current standards, you can make your work more efficient and ensure reliability. Also, several of the standards are often supplied in packages.

Services

Subscription is the service that keeps you up to date with current standards when changes occur in the ones you have chosen to subscribe to. This ensures that you are always working with the right edition.

e-nav is our online service that gives you and your colleagues access to the standards you subscribe to 24 hours a day. With e-nav, the same standards can be used by several people at once.

Type of delivery

You choose how you want your standards delivered. We can supply them both on paper and as PDF files.

Other products

We have books that facilitate standards compliance. They make it easier to understand how compliance works and how this benefits you in your operation. We produce many publications of our own, and also act as retailers. This means that we have more than 500 unique titles for you to choose from. We also have technical reports, specifications and workshop agreements.

Matrices, listed at sis.se, provide an overview of which publications belong together.

Standardisation project

You can influence the content of future standards by taking part in one or other of SIS's 400 or so Technical Committees.

Europastandarden EN 14279:2004+A1:2009 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 14279:2004+A1:2009.

Denna standard ersätter SS-EN 14279:2005, utgåva 1.

The European Standard EN 14279:2004+A1:2009 has the status of a Swedish Standard. This document contains the official English version of EN 14279:2004+A1:2009.

This standard supersedes the Swedish Standard SS-EN 14279:2005, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00.

Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), tel +46 8 555 520 00.

Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

SIS Förlag AB, SE 118 80 Stockholm, Sweden. Tel: +46 8 555 523 10. Fax: +46 8 555 523 11.

E-mail: sis.sales@sis.se Internet: www.sis.se

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14279:2004+A1

March 2009

ICS 79.080; 79.060.20

Supersedes EN 14279:2004

English Version

Laminated Veneer Lumber (LVL) - Definitions, classification and specifications

Lamibois (LVL) - Définitions, classification et spécifications

Furnierschichtholz (LVL) - Definitionen, Klassifizierung und Spezifikationen

This European Standard was approved by CEN on 14 October 2004 and includes Amendment 1 approved by CEN on 3 February 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Classification.....	7
5 Requirements	7
5.1 General requirements.....	7
5.2 Formaldehyde	8
5.3 Additional requirements for LVL/1: LVL for use in dry conditions	9
5.3.1 Bonding quality.....	9
5.3.2 Biological durability	9
5.4 Additional requirements for LVL/2: LVL for use in humid conditions	9
5.4.1 Bonding quality.....	9
5.4.2 Biological durability	9
5.5 Additional requirements for LVL/3: LVL for use in exterior conditions.....	9
5.5.1 Bonding quality.....	9
5.5.2 Biological durability	9
6 Supplementary properties	9
7 Verification	10
7.1 General.....	10
7.2 External control.....	10
7.3 Factory production control.....	10
8 Marking, identification and documentation	11
Annex A (normative) Evaluation of the bonding quality of laminated veneer lumber	12
Annex B (informative) Supplementary properties.....	23
Bibliography	24

Foreword

This document (EN 14279:2004+A1:2009) has been prepared by Technical Committee CEN/TC 112 “Wood-based panels”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2009, and conflicting national standards shall be withdrawn at the latest by September 2009.

This document includes Amendment 1, approved by CEN on 2009-02-03.

This document supersedes EN 14279:2004.

The start and finish of text introduced or altered by amendment is indicated in the text by tags $\boxed{A_1}$ $\boxed{A_1}$.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

LVL is covered by two standards: EN 14374 and EN 14279 (this document), prepared under Mandates M/112 and M/113 respectively.

In the field of application of Mandate M/112 "Structural timber products and ancillaries", LVL is a material used for manufacturing structural products. In the field of application of Mandate M/113 "Wood-based panels", LVL is a product.

The fields of application are to some extent overlapping. In some cases, the standard to be used is specified in the design standards, in other cases it is up to the user to specify the standard to be used.

For relationship with Council Directive 89/106/EEC, EN 14374:2004 has its own Annex ZA.

EN 14279 applies to LVL products for general purposes as well as to LVL products for use in construction, for relationship with Council Directive 89/106/EEC, refer to Annex ZA of EN 13986:2004.

This document has been prepared in concert with CEN/TC 124. Consequently, some parts are common with EN 14374, e.g. some definitions and general specifications.

1 Scope

This document gives definitions, a classification and specifies the requirements for Laminated Veneer Lumber (LVL) for general purposes or for use in construction in dry, humid or exterior conditions.

NOTE This standard will be called up in EN 13986 for construction applications.

Annex A "Evaluation of the bonding quality of laminated veneer lumber" is normative

Information on supplementary properties is given in Annex B.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 310, *Wood-based panels — Determination of modulus of elasticity in bending and of bending strength*

EN 314-1, *Plywood — Bonding quality — Part 1: Test methods*

EN 314-2, *Plywood — Bonding quality — Part 2: Requirements*

EN 315, *Plywood — Tolerances for dimensions*

EN 322, *Wood-based panels — Determination of moisture content*

EN 323, *Wood-based panels — Determination of density*

EN 324-1, *Wood-based panels — Determination of dimensions of boards — Part 1: Determination of thickness, width and length*

EN 324-2, *Wood-based panels — Determination of dimensions of boards — Part 2: Determination of squareness and edge straightness*

EN 326-1, *Wood-based panels — Sampling, cutting and inspection — Part 1: Sampling and cutting of test pieces and expression of test results*

EN 326-2, *Wood based panels — Sampling, cutting and inspection — Part 2: Quality control in the factory*

EN 326-3, *Wood based panels — Sampling, cutting and inspection — Part 3: Inspection of an isolated lot of panels*

EN 335-3, *Durability of wood and wood-based products — Definition of hazard classes of biological attack — Part 3: Application to wood-based panels*

EN 408, *Timber structures — Structural timber and glued laminated timber — Determination of some physical and mechanical properties*

EN 635-2, *Plywood — Classification by surface appearance — Part 2: Hardwood*

EN 635-3, *Plywood — Classification by surface appearance — Part 3: Softwood*

EN 635-5, *Plywood — Classification by surface appearance — Part 5: Methods for measuring and expressing characteristics and defects*

EN 717-1, *Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the chamber method*

EN 717-2, *Wood-based panels — Determination of formaldehyde release — Part 2: Formaldehyde release by the gas analysis method*

EN 789, *Timber structures – Test methods – Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels – Determination of characteristic values of mechanical properties and density*

EN 13986:2004 *Wood-based panels for use in construction — Characteristics, evaluation of conformity and marking*

EN 14374, *Timber structures – Structural laminated veneer lumber (LVL) – Requirements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

laminated veneer lumber – LVL

layered composite of wood veneers with fibres principally in the same direction

NOTE This definition does not preclude the inclusion of cross banded veneers.

3.2

lay-up

composition of LVL with regard to number of veneers and their direction

3.3

dry conditions

conditions corresponding to service class 1 of $\overline{A_1}$ EN 1995-1-1 $\overline{A_1}$ which is characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air only exceeding 65 % for a few weeks per year
[EN 13986:2004]

3.4

humid conditions

conditions corresponding to service class 2 of $\overline{A_1}$ EN 1995-1-1 $\overline{A_1}$ which is characterised by a moisture content in the material corresponding to a temperature of 20°C and a relative humidity of the surrounding air only exceeding 85 % for a few weeks per year
[EN 13986:2004]

3.5

exterior conditions

conditions corresponding to service class 3 of $\overline{A_1}$ EN 1995-1-1 $\overline{A_1}$ which is characterised by climatic conditions leading to higher moisture contents than in service class 2
[EN 13986:2004]

4 Classification

Three types of LVL are classified:

LVL/1 for use in dry conditions

LVL/2 for use in humid conditions

LVL/3 for use in exterior conditions

5 Requirements

5.1 General requirements

LVL shall comply with the general requirements listed in Table 1 when dispatched from the production factory.

The requirements in Table 1 shall be met by the mean or percentile value given, calculated in accordance with EN 326-1.

The bending properties according to Table 1 are used for quality control purposes only and shall not be used in design calculations.

For structural applications, the characteristic values of mechanical properties shall be determined according to EN 1058 from EN 789 test results or EN 408 or methods referred to EN 14374.

NOTE If it is made known by the purchaser that the boards are intended for specific use in flooring, walls or roofing, the performance standard EN 12871 also should be considered. This might result a need for compliance with additional requirements.

Table 1 — General requirements for all LVL Types

No	Property	Test method	Requirement
1 ^a	Tolerances on dimensions — Thickness (sanded) within and between LVLs — Thickness (unsanded) within and between LVLs — Length and width	EN 324-1	EN 315
2 ^a	Edge straightness tolerance	EN 324-2	≤ 1,5 mm/m
3 ^a	Squareness tolerance	EN 324-2	≤ 2,0 mm/m
4	Moisture content	EN 322	6 % to 12 %
5	Tolerance on the mean density within a LVL	EN 323	± 10 %
6	Bending strength — major axis — minor axis	EN 310	5 th percentile Value determined at the initial testing of the product with regard to actual lay-up, density, veneer thickness and veneer grades
7	Modulus of elasticity in bending — major axis — minor axis	EN 310	
8	Bonding quality	EN 314-1 In connection with Annex A	Shear strength and wood fibre failure in accordance with EN 314-2
9	Veneer grade — Hardwood — Softwood	EN 635-5	EN 635-2 appearance class EN 635-3 appearance class

^a Certain uses of LVL can require other tolerances: see separate performance standards.