

# Teknisk rapport

## SIS-CEN/TR 16142:2011

Publicerad/Published: 2011-04-13

Utgåva/Edition: 1


Språk/Language: engelska/English

ICS: 91.100.10; 91.100.30

---

**En studie av urlakning av betong i naturlig omgivning.**

**Concrete – A study of the characteristic leaching behaviour of hardened concrete for use in the natural environment**



# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.


## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Denna tekniska rapport är inte en svensk standard. Detta dokument innehåller den engelska språkversionen av CEN/TR 16142:2011.

This Technical Report is not a Swedish Standard. This document contains the English version of CEN/TR 16142:2011.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Dokumentet är framtaget av kommittén för Cement och byggkalk, SIS/TK 185.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



TECHNICAL REPORT  
RAPPORT TECHNIQUE  
TECHNISCHER BERICHT

**CEN/TR 16142**

March 2011

---

ICS 91.100.30; 91.100.10

English Version

## Concrete - A study of the characteristic leaching behaviour of hardened concrete for use in the natural environment

Zement - Eine Untersuchung der bezeichnenden Auslaugungseigenschaften von ausgehärtetem Beton zur Verwendung in natürlichen Umgebungen

This Technical Report was approved by CEN on 20 December 2010. It has been drawn up by the Technical Committee CEN/TC 51.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

# Contents

Page

Foreword.....	4
Summary.....	5
<b>1 Introduction.....</b>	<b>6</b>
<b>Part I .....</b>	<b>8</b>
<b>2 Scope of the study.....</b>	<b>8</b>
<b>2.1 Summary of three interlaboratory studies (ILS).....</b>	<b>8</b>
<b>2.1.1 First interlaboratory study and its evaluation (ILS #1).....</b>	<b>8</b>
<b>2.1.2 Second interlaboratory study and its evaluation (ILS #2).....</b>	<b>13</b>
<b>2.1.3 Third interlaboratory study and its evaluation (ILS #3).....</b>	<b>17</b>
<b>3 The experimental precision and its implications .....</b>	<b>20</b>
<b>3.1 Introduction.....</b>	<b>20</b>
<b>3.2 Discussion of the precision estimates .....</b>	<b>22</b>
<b>4 Standardisation of the characterisation leaching method .....</b>	<b>23</b>
<b>4.1 Introduction.....</b>	<b>23</b>
<b>4.2 Potential applications for the method .....</b>	<b>23</b>
<b>4.3 Necessary developments before any method can be applied .....</b>	<b>24</b>
<b>5 Conclusions .....</b>	<b>24</b>
<b>6 Appendices.....</b>	<b>26</b>
<b>6.1 Members of the Project Team that undertook the investigations .....</b>	<b>26</b>
<b>6.2 Laboratories participating in the precision experiment in ILS #3 .....</b>	<b>26</b>
<b>7 References.....</b>	<b>27</b>
<b>Part II (informative) TEST METHOD USED IN THE STUDY FOR CHARACTERISATION OF LEACHING .....</b>	<b>28</b>
<b>1 Scope .....</b>	<b>28</b>
<b>2 Normative references .....</b>	<b>29</b>
<b>3 Terms, definitions, symbols and abbreviations .....</b>	<b>29</b>
<b>4 Materials and reagents.....</b>	<b>31</b>
<b>4.1 Materials .....</b>	<b>31</b>
<b>4.1.1 General.....</b>	<b>31</b>
<b>4.1.2 Requirements for standard specimens as test pieces (P<sub>D</sub>) and test pieces (P<sub>A</sub>) .....</b>	<b>31</b>
<b>4.1.3 Requirements for precast products (or parts thereof) as test pieces (P<sub>D</sub>) and (P<sub>A</sub>) .....</b>	<b>33</b>
<b>4.2 Reagents.....</b>	<b>33</b>
<b>4.2.1 General requirements.....</b>	<b>33</b>
<b>4.2.2 Leachant .....</b>	<b>33</b>
<b>4.2.3 Acids .....</b>	<b>33</b>
<b>4.2.4 Oxidising agent.....</b>	<b>34</b>
<b>5 Apparatus .....</b>	<b>34</b>
<b>5.1 General.....</b>	<b>34</b>
<b>5.2 Sealable tank (or bucket) .....</b>	<b>35</b>
<b>5.3 Filtering equipment.....</b>	<b>35</b>
<b>5.4 Membrane filters .....</b>	<b>35</b>
<b>5.5 Plastics bottles.....</b>	<b>35</b>
<b>5.6 pH meter .....</b>	<b>36</b>
<b>5.7 Conductivity meter .....</b>	<b>36</b>
<b>6 Determining the leaching behaviour.....</b>	<b>36</b>
<b>6.1 General.....</b>	<b>36</b>
<b>2</b>	

6.2	Principles .....	36
6.2.1	Diffusion (tank) test.....	36
6.2.2	Availability test .....	36
6.2.3	Surface area determination .....	36
6.2.4	Assessment of the characteristic leaching .....	36
6.3	Diffusion (tank) test.....	37
6.3.1	Test conditions .....	37
6.3.2	Procedure .....	37
7	Calculation of cumulative leaching and expression of results .....	38
7.1	Measured leaching of a component per leachate fraction.....	38
7.2	Measured and theoretical cumulative leaching of a component .....	39
7.2.1	General .....	39
7.2.2	Measured cumulative leaching of a component .....	39
7.2.3	Theoretical cumulative leaching of a component.....	40
8	Precision of cumulative leaching .....	40
8.1	General .....	40
8.2	Precision of the availability test.....	41
8.3	Precision of the diffusion (tank) test.....	42
9	Characterising the leaching behaviour.....	42
9.1	General .....	42
9.2	Determining the controlling leaching mechanism.....	43
9.3	Calculating the effective and mean effective diffusion coefficients of a component .....	43
9.3.1	Effective diffusion coefficient of a component .....	43
9.3.2	Mean effective diffusion coefficient of a component .....	44
9.3.3	Selection of the lowest value of the mean effective diffusion coefficient.....	44
9.4	Calculating the cumulative leaching of a component per surface unit, per time interval .....	44
9.5	Assessment of components for which no diffusion coefficient can be determined .....	45
9.6	Assessment of a diffusion coefficient.....	45
9.6.1	General .....	45
9.6.2	Assessment of the negative logarithm of the mean effective diffusion coefficient.....	45
9.7	Comparison of the mobility of a component with the free mobility of the same component in water .....	45
9.7.1	General .....	45
9.7.2	Calculating the tortuosity .....	46
9.7.3	Calculating the retention factor .....	46
9.8	Calculating the quantity leached, per mass unit, in the diffusion (tank) test .....	46
9.9	Calculating the extent of depletion of a component.....	47
10	Test report.....	47
Annex A	(normative) Determination of the available (potential) amount of a component for leaching .....	49
A.1	Procedure .....	49
A.2	Expression of results .....	49
Annex B	(normative) Determination of the surface area (A) of a test piece (PD) for use in the diffusion (tank) test .....	50
B.1	Procedure .....	50
B.2	Calculation and expression of results .....	50
Annex C	(informative) Diagrammatic representation of the diffusion (tank) leaching procedure .....	51
Annex D	(informative) Supplementary procedures for calculating the indicative upper limit for leaching for particular characteristics of the leaching behaviour .....	52
D.1	General .....	52
D.2	Diffusion-controlled leaching of components for which no diffusion coefficient can be established .....	52
Bibliography	.....	55

## Foreword

This document (CEN/TR 16142:2011) has been prepared by Technical Committee CEN/TC 51 “Cement and building limes”, the secretariat of which is held by NBN.

The work which the report refers to was developed by CEN/TC51-TC104 JWG12/TG6 in the period 1994-1999.

JWG12/TG6 has continued to work on this subject and has produced the CEN/TR 15678:2008 which is complementary to this TR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.



## Summary

At the initiative of CEN/TC 51 (Cement and building limes) and CEN/TC 104 (Concrete and related products), a task group (TG 6) of TC 51/WG 12 was convened in order to accompany or follow research work being carried out within the EC research programme which has the objective of establishing the effects, if any, of concrete on the natural environment and the potential effects of cementitious materials on the quality of drinking water.

This Technical Report deals only with developments, as officially reported, by a consortium of Dutch/German Institutes, to the European Commission in EUR 17869 EN [1], leading to a performance test method for characterising the leaching behaviour of hardened concrete for use in contact with the natural environment.

**NOTE** The standardisation of test methods for the use of cementitious materials (possibly including concrete) in contact with drinking water, although not fundamentally different in principle, is being developed within an ad hoc group of CEN/TC 164/WG 3 and will be reported elsewhere.

The protection of the natural environment and the public's health and safety are matters of major importance. Also of significant importance, however, is the efficient and sustainable use of natural and secondary materials/resources. Many of these may be used as constituents of concrete. The need to appropriately balance these two issues within the concept of sustainable construction, provided the motivation for the investigations considered in this Technical Report.

The prenormative research, underpinning this Technical Report, included a literature survey and three progressively staged interlaboratory studies (ILS). These led to the refinement of a characterisation (sequential leaching) test, comprising a tank (diffusion) test and a separate availability (maximum leaching) test. A single-extraction compliance test was not developed. A range of inorganic components/species (anionic and cationic) was targeted; some with a potential environmental significance, others of a more mechanistic relevance. Overall, a statistical and mechanistic evaluation of the results within EUR 17869 EN [1] and an environmental analysis undertaken in this Technical Report, has led to the following conclusions.

- The leaching of major components/species, which have no environmental significance (e.g. Ca, Na, K and SO<sub>4</sub>) from monolithic hardened concrete is diffusion controlled.
- Diffusion control could not be demonstrated, even after 14 days of leaching, for most environmentally relevant elements (e.g. As, Cd, Co and Cu) even from a relatively weak and porous concrete, since concentrations were at or below the limits of detections (DTL) of the sensitive instrumental techniques employed.
- Leached levels of components from monoliths are not related, in any simple or consistent manner, to the total concentrations of components present in concrete, and are, typically, orders of magnitude smaller.
- Leached levels of components from monolithic specimens are not related, in any simple or consistent manner, to amounts apparently available for leaching as indicated from a leaching test on finely ground concrete and the appropriateness of using such a test in attempting to characterise the leaching behaviour of hardened concrete is subject to continuing discussion.
- The concentration levels found in almost all leachates from the different tests were very low and often near the limit of the chemical analysis, indicating the good environmental quality of the concrete mixes tested.

- Concrete, containing a bituminous coal fly ash constituent specifically selected for its relatively high content of trace/heavy metals, and designed to represent a worst case within EN 206-1 [2] in terms of permeability, did not show significant leaching of trace/heavy metals. Most components were at concentrations below the analytical limits of detection.
- The anomalous leaching behaviour shown by specimens where the mixing water was spiked with aqueous solutions of the very mobile oxyanions of As, Cr, Cd and V, indicates that they were not representative of real concretes, as acknowledged by the research investigators.
- The disproportionate effect observed in the investigations, between the relatively large amounts of trace/heavy metals added as spikes to fresh concrete and apparently available for leaching, versus the minimal amounts actually leached, suggests that substituting standardized recycled or more marginal, but standardized, novel materials for the traditional constituents of concrete, would not significantly affect concrete's environmental compatibility.
- Subjecting the solid constituents of concrete to test, in isolation, either on the basis of their total elemental composition, or their response to an availability test, or their individual performance in a compliance test, will give no indication of their potential performance (either relative or absolute) when chemically and physically bound in hardened concrete.
- The characterisation leaching method, reproduced in Part II of this Technical Report, demonstrates such poor reproducibility (R approximately 76 % at 14d for trace metals As/Cd/Cr/V) that without much further investigation and development, it should not proceed to CEN/TS status or become the precursor to a draft compliance test or be used for any regulatory purpose.
- Concretes within the envelope of compositions permitted in the EN 206-1 [2] will have an insignificant impact upon the natural environment under conditions of natural exposure.

## 1 Introduction

Traditionally, hardened concrete has not been perceived to be a material which has contributed emissions adversely affecting the quality of the natural environment. Indeed, concrete construction in contact with the natural environment constitutes the bedrock of infrastructure and the built environment. Additionally, hardened concrete has never been shown to be responsible for any incidence of environmental pollution. Accordingly, within the range of traditional compositions used in the EU Member States, concrete's environmental service record can be taken to be unblemished.

Concrete, unlike most other construction materials, is an active material; its chemical and physical microstructure develops in a continuous process as it ages. These changes give rise to a densification of the matrix, with attendant reductions in porosity/permeability and a more efficient/effective binding of chemical species within the hydrate structures. It would be expected that concrete's leaching behaviour would also be subject to age-related changes and that this would be dissimilar to many other materials. Much research indicates that this is the case and so calls into question whether protocols, derived as in this study, from those developed for testing inert materials, are at all appropriate for concrete.

Concrete is, however, in common with other construction materials, subject to continual product development. Its compositional complexity is increasing, as constituent materials, formerly considered to be marginal, are either now in use or being considered for use. In the absence of quantitative information, some of the more marginal materials (e.g. where a total analysis reveals an apparently high heavy metal content) can give rise to concerns about their potential emission levels.

In addition, environmental regulatory activity, although at different points in the cycle in different EU Member States, is more and more subject to centralised direction via instruments such as EU Directives and mandates, and is generally increasing in its pace and scope.

Within this operational framework, standardised leaching tests, whether national or international, have taken a range of forms:

- characterisation;
- compliance;
- verification;

each of which can be used to evaluate the environmental performance/compatibility of hardened concrete, under different specified conditions using different assessment criteria. Characterisation leaching tests consist of an availability (granular or pulverized specimen) procedure and a sequential/periodic tank (monolithic specimen) procedure which together provide the means for discriminating between the several transport processes such as:

- dissolution;
- wash-off;
- diffusion;

and for predicting the rate of leaching and long term behaviour of a material.

In addition, physical characteristics such as tortuosity, which is a measure of the prolonged path along which leached components have to travel, can be calculated.

Compliance leaching tests consist of single extractions of short duration, generally without agitation, and which permit a direct comparison with regulatory limits for individual analytical components. Such tests use the prior output from characterisation tests to establish and optimise their parameters.

Verification leaching tests are essentially second order compliance tests, modified for operation in the field and used to identify/assess changes in established performance of batches of a material.

A final, and desirable, element in any authoritative procedure designed to evaluate environmental performance would be the preparation and maintenance of a certified reference material (CRM), for example, a certified reference concrete, preferably used within the context of a proficiency testing scheme (PTS), in order to monitor the performance of a laboratory and validate the accuracy of its procedures. In the case of concrete, the preparation and robust certification of a CRM is unlikely to be either attempted or to be feasible given the continuous changes in microstructure to be expected, with the likelihood of associated changes in its leaching characteristics.

Accepting that a concrete CRM is unlikely to be developed, then the preparation of a standard leachate, again for use within a PTS, would be the minimum expected for validation of laboratory performance.

It should be understood that the complete analysis of a concrete (or any of its constituents) in order to give a total elemental composition, is generally acknowledged to be of little environmental value and would be rarely undertaken in testing given that the greater proportion of most analytical components, whether environmentally significant or not, is known to be insoluble under naturally occurring exposure conditions.