

SVENSK STANDARD

SS-EN ISO 10893-10:2011

Fastställt/Approved: 2011-04-20
Publicerad/Published: 2011-05-18
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 23.040.10; 77.040.20; 77.140.75

**Oförstörande provning av stålrör –
Del 10: Automatiserad fullständig utvändig ultraljudprovning på
sömlösa och svetsade (förutom pulverbågsvetsade) stålrör för
detektering av längs- och/eller tvärgående imperfektioner
(ISO 10893-10:2011)**

**Non-destructive testing of steel tubes –
Part 10: Automated full peripheral ultrasonic testing of seamless
and welded (except submerged arc-welded) steel tubes for the
detection of longitudinal and/or transverse imperfections
(ISO 10893-10:2011)**



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.


Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN ISO 10893-10:2011 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 10893-10:2011.

Denna standard ersätter SS-EN 10246-6, utgåva 1 och SS-EN 10246-7:2005, utgåva 2.

The European Standard EN ISO 10893-10:2011 has the status of a Swedish Standard. This document contains the official version of EN ISO 10893-10:2011.

This standard supersedes the Swedish Standard SS-EN 10246-6, edition 1 and SS-EN 10246-7:2005, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Oförstörande provning, SIS/TK 125.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

**Förhållandet till övriga delar under samma huvudtitel - Utdrag ur Förord i ISO 10893-10:2011/
Relations to other parts under the same general title - Extract from the Foreword of
ISO 10893-10:2011**

ISO 10893 consists of the following parts, under the general title *Non-destructive testing of steel tubes*:

- *Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness*
- *Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections*
- *Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections*
- *Part 4: Liquid penetrant inspection of seamless and welded steel tubes for the detection of surface imperfections*
- *Part 5: Magnetic particle inspection of seamless and welded ferromagnetic steel tubes for the detection of surface imperfections*
- *Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections*
- *Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections*
- *Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections*
- *Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes*
- *Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections*
- *Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections*
- *Part 12: Automated full peripheral ultrasonic thickness testing of seamless and welded (except submerged arc-welded) steel tubes*

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 10893-10

April 2011

ICS 23.040.10; 77.040.20; 77.140.75

Supersedes EN 10246-6:1999, EN 10246-7:2005

English Version

Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10:2011)

Essais non destructifs des tubes en acier - Partie 10:
Contrôle automatisé par ultrasons sur toute la
circonférence des tubes en acier sans soudure et soudés
(sauf à l'arc immergé sous flux en poudre) pour la détection
des imperfections longitudinales et/ou transversales (ISO
10893-10:2011)

Zerstörungsfreie Prüfung von Stahlrohren - Teil 10:
Automatisierte Ultraschallprüfung nahtloser und
geschweißter (ausgenommen unterpulvergeschweißter)
Stahlrohre über den gesamten Rohrumfang zum Nachweis
von Unvollkommenheiten in Längs- und/oder Querrichtung
(ISO 10893-10:2011)

This European Standard was approved by CEN on 10 December 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General requirements	3
5 Test method	3
6 Reference tube.....	4
6.1 General	4
6.2 Types of reference notches.....	4
6.3 Dimensions of reference notches.....	5
7 Equipment calibration and checking.....	6
7.1 General	6
7.2 Adjustment of trigger/alarm level	6
7.3 Calibration check and recalibration	7
8 Acceptance	7
9 Test report.....	8
Annex A (normative) Testing on longitudinal imperfections of tubes with a ratio of the specified outside diameter to the average of the specified thickness range less than 5	9
Annex B (normative) Manual/semi-automated testing of untested ends and suspect areas	11

Foreword

This document (EN ISO 10893-10:2011) has been prepared by Technical Committee ISO/TC 17 "Steel" in collaboration with Technical Committee ECISS/TC 110 "Steel tubes, and iron and steel fittings" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2011, and conflicting national standards shall be withdrawn at the latest by October 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10246-6:1999, EN 10246-7:2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 10893-10:2011 has been approved by CEN as a EN ISO 10893-10:2011 without any modification.

Non-destructive testing of steel tubes —

Part 10:

Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections

1 Scope

This part of ISO 10893 specifies requirements for automated full peripheral ultrasonic shear wave (generated by conventional or phased array technique) testing of seamless and welded [except submerged arc-welded (SAW)] steel tubes, for the detection of longitudinal and/or transverse imperfections.

Unless otherwise specified in the purchase order, the testing method is applicable to the detection of predominantly longitudinal imperfections.

In the case of testing on longitudinal imperfections, Lamb wave testing can be applied at the discretion of the manufacturer.

For seamless tubes, by agreement between the purchaser and manufacturer, testing principles of this part of ISO 10893 can be applied to detect imperfections having other orientations.

This part of ISO 10893 is applicable to the inspection of tubes with an outside diameter greater than or equal to 10 mm, normally with an outside diameter-to-thickness ratio greater than or equal to 5.

This part of ISO 10893 can also be applicable to the testing of circular hollow sections.

NOTE For options for testing tubes with an outside diameter-to-thickness ratio less than 5 on longitudinal imperfections, see Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic inspection — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of personnel*

ISO 11484, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577 and ISO 11484 and the following apply.

3.1

reference standard

standard for the calibration of non-destructive testing equipment (e.g. drill holes, notches, recesses)

3.2

reference tube

tube or length of tube containing the reference standard(s)

3.3

reference sample

sample (e.g. segment of tube, plate or strip) containing the reference standard(s)

NOTE Only the term "reference tube" is used in this part of ISO 10893, also covering the term "reference sample".

3.4

tube

hollow long product open at both ends, of any cross-sectional shape

3.5

seamless tube

tube made by piercing a solid product to obtain a tube hollow, which is further processed, either hot or cold, into its final dimensions

3.6

welded tube

tube made by forming a hollow profile from a flat product and welding adjacent edges together, and which after welding can be further processed, either hot or cold, into its final dimensions

3.7

manufacturer

organization that manufactures products in accordance with the relevant standard(s) and declares the compliance of the delivered products with all applicable provisions of the relevant standard(s)

3.8

agreement

contractual arrangement between the manufacturer and purchaser at the time of enquiry and order

3.9

average of the specified thickness range

average of the specified thickness range given by:

$$\frac{T_{\max} + T_{\min}}{2}$$

where T_{\max} and T_{\min} are the maximum and the minimum thicknesses allowed by the standard when taking into account the wall thickness tolerances

4 General requirements

4.1 Unless otherwise specified by the product standard or agreed on by the purchaser and manufacturer, this ultrasonic testing shall be carried out on tubes after completion of all the primary production process operations (rolling, heat treating, cold and hot working, sizing and straightening, etc.).

4.2 The tubes under test shall be sufficiently straight to ensure the validity of the test. The surfaces shall be sufficiently free of foreign matter which can interfere with the validity of the test.

4.3 This test shall be carried out by suitable trained operators qualified in accordance with ISO 9712, ISO 11484 or equivalent and supervised by competent personnel nominated by the manufacturer. In the case of third-party inspection, this shall be agreed on by the purchaser and manufacturer.

The operating authorization issued by the employer shall be according to a written procedure. Non-destructive testing (NDT) operations shall be authorized by a level 3 NDT individual approved by the employer.

NOTE The definition of levels 1, 2 and 3 can be found in appropriate International Standards, e.g. ISO 9712 and ISO 11484.

5 Test method

5.1 The tubes shall be tested by using an ultrasonic shear wave technique for the detection of longitudinal and transverse imperfections. Lamb wave technique may be applied for the detection of longitudinal imperfections.

5.2 During testing, the tubes and the transducer assembly shall be moved relative to each other such that the whole of the tube surface is scanned, with coverage calculated on the dimension of the transducer(s). The relative speed of movement during testing shall not vary by more than $\pm 10\%$. There can be a short length at both tube ends which cannot be tested. Any untested ends shall be dealt with in accordance with the requirements of the appropriate product standard (see Annex B).

5.3 Unless otherwise agreed on by the purchaser and manufacturer, testing shall be carried out in two opposite directions of sound propagation for the requested type of inspection, clockwise and anticlockwise for the detection of longitudinal defects and forward and backward for the detection of transversal defects.

5.4 For the detection of longitudinal imperfections, the maximum width of each individual transducer, measured parallel to the major axis of the tube, shall be 25 mm. For U1 category tubes with an outside diameter equal to or less than 50 mm, the width of any one transducer unit shall normally be restricted to a maximum of 12,5 mm.

In the case of use of the Lamb wave technique or phased array technique, the maximum width of transducer or active aperture, measured parallel to the major axis of the tube, shall be limited to 35 mm.

For the detection of transversal imperfections, the maximum width of each individual transducer, measured perpendicular to the major axis of the tube, shall be 25 mm.

5.5 The ultrasonic test frequency of transducers that shall be used shall be in the range 1 MHz to 15 MHz for shear wave technique and in the range 0,3 MHz to 1 MHz for Lamb wave technique, depending on the product condition and properties, the thickness and surface finishing of tubes under examination.

5.6 The equipment shall be capable of classifying tubes as either acceptable or suspect, by means of an automated trigger/alarm level combined with a marking and/or sorting system.