

SVENSK STANDARD

SS-ISO 12636:2018



Fastställt/Approved: 2018-02-07
Publicerad/Published: 2018-02-08
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 01.140.40; 37.100.01; 37.100.10

Grafisk teknik – Gummidukar för offsettryck (ISO 12636:2018, IDT)

Graphic technology – Blankets for offset printing (ISO 12636:2018, IDT)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-80001065>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.



Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Den internationella standarden ISO 12636:2018 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av ISO 12636:2018.

The International Standard ISO 12636:2018 has the status of a Swedish Standard. This document contains the official version of ISO 12636:2018.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Grafisk teknik, SIS/TK 434.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
4.1 Information.....	2
4.2 Dimension.....	3
4.2.1 Thickness.....	3
4.2.2 Mean thickness.....	3
4.2.3 Accuracy of width and length.....	3
4.2.4 Plan view.....	4
4.3 Elongation.....	4
4.4 Tensile strength.....	4
4.5 Compressibility.....	4
4.6 Thickness change.....	4
4.6.1 Swelling and/or shrinkage due to printing ink component.....	4
4.6.2 Swelling and/or shrinkage due to blanket washes.....	4
4.7 Cut blanket markings.....	4
5 Test methods	4
5.1 General.....	4
5.2 Thickness.....	4
5.3 Elongation.....	5
5.4 Tensile strength.....	5
5.5 Load at specific deflection.....	5
5.6 Compressibility – Deflection.....	6
5.7 Compressibility – Indentation.....	6
5.8 Surface texture.....	8
5.9 Thickness change.....	9
5.9.1 Swelling or shrinkage after exposure to a test liquid.....	9
5.9.2 Swelling or shrinkage after recovery from exposure to a test liquid.....	9
5.9.3 Exposure conditions for printing ink ingredients.....	10
5.9.4 Exposure conditions for washes.....	10
5.9.5 Report.....	10
Bibliography	11

SS-ISO 12636:2018 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 130, *Graphic technology*.

This second edition cancels and replaces the first edition (ISO 12636:1998), which has been technically revised.

Introduction

The blanket is an essential part of every offset printing press. Its properties exert a profound influence on the mechanical conditions within the press and the visual characteristics of the prints produced. It is therefore useful to provide test methods, unified data, and tolerances for some essential properties of the blankets. This permits the suppliers to state properties of blanket types in a standardized and universally understood manner. It also helps the printer to select the appropriate blanket type for a particular press type or press condition. A further benefit is that the design of printing presses can be based on blanket data resulting from unified test methods.

Graphic technology — Blankets for offset printing

1 Scope

This document defines vocabulary and specifies test methods, characteristics, ordering and labelling information for blankets for offset printing. This document does not apply to un-tensioned or unclamped blankets for offset printing, nor offset printing sleeves used on gapless presses.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

across cylinder direction

direction of the side of the *blanket* (3.4) as intended to be applied perpendicular to the direction of rotation

3.2

around-the-cylinder direction

direction of the side of the *blanket* (3.4) as intended to be applied in the direction of the rotation

3.3

average thickness

mean of thickness measurements

3.4

blanket

composite body, consisting of coated carrier material, e.g. fabric, used for transfer of the printing ink from the form onto the material to be printed on, e.g. for offset printing

3.5

load at specific deflection

average stress of a *blanket* (3.4) under compressive force

Note 1 to entry: It is expressed in kPa.

3.6

compressibility-deflection

average thickness reduction of a *blanket* (3.4) measured under a specific pressure

Note 1 to entry: It is expressed in millimetres.

SS-ISO 12636:2018 (E)

3.7

compressibility-indentation

average depth of impression, l , in a *blanket* (3.4) measured under a specific pressure

Note 1 to entry: It is expressed in millimetres or as percentage indentation, I_p .

3.8

elongation

increase of the dimension in the *around-the-cylinder direction* (3.2) of a *blanket* (3.4) under longitudinal stress

Note 1 to entry: It is expressed in percentage of the length at a specified force per width.

3.9

packing

underlay material placed under the *blanket* (3.4)

3.10

printing surface

side of the *blanket* (3.4) that is used for the transfer of printing ink

3.11

shrinkage

decrease in thickness due to mechanical forces and decrease in all dimensions due to exposure of the blanket printing surface to a liquid

Note 1 to entry: It is expressed as a percentage of the original blanket thickness, or as an absolute thickness decrease in millimetres.

3.12

sizes

dimensions (thickness, width and length) of a cut ready-to-use *blanket* (3.4)

3.13

swelling

increase in thickness due to exposure of the blanket printing surface to a liquid

Note 1 to entry: It is expressed as a percentage of the original blanket thickness or as an absolute thickness increase in millimetres.

3.14

tensile strength

force per unit width required for breaking a *blanket* (3.4) under longitudinal stress in the *around-the-cylinder direction* (3.2)

3.15

thickness variation

difference between the greatest and the smallest thickness value in millimetres

3.16

surface texture

average roughness of blanket surface, R_a

Note 1 to entry: It is expressed in micrometres.

4 Requirements

4.1 Information

The compatibility of the blankets to either conventional, dual use or ultraviolet (UV) inks shall be documented.

The overall hardness and the microhardness are not specified in this document. They are the choice of the manufacturer. If the manufacturer provides such information, the test method shall also be documented and mentioned with the results.

The printing surface material formulation and surface texture are the choice of the manufacturer and may be stated in technical descriptions by the supplier. The surface texture may vary, e.g. cast (moulded) or ground (buffed). No specification for surface texture is given in this document. The measurement method is based on [5.8](#). The use of data to market products is the choice of the manufacturer.

The nominal (mean) thickness shall be stated in technical descriptions when ordered.

Compressibility information should be given to the user and the test method shall be indicated.

When testing the compatibility of blanket washes and an offset printing blanket, it is the option of the blanket manufacturer to report the test results using the test method according to [5.9](#) for each property.

On the non-printing side of the cut-to-size blanket, the following should be reported:

- a) blanket dimensions (average actual thickness, width and length) indicating which dimension is the around-the-cylinder direction. If the recorded thickness is nominal, it shall be stated;
- b) the batch control number;
- c) the name of the manufacturer or the supplier and the blanket brand or trade name.

4.2 Dimension

4.2.1 Thickness

The test method according to [5.2](#) shall be used. For applications with packing, the nominal thickness should be 1,68 mm or 1,95 mm. For applications without packing, the nominal thickness should be agreed upon between the supplier and the user of the product.

The thickness variations of blankets with an area not in excess of 1,5 m² shall be less than $\pm 0,02$ mm. Those of greater sizes shall be less than $\pm 0,03$ mm. No individual thickness measurement shall yield a value which deviates more than 0,05 mm from the ordered thickness.

4.2.2 Mean thickness

Mean thickness is an average of four measurements of a cut blanket where the measurements have been made on the points indicated in [Figure 1](#), namely on two diagonally opposed corners and one each at the middle of the two sides that are perpendicular to each other within a right triangle.




Figure 1 — Thickness measurement points

4.2.3 Accuracy of width and length

If one of the sides is 1 m or less, the tolerance shall be ± 3 mm; otherwise, it shall be ± 4 mm.