

# SVENSK STANDARD

## SS-EN 10164:2018



Fastställt/Approved: 2018-10-09  
Utgåva/Edition: 3  
Språk/Language: engelska/English  
ICS: 77.140.50;77.140.70

---

### **Stålprodukter med förbättrade deformationsegenskaper i tjockleksriktningen – Tekniska leveransbestämmelser**

**Steel products with improved deformation properties perpendicular to the surface of the product – Technical delivery conditions**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-80007148>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.


## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 10164:2018 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 10164:2018.

Denna standard ersätter SS-EN 10164:2005, utgåva 2.

The European Standard EN 10164:2018 has the status of a Swedish Standard. This document contains the official version of EN 10164:2018.

This standard supersedes the SS-EN 10164:2005, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Konstruktionsstål, SIS/TK 142.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](https://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

EN 10164

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2018

ICS 77.140.50; 77.140.70

Supersedes EN 10164:2004

English Version

## Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions

Aciers de construction à caractéristiques de  
déformation améliorées dans le sens perpendiculaire à  
la surface du produit - Conditions techniques de  
livraison

Stahlerzeugnisse mit verbesserten  
Verformungseigenschaften senkrecht zur  
Erzeugnisoberfläche - Technische Lieferbedingungen

This European Standard was approved by CEN on 16 May 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

**SS-EN 10164:2018 (E)**

<b>Contents</b>		<b>Page</b>
<b>European foreword</b> .....		<b>3</b>
<b>Introduction</b> .....		<b>4</b>
<b>1</b>	<b>Scope</b> .....	<b>5</b>
<b>2</b>	<b>Normative references</b> .....	<b>5</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>5</b>
<b>4</b>	<b>Designation</b> .....	<b>5</b>
<b>5</b>	<b>Information to be supplied by the purchaser</b> .....	<b>6</b>
<b>5.1</b>	<b>Mandatory information</b> .....	<b>6</b>
<b>5.2</b>	<b>Options</b> .....	<b>6</b>
<b>6</b>	<b>Requirements</b> .....	<b>6</b>
<b>6.1</b>	<b>Reduction of Area</b> .....	<b>6</b>
<b>6.2</b>	<b>Internal soundness</b> .....	<b>7</b>
<b>7</b>	<b>Inspection - Test unit for through thickness testing</b> .....	<b>7</b>
<b>7.1</b>	<b>General</b> .....	<b>7</b>
<b>7.2</b>	<b>Flat products</b> .....	<b>7</b>
<b>7.3</b>	<b>Sections</b> .....	<b>8</b>
<b>8</b>	<b>Preparation of samples and test pieces</b> .....	<b>8</b>
<b>8.1</b>	<b>Identification of samples and test pieces</b> .....	<b>8</b>
<b>8.2</b>	<b>Location and orientation of samples and test pieces</b> .....	<b>8</b>
<b>8.2.1</b>	<b>Preparation of samples</b> .....	<b>8</b>
<b>8.2.2</b>	<b>Preparation of test pieces</b> .....	<b>9</b>
<b>9</b>	<b>Test methods</b> .....	<b>13</b>
<b>9.1</b>	<b>Tensile test</b> .....	<b>13</b>
<b>9.2</b>	<b>Retest</b> .....	<b>14</b>
<b>9.3</b>	<b>Invalidation of tests</b> .....	<b>14</b>
<b>9.4</b>	<b>Sorting and reprocessing</b> .....	<b>14</b>
<b>10</b>	<b>Marking, labelling and packaging</b> .....	<b>14</b>
<b>11</b>	<b>Complaints</b> .....	<b>14</b>
<b>12</b>	<b>Options (see 5.2)</b> .....	<b>15</b>
<b>Bibliography</b> .....		<b>16</b>

## **European foreword**

This document (EN 10164:2018) has been prepared by Technical Committee ECISS/TC 103 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2019, and conflicting national standards shall be withdrawn at the latest by April 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10164:2004.

The main changes with respect to the previous edition are listed below:

- a) Normative references added and updated;
- b) Clauses 6.1 and 6.2 revised;
- c) Clause 8.2.2.2.3 c) is applicable for thicknesses  $20 \text{ mm} < t \leq 80 \text{ mm}$ ;
- d) Figure 1 and 4 revised;
- e) Clause 12 revised;
- f) Standard editorial revised.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **SS-EN 10164:2018 (E)**

### **Introduction**

Flat products and sections of steel as normally manufactured have deformation properties perpendicular to the surface (through thickness) which are different from those obtained in the surface direction. This anisotropy of the properties may lead to difficulties in welded structures, for instance lamellar tearing.

It is, however, possible to improve the through thickness properties by using additional steel making procedures.

Through thickness properties are characterized in this document by specified values for reduction of area in a through thickness tensile test.

The minimum values for reduction of area in this document cannot by themselves be regarded as ensuring safety against occurrence of lamellar tearing. Indeed, the risk of lamellar tearing is also basically influenced for instance by the type of structure, weld design and welding procedure.

However, the reduction of area is a good general guide to lamellar tear resistance, i.e. the risk of lamellar tearing decreases with increased reduction of area in the through thickness tensile test.



## 1 Scope

This document specifies deformation properties perpendicular to the surface of the product.

This document can be applied as a supplement to all product standards for flat products and sections of fully killed steels, except stainless steels. It covers products having a nominal thickness ( $t$ ) between 15 mm and 400 mm of steels with a specified minimum upper yield strength  $R_{eH}$  or proof strength  $R_{p0,2} \leq 960 \text{ MPa}$ <sup>1)</sup> for which improved through thickness properties are required.

This document can be applied to other steel types if agreed at the time of the order.

This document can be applied to products with thickness between  $10 \text{ mm} \leq t < 15 \text{ mm}$  if agreed at the time of the order. See option 1.

This document can be applied to products with thickness  $t > 400 \text{ mm}$  if agreed at the time of the order. See option 2.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

EN 10021, *General technical delivery conditions for steel products*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10306:2001, *Iron and steel - Ultrasonic testing of H beams with parallel flanges and IPE beams*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Designation

Products with requirements for improved deformation properties perpendicular to the surface of the product shall be designated as follows:

- the designation of the steel (according to the relevant product standard);
- the number of this document (EN 10164);
- the designation of the quality class (according to Table 1).

---

1)  $1 \text{ MPa} = 1 \text{ N/mm}^2$

## SS-EN 10164:2018 (E)

EXAMPLE Steel according to EN 10025-3 of the grade S355N (1.0545) with requirements for improved deformation properties perpendicular to the surface of the product according to EN 10164 of class Z25:

Steel EN 10025-3 - S355N + EN 10164 - Z25

or

Steel EN 10025-3 - 1.0545 + EN 10164 - Z25

## 5 Information to be supplied by the purchaser

### 5.1 Mandatory information

The following information shall be supplied by the purchaser at the time of the order:

- a) the designation of the steel (according to the relevant product standard);
- b) the designation of the quality class (see Table 1).

Where no specific choice is made by the purchaser, the supplier shall refer back to the purchaser.

### 5.2 Options

A number of options are specified in Clause 12. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.

## 6 Requirements

### 6.1 Reduction of Area

Table 1 gives minimum values for reduction of area for the specified quality classes.

NOTE Reduction of area (Z) is defined in EN ISO 6892-1 as:

$$\left( \frac{S_o - S_u}{S_o} \right) \times 100$$

where

$S_o$  is the original cross-sectional area of the parallel length;

$S_u$  is the minimum cross-sectional area after fracture.

The minimum values for reduction of area apply for the whole product, except that for nominal thickness  $t > 80$  mm the requirements do not apply to the mid-thickness region.

For sections, the minimum values for reduction of area apply to the flange.

**Table 1 — Quality classes and minimum values for the reduction of area**

Quality class	Reduction of area in %	
	Minimum average value of three tests	Minimum individual value
Z15	15	10
Z25	25	15
Z35	35	25

## 6.2 Internal soundness

Unless otherwise agreed at the time of the order, flat products shall meet the requirements of class S1 in accordance with EN 10160, sections shall meet the requirements of class 2.3 in accordance with EN 10306:2001, Table 2.

See options 3 and 4.

At the discretion of the manufacturer the fulfilment of the requirements on the internal soundness can be demonstrated by carrying out ultrasonic testing or through factory production control system (FPC) and statistical data.

See option 5.

NOTE Application of ultrasonic techniques does not give full information about the susceptibility to lamellar tearing.

## 7 Inspection - Test unit for through thickness testing

### 7.1 General

Each consignment shall be subdivided into test units in accordance with 7.2 and 7.3.

### 7.2 Flat products

The test units for flat products of the quality classes Z15, Z25 and Z35 based on the sulphur content of the ladle analysis are given in Table 2.