

# INTERNATIONAL STANDARD

**ISO**  
**18184**

Second edition  
2019-06

---

---

## **Textiles — Determination of antiviral activity of textile products**

*Textiles — Détermination de l'activité virucide de produits textiles*



Reference number  
ISO 18184:2019(E)

© ISO 2019

## ISO 18184:2019(E)



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>3</b>
<b>5 Virus and host cell</b> .....	<b>3</b>
<b>6 Warning</b> .....	<b>3</b>
<b>7 Apparatus</b> .....	<b>3</b>
<b>8 Sterilization of apparatus</b> .....	<b>6</b>
<b>9 Reagent and medium</b> .....	<b>6</b>
<b>10 Preparation</b> .....	<b>11</b>
10.1 Restoration of host cell from cryopreservation.....	11
10.2 Subculture of host cell.....	12
10.3 Cell culture for the infectious virus titre assay.....	13
10.4 Preparation for test virus.....	13
10.4.1 General.....	13
10.4.2 Influenza virus.....	13
10.4.3 Feline calicivirus.....	14
10.4.4 Infectivity titre of the test viruses.....	15
10.5 Preparation for test specimen.....	16
10.5.1 Control fabric.....	16
10.5.2 Preparation of test specimens.....	16
10.5.3 Sterilization of specimens.....	16
10.6 Control test.....	16
10.6.1 General.....	16
10.6.2 Verification of cytotoxicity by cell sensitivity to virus and the inactivation of antiviral activity.....	17
<b>11 Test procedure</b> .....	<b>17</b>
11.1 Preparation of specimen.....	17
11.2 Deposit of virus to the specimens.....	17
11.3 Contacting time.....	17
11.4 Wash-out of virus immediately after deposit.....	18
11.5 Wash-out of virus after contacting time.....	18
<b>12 Preparation of the series of the dilution for the virus suspension</b> .....	<b>18</b>
<b>13 Determination of the infectious titre</b> .....	<b>18</b>
13.1 Plaque assay.....	18
13.2 TCID <sub>50</sub> method.....	19
<b>14 Calculation of infectivity titre</b> .....	<b>19</b>
14.1 Plaque assay.....	19
14.2 TCID <sub>50</sub> method.....	19
14.2.1 Behrens and Karber method.....	19
14.2.2 Example of calculation.....	20
14.3 Test result.....	22
14.3.1 Verification of this test.....	22
14.3.2 Calculation of antiviral activity value.....	22
<b>15 Test report</b> .....	<b>22</b>

## ISO 18184:2019(E)

<b>Annex A</b> (informative) <b>Virus strains and host cells</b> .....	<b>23</b>
<b>Annex B</b> (normative) <b>Infectivity titre test: Plaque assay</b> .....	<b>24</b>
<b>Annex C</b> (normative) <b>Infectivity titre test: TCID<sub>50</sub> method</b> .....	<b>26</b>
<b>Annex D</b> (informative) <b>Composition of media</b> .....	<b>27</b>
<b>Annex E</b> (informative) <b>Testing method using specific pathogen free (SPF) embryonated hen's eggs</b> .....	<b>30</b>
<b>Annex F</b> (informative) <b>Antiviral efficacy — Antiviral performance of the products</b> .....	<b>35</b>
<b>Annex G</b> (informative) <b>Interlaboratory test result (1)</b> .....	<b>36</b>
<b>Annex H</b> (informative) <b>Interlaboratory test result (2)</b> .....	<b>38</b>
<b>Bibliography</b> .....	<b>41</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 38, *Textile*.

This second edition cancels and replaces the first edition (ISO 18184:2014), which has been technically revised. The main changes compared to the previous edition are as follows:

- [Clause 1](#) has been updated;
- in [Clause 5](#), viruses and host cells used in this document has been changed to examples of species;
- in [10.6](#), "Verification of cytotoxic effect" has been removed;
- [11.1](#), "Preparation of specimen" has been updated;
- [14.3.2](#), "Calculation of antiviral activity value" has been updated;
- Annex E (Additional virus: Polio virus) has been removed.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## ISO 18184:2019(E)

### Introduction

Recently, along with the global improvement in the level of living, consumers are showing the trend to seek healthcare or health protective products. Also, an increase in the people's interest for protection against epidemic diseases has been noted, as the overcrowded commuting train car where the commuters experience every day, the hospitals, nursing homes, etc.

Being supported by the processing technology of textile products to provide a high performance which has been highly developed recently, the health protective and hygiene relating products have been advancing into the market.

Because those products are relatively new and included the technical aspects out of textile technology, the testing methods have been developed by the individual producers to evaluate the product performance. That has resulted in inexistence of a unified test method, hindering for both consumers and producers a true explanation or understanding of those high functional products.

The antiviral product is one of those products and includes the technical fields of the textile technology and the biotechnology.

The demand to establish an international standard has been growing in the consumers, retailers, producers, etc. as the stakeholders in the market.

Antiviral textile products are textiles capable of reducing the number of infective virus particles that contact the surface of the textile. This document provides a quantitative test method to assess the antiviral performance of such products.

The data obtained in an objective manner by this document give the common knowledge to all the stake holders such as consumers, producers, retailers, etc. to understand the correct performance of the antiviral textile products.

There are two methods to quantify the number of infective virus, as infective virus titre in this document, which are the plaque method and the TCID<sub>50</sub> method. The method used can be selected by the experience and the convenience of each testing house. Any appropriate cellular system can be used and that the testing conditions when used should be reported.

See [Annexes G](#) and [H](#) for interlaboratory test results.

# Textiles — Determination of antiviral activity of textile products

## 1 Scope

This document specifies testing methods for the determination of the antiviral activity of the textile products against specified viruses. Due to the individual sensitivities, the results of one test virus cannot be transposed to other viruses.

The textile products include woven and knitted fabrics, fibres, yarns, braids, etc.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-F02, *Textiles — Tests for colour fastness — Part F02: Specification for cotton and viscose adjacent fabrics*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **virus**

original biological entity which has a single type of nucleic acid (DNA or RNA), specific structure that opposes the virus to living organisms with a cellular structure (prokaryotes and eukaryotes), and reproduces from its genetic material by replication within the host cell, and leads to absolute intracellular parasitism

Note 1 to entry: The virion is the infectious viral particle.

### 3.2

#### **virus activity**

ability to replicate in the susceptible and permissive host cells

### 3.3

#### **antiviral activity**

property of any substance (chemical or otherwise) producing a modification of one of the elements of the virion structure which induces the latter's inability to replicate

Note 1 to entry: Property that reduces the viral activity, generally through morphological change or structural damage to the surface protein of the virus.

Note 2 to entry: It is not necessarily to imply that the change of antigenic response or the change of constituent element is the reduction of virus infectivity.

## ISO 18184:2019(E)

### 3.4 antiviral chemicals

inorganic or organic chemicals able to reduce *virus activity* ([3.2](#))

Note 1 to entry: The organic antiviral chemicals give the change to the surface protein of virus by the chemical adsorption. The inorganic metallic antiviral substances destroy or change the morphology of the virus by the extraction of hydrogen atom in the virus protein by OH radicals which are generated by the radical reaction.

### 3.5 control fabric

fabric used to verify the stability of the test virus on a textile fabric

Note 1 to entry: The fabrics before the antivirus treatment should be used as a control fabric with the same condition described in [3.5](#).

Note 2 to entry: In the absence of a control fabric as described in Note 1, the 100 % cotton cloth described in ISO 105-F02 should be used without any chemical treatments such as the fluorescent bleach, etc.

### 3.6 control test

test to confirm that a specimen does not affect the host cell

Note 1 to entry: This test is performed as same as actual test, but without virus.

Note 2 to entry: Also referred to as control test of specimen,

### 3.7 cytopathic effect cytopathic effect (CPE) caused by virus

effect appears as morphological change or destruction of the host cells as a result of the virus multiplication

### 3.8 infectivity titre of virus

number of infectious viral particles present per unit volume in a cell lysate or in viral suspension

### 3.9 plaque

area of lysed cells in a monolayer cell culture

### 3.10 plaque forming units PFU

unit expressed as the concentration of the infectious virus per unit volume

### 3.11 plaque assay

assay to determine the infectivity *titre of virus* ([3.8](#)) from PFU by using the series of dilution

### 3.12 TCID<sub>50</sub>

50 % infectious dose of a wash-out virus suspension or the dilution of the virus suspension that induces a CPE in 50 % of cell culture units

Note 1 to entry: See [3.7](#).

### 3.13 TCID<sub>50</sub> method

assay to determine the *infectivity titre of virus* ([3.8](#)) from TCID<sub>50</sub> by using the series of dilution

### 3.14

#### cytotoxicity

morphological alteration of cells and/or their destruction or the reduction of their sensitivity to the multiplication of viruses induced by a product

## 4 Principle

The viruses are deposited onto a specimen. After specific contact time, the remaining infectious virus is counted, and the reduction rate is calculated by the comparison between the antiviral product test specimen and the control specimen by common logarithm. There are two methods to quantify the infectious virus titre. One method is the plaque assay and the other is the TCID<sub>50</sub> method. The selection of the method depends on the convenience and experience of the testing organization.

## 5 Virus and host cell

Examples of species of viruses and host cells are shown in [Annex A](#).

Other species of viruses and host cells can be used after appropriate validations, as the important virus may differ depending on target application. If the other species are used, the name of the species and the specific reason for their use shall be included in the test report.

NOTE Reference viruses are listed in EN 14476 and EN 14675.

## 6 Warning

This document calls for use of the infectious viruses or substances/procedures that may be injurious to the health/environment if appropriate conditions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety/environment at any stage.

The warning is extended as the following. The virus in the standard shall be the one of biotechnology safety level class II classified by the directives of WHO as stated. The user of this document shall have enough knowledge and experience of the microbiology. Moreover, users shall comply strictly to the safety standard of the manufacturers and the domestic regulation.

## 7 Apparatus

**7.1 High pressure steam sterilizer: Autoclave**, capable of operating at a temperature of  $(121 \pm 2)$  °C.

NOTE The autoclave is described in EN 12353.

**7.2 Dry heat sterilizer: Ovens**, capable of operating at a temperature of  $(180 \pm 2)$  °C and  $(160 \pm 2)$  °C.

NOTE The hot air ovens are described in EN 12353.

**7.3 Measuring flask**, with capacity of 1 l.

**7.4 Scale**, with the available range of 0,01 g to 100 g with accuracy of 1,0 %.

**7.5 Pipette**, of various capacities with accuracy of 10 % of the nominal volume.

**7.6 Washing machine**.

**7.7 Pipetter**, capable of mounting the glass or plastic pipettes.

## ISO 18184:2019(E)

**7.8 Micropipette**, having the most suitable volume for each use, with a tip made of glass or plastic, and with a tolerance of 0,5 % or less.

**7.9 Water bath**, capable of maintaining at a temperature of  $(37 \pm 1) ^\circ\text{C}$ ,  $(50 \pm 1) ^\circ\text{C}$  and  $(56 \pm 1) ^\circ\text{C}$ .

**7.10 Vortex<sup>®1)</sup>-type mixer**, used for microbial testing.

**7.11 Freezer**, capable of operating at a temperature of  $(-80 \pm 2) ^\circ\text{C}$  or  $(-20 \pm 2) ^\circ\text{C}$ .

**7.12 Liquid nitrogen bath**, for the preservation approximately at  $-196 ^\circ\text{C}$ .

**7.13 Membrane filtration device**, with a pore size of 0,22  $\mu\text{m}$ .

**7.14 Refrigerator**, capable of operating at a temperature between  $2 ^\circ\text{C}$  and  $8 ^\circ\text{C}$ .

**7.15 pH meter**, having an inaccuracy of calibration  $\pm 0,1$  pH units at  $(20 \pm 1) ^\circ\text{C}$ .

NOTE The pH meters are described in EN 12353.

**7.16 Inverted microscope**, capable of being used for cultured cells observation.

**7.17 Tweezers**, capable of being sterilized.

**7.18 Centrifuge**, capable of being operated at a temperature of  $(4 \pm 2) ^\circ\text{C}$ , and relative centrifugal force of approximately 1 000 g.

**7.19 Biological safety cabinet**, class II.


**7.20 Vial container**, with a capacity of 30 ml and closed with the screw cap. The gasket is made of perfluoroethylene or silicone and the cap is made of polypropylene.

**7.21 96 wells microplate with the gamma radiation sterilization**, for TCID<sub>50</sub> method.

96 wells microplates with other sterilization finish may be used after appropriate validation for the growth of cells. See [Figure 1](#).

---

1) This information is given for the convenience of users of this document and does not constitute an endorsement of ISO by this product.



**Figure 1 — 96 wells microplate for TCID<sub>50</sub> method**

**7.22 6 wells plastic plate with the gamma radiation sterilization**, for plaque assay.

6 wells plates with other sterilization finish may be used after appropriate validation for the growth of cells. See [Figure 2](#).



**Figure 2 — 6 wells plastic plate for plaque assay**

**7.23 Flask**, for cell culture use with the gamma radiation sterilization finish, with an adherent type, a cell culture area of 75 cm<sup>2</sup> and with the vent cap. The vent cap can exchange abacterial air through 0,2 µm filter. See [Figure 3](#).

Flask with other sterilization finish may be used after appropriate validation for the growth of cells.