

SVENSK STANDARD

SS-EN 16809-1:2019

**Värmeisoleringsprodukter för byggnader – In situ-formad lösfallnadsisolering av expanderad polystyren (EPS) pärlor och bundna expanderade polystyrenpärlor –
Del 1: Egenskapsredovisning för bundna och lösfallnadsprodukter före installation**

**Thermal insulation products of buildings – In-situ formed products from loose-fill expanded polystyrene (EPS) beads and bonded expanded polystyrene beads –
Part 1: Specification for the bonded and loose-fill products**



SIS Svenska
Institutet för
Standarder

Språk: engelska/English
Utgåva: 1

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-80018795>

Den här standarden kan hjälpa dig att effektivisera och kvalitetssäkra ditt arbete. SIS har fler tjänster att erbjuda dig för att underlätta tillämpningen av standarder i din verksamhet.

SIS Abonnemang

Snabb och enkel åtkomst till gällande standard med SIS Abonnemang, en prenumerationstjänst genom vilken din organisation får tillgång till all världens standarder, senaste uppdateringarna och där hela din organisation kan ta del av innehållet i prenumerationen.

Utbildning, event och publikationer

Vi erbjuder även utbildningar, rådgivning och event kring våra mest sålda standarder och frågor kopplade till utveckling av standarder. Vi ger också ut handböcker som underlättar ditt arbete med att använda en specifik standard.

Vill du delta i ett standardiseringsprojekt?

Genom att delta som expert i någon av SIS 300 tekniska kommittéer inom CEN (europeisk standardisering) och/eller ISO (internationell standardisering) har du möjlighet att påverka standardiseringsarbetet i frågor som är viktiga för din organisation. Välkommen att kontakta SIS för att få veta mer!

Kontakt

Skriv till kundservice@sis.se, besök [sis.se](https://www.sis.se) eller ring 08 - 555 523 10

© Copyright/Upphovsrätten till denna produkt tillhör Svenska institutet för standarder, Stockholm, Sverige. Upphovsrätten och användningen av denna produkt regleras i slutanvändarlicensen som återfinns på [sis.se/slutanvandarlicens](https://www.sis.se/slutanvandarlicens) och som du automatiskt blir bunden av när du använder produkten. För ordlista och förkortningar se [sis.se/ordlista](https://www.sis.se/ordlista).

© Copyright Svenska institutet för standarder, Stockholm, Sweden. All rights reserved. The copyright and use of this product is governed by the end-user licence agreement which you automatically will be bound to when using the product. You will find the licence at [sis.se/enduserlicenseagreement](https://www.sis.se/enduserlicenseagreement).

Upplysningar om sakinnehållet i standarden lämnas av Svenska institutet för standarder, telefon 08 - 555 520 00. Standarder kan beställas hos SIS som även lämnar allmänna upplysningar om svensk och utländsk standard.

Standarden är framtagen av kommittén för Material och konstruktioner, SIS/TK 189/AG 01.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

Europastandarden EN 16809-1:2019 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 16809-1:2019.

The European Standard EN 16809-1:2019 has the status of a Swedish Standard. This document contains the official version of EN 16809-1:2019.

EUROPEAN STANDARD

EN 16809-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2019

ICS 91.100.60

English Version

Thermal insulation products of buildings - In-situ formed products from loose-fill expanded polystyrene (EPS) beads and bonded expanded polystyrene beads - Part 1: Specification for the bonded and loose-fill products before installation

Produits isolants thermiques destinés aux bâtiments - Produits formés sur place à partir de billes en polystyrène expansé (PSE) en vrac et de billes en polystyrène expansé liées - Partie 1 : Spécification des produits avec et sans liant avant mise en œuvre

Wärmedämmstoffe für Gebäude - An der Verwendungsstelle hergestellte Produkte aus losen expandierten Polystyrolkugeln (EPS) und gebundenen expandierten Polystyrolkugeln - Teil 1: Spezifikation für gebundene und lose Schütt- und Einblasdämmstoffe vor dem Einbau

This European Standard was approved by CEN on 23 September 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

SS-EN 16809-1:2019 (E)

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms, definitions, symbols and abbreviations	5
4 Requirements	7
5 Test methods	9
6 Designation code	11
7 Assessment and verification of the constancy of performance	11
8 Marking and labelling	12
Annex A (normative) Determination of the declared values of thermal resistance and thermal conductivity	13
Annex B (normative) Product type determination (PTD) and factory production control (FPC)	16
Annex C (normative) Specimen preparation method for thermal resistance and thermal conductivity test	20
Annex D (normative) Preparing samples for testing for reaction to fire of products	23
Annex E (normative) Specimen preparation method for water absorption test and water vapour diffusion resistance test	24
Annex F (normative) Specimen preparation method for density measurement	25
Annex G (normative) Determination of settlement for EPS loose-fill product	26
Annex H (informative) Masonry cavity walls - Method for determining suitable spacings for blowing holes	28
Bibliography	30

European foreword

This document (EN 16809-1:2019) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2020, and conflicting national standards shall be withdrawn at the latest by August 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

EN 16809-1, *Thermal insulation products for buildings — In situ formed products from loose-fill expanded polystyrene (EPS) beads and bonded expanded polystyrene beads*, consists of two parts which form a package. The first part (this document), covers the products, which are placed on the market. The second part covers the specification for the installed products. Both parts need to be used for the application of the insulation product in the end-use applications covered by EN 16809-2.

The reduction in energy used and emissions produced during the installed life of insulation products exceeds by far the energy used and emissions made during the production and disposal processes.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SS-EN 16809-1:2019 (E)

1 Scope

This document specifies the requirements for products of loose-filled expanded polystyrene (EPS) beads and bonded expanded polystyrene beads for *in situ* installation in masonry cavity walls and frame constructions.

This document is a specification for the insulation products before installation. It describes the product characteristics and includes procedures for testing, marking and labelling.

This document does not specify the required level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application are to be found in regulations or non-conflicting standards.

NOTE To avoid water penetration in masonry walls special tests adjusted to local climate could be needed.

This document does not cover factory made expanded polystyrene (EPS) insulation products and factory made or *in situ* products intended to be used for the insulation of building equipment and industrial installations.

Products with a declared thermal resistance lower than $0,25 \text{ m}^2 \cdot \text{K}/\text{W}$ or a declared thermal conductivity greater than $0,060 \text{ W}/(\text{m} \cdot \text{K})$ at $10 \text{ }^\circ\text{C}$ are not covered by this document.

This document does not cover products intended for airborne sound insulation and for acoustic absorption applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 933-1, *Tests for geometrical properties of aggregates – Part 1: Determination of particle size distribution – Sieving method*

EN 1602, *Thermal insulating products for building applications — Determination of the apparent density*

EN 1609, *Thermal insulating products for building applications — Determination of short term water absorption by partial immersion*

EN 12086, *Thermal insulating products for building applications – Determination of water vapour transmission properties*

EN 12667, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance*

EN 13172, *Thermal insulation products — Evaluation of conformity*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13820, *Thermal insulating materials for building applications — Determination of organic content*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN 15715, *Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing — Factory made products*

EN ISO 1182, *Reaction to fire tests for products — Non-combustibility test (ISO 1182)*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2)*

ISO 16269-6:2014, *Statistical interpretation of data — Part 6: determination of statistical tolerance intervals*

3 Terms, definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1.1

expanded polystyrene beads

insulation material consisting of beads manufactured from expandable polystyrene or one of its copolymers with an air filled closed cellular structure

Note 1 to entry: Beads can be made from non-infrared absorbing or infrared absorbing raw material.

3.1.2

blowing hole

hole, cut or formed, in a masonry cavity wall or frame construction, through which the EPS beads are blown

3.1.3

frame construction

walls with wood or metal studs, sloping roof with insulation between rafters, the larger surfaces covered by facings

3.1.4

settlement

decrease of installed insulation height in cavities and frame constructions with time, expressed as a percentage of the initial installed height

SS-EN 16809-1:2019 (E)

3.2 Symbols and abbreviations

Symbols used in this document:

$\lambda_{90/90}$	is the 90 % fractile with a confidence level of 90 % for the thermal conductivity	W/(m·K)
λ_D	is the declared thermal conductivity	W/(m·K)
λ_i	is one test result of thermal conductivity	W/(m·K)
λ_{mean}	is the mean thermal conductivity	W/(m·K)
ρ_D	is the declared density	kg/m ³
A	is the area of the test specimen	m ²
d	is the thickness of the test specimen	mm
D	is the diameter of the beads	mm
n	is the number of test results	-
$P_{90/90}$	is the 90 % fractile with a confidence level of 90 % for the thermal resistance	m ² ·K/W
R_D	is the declared thermal resistance	m ² ·K/W
R_i	is one test result of thermal resistance	m ² ·K/W
s_λ	is the estimate of the standard deviation of the thermal conductivity	W/(m·K)
s_R	is the estimate of the standard deviation of the thermal resistance	m ² ·K/W
s_ρ	is the estimate of the standard deviation of the density	kg/m ³
W_p	is the short-term water absorption	kg/m ²
Q_{nom}	is the nominal weight of the quantity delivered	kg
MU	is the symbol for the declared value for water vapour diffusion resistance factor	
S	is the symbol for the declared class for settlement	
WS	is the symbol of the declared level for short-term water absorption	

Abbreviations used in this document:

EPS	Expanded PolyStyrene
AVCP	Assessment and Verification of Constancy of Performance (previously named Attestation of Conformity)
DoP	Declaration of Performance
FPC	Factory Production Control
PTD	Product Type Determination (previously named ITT for Initial Type Test)
RtF	Reaction to Fire
ThIB	Thermal Insulation for Buildings

4 Requirements

4.1 General

Product properties shall be assessed in accordance with Clause 5. To comply with this standard, products shall meet the requirements of 4.2, and the requirements of 4.3 as appropriate.

One test result on a product property is the average of the measured values on the number of test specimens given in Table 1.

4.2 For all applications

4.2.1 Thermal conductivity – Thermal resistance

Thermal resistance and thermal conductivity shall be based upon measurements carried out in accordance with EN 12667 or EN 12939 for thick products

The thermal values shall be determined in accordance with Annex A and declared by the manufacturer, according to the following:

- the reference mean temperature shall be 10 °C;
- the measured values shall be expressed with three significant figures;
- the thermal resistance, R_D , shall always be declared. The thermal conductivity, λ_D , shall be declared where possible;
- the thermal resistance, R_D , and the thermal conductivity, λ_D , shall be given as limit values representing at least 90 % of the production determined with a confidence level of 90 %;
- the value of thermal conductivity $\lambda_{90/90}$ shall be rounded upwards to the nearest 0,001 W/(m·K) and declared in levels with steps of 0,001 W/(m·K);
- the declared thermal resistance, R_D , shall be calculated from the insulation thickness and the corresponding thermal conductivity, $\lambda_{90/90}$ (see Note below);
- The value of thermal resistance, R_D , shall be rounded downward to the nearest 0,05 m²·K/W and declared in levels with steps of 0,05 m²·K/W.

NOTE The declaration of the installed thermal resistance for blown EPS beads is described in EN 16809-2.

4.2.2 Density of the sale unit

The density of the material in one sale unit, measured according to EN 1602, shall not be lower than the minimum density declared by the manufacturer.

4.2.3 Expanded bead size

The bead size is measured according to EN 933-1.

NOTE 1 The bead size normally is between 1 and 10 mm.

NOTE 2 In masonry cavity wall insulation and frame insulation, the bead size depends on what is suitable for the way the beads are injected into the cavity.