

SVENSK STANDARD

SS-EN 636:2012+A1:2015

Fastställt/Approved: 2015-03-22
Publicerad/Published: 2015-04-01
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 79.060.10; 92.300.30; 94.350

Plywood – Specifikationer

Plywood – Specifications

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8013554>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 636:2012+A1:2015 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 636:2012+A1:2015.

Denna standard ersätter SS-EN 636:2012, utgåva 2.

The European Standard EN 636:2012+A1:2015 has the status of a Swedish Standard. This document contains the official English version of EN 636:2012+A1:2015.

This standard supersedes the Swedish Standard SS-EN 636:2012, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Träbaserade skivor, SIS/TK 182/AG 8.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 636:2012+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2015

ICS 79.060.10

Supersedes EN 636:2012

English Version

Plywood - Specifications

Contreplaqué - Exigences

Sperrholz - Anforderungen

This European Standard was approved by CEN on 11 August 2012 and includes Amendment 1 approved by CEN on 27 December 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	7
4 Symbols and subscripts	7
5 Classification system	8
6 General requirements.....	9
6.1 Tolerances on dimensions	9
6.2 Mechanical characteristics	9
6.2.1 General purpose (non-structural application)	9
6.2.2 Structural application	10
6.3 Formaldehyde release	10
6.3.1 Classification.....	10
6.3.2 Conditioning of test pieces.....	11
7 Requirements for plywood for use in dry conditions	11
7.1 Bonding quality.....	11
7.2 Biological durability	11
8 Requirements for plywood for use in humid conditions	12
8.1 Bonding quality.....	12
8.2 Biological durability	12
9 Requirements for plywood for use in exterior conditions.....	12
9.1 Bonding quality.....	12
9.2 Biological durability	12
10 Supplementary properties	12
11 Verification of compliance	12
11.1 General.....	12
11.2 External control.....	12
11.3 Factory production control.....	13
12 Marking, identification and documentation	14
12.1 Boards marketed within the European Economic area for construction applications	14
12.2 Other boards	14
Annex A (normative) Supplementary properties	15
Annex B (informative) Durability of wood and wood-based products - Definition of Use classes of biological attack- Application to plywood	16
B.1 General.....	16
B.2 Use class1	16
B.3 Use class 2	16
B.4 Use class 3	16
B.5 Use class 4	17
B.6 Use class 5	17

B.7	Summary of Use classes for plywood.....	18
B.8	Guide for the application to plywood	19
B.8.1	Introduction.....	19
B.8.2	General decision making	19
B.8.3	General precautions	19
B.8.4	Durability (inherent or conferred) of plywood	20
	Bibliography.....	21

Foreword

This document (EN 636:2012+A1:2015) has been prepared by Technical Committee CEN/TC 112 “Wood-based panels”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2015, and conflicting national standards shall be withdrawn at the latest by September 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1, approved by CEN on 2014-12-27.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document supersedes A1 EN 636:2012 A1.

A1 Deleted text A1

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

A1) This European Standard specifies the requirements for plywood, as defined in EN 313-2, for both general purpose use (non-structural application) and structural application in dry, humid or exterior conditions. It also gives a classification system based on the bending properties.

NOTE 1 This European Standard is referenced in EN 13986 for construction applications.

This standard can be appropriately applied for all plywood, including overlaid and coated plywood, but it does not cover materials or processes used for overlaying or coating. Neither does it cover any materials or processes applied in relation to enhancement of biological durability.

NOTE 2 For additional guidance on biological durability and the potential need for preservative treatment, according to application and serviceability, reference can be made to CEN/TS 1099.

The values listed under Clause 4 relate only to product properties; they are not 'characteristic values' and are not to be used in design calculations.

NOTE 3 Characteristic values (i.e. for use in design calculation according to EN 1995-1-1) are given either in EN 12369-2 which is based on the classification system given in this standard or by the manufacturer based on testing according to EN 789, EN 1058 and ENV 1156.

Additional information on supplementary properties for certain applications is also given. **A1)**

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 310, *Wood-based panels - Determination of modulus of elasticity in bending and of bending strength*

EN 314-1, *Plywood - Bonding quality - Part 1: Test methods*

EN 314-2, *Plywood - Bonding quality - Part 2: Requirements*

EN 315, *Plywood - Tolerances for dimensions*

EN 318, *Wood based panels - Determination of dimensional changes associated with changes in relative humidity*

EN 322, *Wood-based panels - Determination of moisture content*

EN 323, *Wood-based panels - Determination of density*

EN 324-1, *Wood-based panels - Determination of dimensions of boards - Part 1: Determination of thickness, width and length*

EN 324-2, *Wood-based panels - Determination of dimensions of boards - Part 2: Determination of squareness and edge straightness*

EN 326-1, *Wood-based panels - Sampling, cutting and inspection - Part 1: Sampling and cutting of test pieces and expression of test results*

EN 326-2, *Wood-based panels - Sampling, cutting and inspection - Part 2: Initial type testing and factory production control*

EN 326-3, *Wood-based panels - Sampling, cutting and inspection - Part 3: Inspection of an isolated lot of panels*

EN 335-3:1995, *Durability of wood and wood-based products — Definition of hazard classes of biological attack —Part 3: Application to wood-based panels*

EN 594, *Timber structures - Test methods - Racking strength and stiffness of timber frame wall panels*

EN 596, *Timber structures - Test methods - Soft body impact test of timber framed walls*

EN 635-1, *Plywood - Classification by surface appearance - Part 1: General*

EN 635-2, *Plywood - Classification by surface appearance - Part 2: Hardwood*

EN 635-3, *Plywood - Classification by surface appearance - Part 3: Softwood*

CEN/TS 635-4, *Plywood - Classification by surface appearance - Part 4: Parameters of ability for finishing, guideline*

EN 635-5, *Plywood - Classification by surface appearance - Part 5: Methods for measuring and expressing characteristics and defects*

EN 717-1, *Wood-based panels - Determination of formaldehyde release - Part 1: Formaldehyde emission by the chamber method*

EN 717-2, *Wood-based panels - Determination of formaldehyde release - Part 2: Formaldehyde release by the gas analysis method*

EN 789, *Timber structures - Test methods - Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels - Determination of characteristic 5-percentile values and characteristic mean values*

ENV 1156, *Wood-based panels — Determination of duration load and creep factors*

EN 1195, *Timber structures - Test methods - Performance of structural floor decking*

EN 12369-2, *Wood-based panels - Characteristic values for structural design - Part 2: Plywood*

EN 13446, *Wood-based panels - Determination of withdrawal capacity of fasteners*

EN 13810-1, *Wood-based panels - Floating floors - Part 1: Performance specifications and requirements*

CEN/TS 13810-2, *Wood-based panels - Floating floors - Part 2: Test methods*

EN 13986, *Wood-based panels for use in construction - Characteristics, evaluation of conformity and marking*

EN 14272, *Plywood - Calculation method for some mechanical properties*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

plywood for use in dry conditions

plywood to be used in conditions characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air only exceeding 65 % for a few weeks per year

Note 1 to entry: These conditions correspond with Service Class 1 according to EN 1995–1-1.

Note 2 to entry: Boards of this type are suitable for use in Use Class 1 of EN 335–3.

3.2

plywood for use in humid conditions

plywood to be used in conditions characterised by a moisture content in the material corresponding to a temperature of 20 °C and relative humidity of the surrounding air only exceeding 85 % for a few weeks per year

Note 1 to entry: These conditions correspond with Service Class 2 according to EN 1995–1-1.

Note 2 to entry: Boards of this type are suitable for use in Use Class 1 and 2 of EN 335–3.

Note 3 to entry: This type of plywood is appropriate for protected external applications (e.g. behind cladding or under roof coverings), but is also capable of resisting weather exposure for short periods (e.g. when exposed during the construction). It is also suitable for interior situations where the service moisture condition is raised above humidity of dry conditions.

3.3

plywood for use in exterior conditions

plywood to be used in climatic conditions leading to higher moisture contents than in service class 2

Note 1 to entry: These conditions correspond with Service Class 3 according to EN 1995–1-1.

Note 2 to entry: Boards of this type are suitable for use in Use Class 1, 2 and 3 of EN 335–3.

Note 3 to entry: This type of plywood is capable of withstanding exposure to weathering conditions and liquid water, or water vapour in a damp but ventilated location, under consideration of 9.2.

4 Symbols and subscripts

E modulus of elasticity (defined as stiffness in EN 1995-1-1), in Newton per square millimetre

E class of modulus of elasticity in bending

f strength in Newton per square millimetre

F class of bending strength

m bending

0 in the direction of the grain of the outer layer of plywood

90 perpendicular to the grain of the outer layer of plywood