

# SVENSK STANDARD

## SS-EN ISO 4499-4:2016



Fastställt/Approved: 2016-03-22  
Publicerad/Published: 2016-03-29  
Utgåva/Edition: 1  
Språk/Language: engelska/English  
ICS: 77.040.99; 77.160

---

### **Hårdmetall – Metallografisk bestämning av mikrostruktur – Del 4: Karakterisering av porositet, koldefekter och mängd etafas (ISO 4499-4:2016)**

### **Hardmetals – Metallographic determination of microstructure – Part 4: Characterisation of porosity, carbon defects and eta-phase content (ISO 4499-4:2016)**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-8019626>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN ISO 4499-4:2016 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 4499-4:2016.

Denna standard ersätter SS-EN 24505, utgåva 1.

The European Standard EN ISO 4499-4:2016 has the status of a Swedish Standard. This document contains the official English version of EN ISO 4499-4:2016.

This standard supersedes the Swedish Standard SS-EN 24505, edition 1.

**Förhållandet till övriga delar under samma huvudtitel - Utdrag ur Förord i ISO 4499-4:2016/  
Relations to other parts under the same general title - Extract from the Foreword of ISO 4499-4:2016**

ISO 4499 consists of the following parts, under the general title *Hardmetals — Metallographic determination of microstructure*:

- Part 1: *Photomicrographs and description*
- Part 2: *Measurement of WC grain size*
- Part 3: *Measurement of microstructural features in Ti (C,N) and WC/cubic carbide based hardmetals*
- Part 4: *Characterisation of porosity, carbon defects and eta-phase content*

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Pulvermetallurgi, SIS/TK 133.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

EN ISO 4499-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2016

ICS 77.040.99; 77.160

Supersedes EN 24505:1993

English Version

## Hardmetals - Metallographic determination of microstructure - Part 4: Characterisation of porosity, carbon defects and eta-phase content (ISO 4499-4:2016)

Métaux-durs - Détermination métallographique de la  
microstructure - Partie 4: Caractérisation de la  
porosité, des défauts carbone et de la teneur en phase  
êta (ISO 4499-4:2016)

Hartmetalle - Metallographische Bestimmung der  
Mikrostruktur - Teil 4: Charakterisierung von  
Porosität, Kohlenstofffehlern und Anteil an Eta-Phase  
(ISO 4499-4:2016)

This European Standard was approved by CEN on 4 February 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

# Contents

Page

<b>European foreword</b> .....	<b>iii</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Symbols and Units</b> .....	<b>1</b>
<b>5 Principle</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Calibration of measurement apparatus</b> .....	<b>2</b>
<b>8 Preparation of test samples</b> .....	<b>2</b>
8.1 Methods of preparation.....	2
8.2 Characterisation of porosity and carbon (graphite) defects.....	3
8.3 Characterisation of eta-phase.....	3
<b>9 Procedure</b> .....	<b>3</b>
9.1 General.....	3
9.2 Determination of porosity.....	3
9.3 Determination of carbon defects.....	4
9.4 Determination of the $\eta$ -phase (eta-phase).....	7
<b>10 Uncertainty of measurement</b> .....	<b>9</b>
<b>11 Test report</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>10</b>

## European foreword

This document (EN ISO 4499-4:2016) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 24505:1993.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 4499-4:2016 has been approved by CEN as EN ISO 4499-4:2016 without any modification.

## Introduction

In standard WC/Co hardmetals, the chemistry, magnetic properties and density are generally controlled so that only two phases WC and Co are present.<sup>[1][2][3]</sup> The Co phase is an alloy and contains some W and C in solid solution. The WC phase is stoichiometric. If the composition is either high or low in total carbon content, then it is possible to see a third phase in the structure. For high C, this is graphite; for low C, it is eta phase ( $\eta$ ); typically, an  $M_6C$  or  $M_{12}C$  carbide where M is  $(Co_xW_y)$ . This part of ISO 4499 is concerned with the detection and measurement of these microstructural features together with the measurement of porosity levels. Porosity is important since these materials are manufactured by a powder metallurgical route and although the technique of liquid phase sintering is used to consolidate the multiphase structure, low levels of porosity can arise in some instances and affect properties such as density and strength.



# Hardmetals — Metallographic determination of microstructure —

## Part 4: Characterisation of porosity, carbon defects and eta-phase content

### 1 Scope

This part of ISO 4499 specifies methods for the metallographic determination of the presence, type, and distribution of porosity, uncombined carbon and eta-phase in hardmetals.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4499-2:2008, *Hardmetals — Metallographic determination of microstructure — Part 2: Measurement of WC grain size*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### carbon defects

macroscopic precipitates of carbon (graphite) which can be in the form of large angular rosettes or small flakes

#### 3.2

##### eta-phase

##### $\eta$ -phase

cubic carbide based on M<sub>6</sub>C or M<sub>12</sub>C structure where M is a mixture of Co and W usually in equal proportions; and which can be present as large (up to 100  $\mu\text{m}$  diameter) rosettes or small micrometre-sized particles

### 4 Symbols and Units

ECD Equivalent Circle Diameter of a specified phase, in micrometres ( $\mu\text{m}$ )

$L$  total line length in a specified phase, in millimetres (mm)

$l_i$  measured length of individual intercepts in a specified phase, in micrometres ( $\mu\text{m}$ )

$\sum l_i$  sum of the measured length of each individual intercept

$l_x$  arithmetic mean linear intercept in phase  $x$ , in micrometres ( $\mu\text{m}$ )

$N$  number of eta-phase particles intercepted

$m$  magnification

$m_{\max}$  maximum magnification

$m_{\min}$  minimum magnification

## 5 Principle

This part of ISO 4499 handles the following key issues:

- description of methods for sample preparation;
- description of how to identify and measure the relevant feature.

In some cases, the approach adopted in ISO 4499-2 and ISO 4499-3 can be useful, whereby the intercept method is used on microphotographs of the structure for relevant quantification of feature size, such as eta-phase or graphite rosettes.

## 6 Apparatus

**6.1 Metallographic optical microscope**, or other suitable equipment permitting observations and measurements on a screen up to the required magnification.

**6.2 Scanning electron microscope (SEM)**, permitting observations and measurements of features too small to be resolved with an optical microscope.

**6.3 Equipment for preparation of test-piece sections.**

## 7 Calibration of measurement apparatus

For reliable quantitative measurements, images shall be calibrated against a stage micrometre or scale traceable to a National Reference Standard. The most commonly used stage micrometres for SEMs are the SIRA grids. These are ruled lines which form a grid and are available with 19,7 lines/mm and 2 160 lines/mm. However, these shall also be calibrated and certified as being traceable to a National Reference Standard.

For images obtained from an optical microscope, an image of the calibration graticule shall also be obtained using the same objectives (and internal magnification step changers or zoom position) and illuminating technique. The microscope shall be set up for Köhler illumination to obtain the maximum resolution, see Reference [4].

For images obtained from a scanning electron microscope, images of the graticule should be obtained under the same conditions (accelerating kV, working distance, illumination aperture) as those used for the hardmetal.

## 8 Preparation of test samples

### 8.1 Methods of preparation

There are several methods for the preparation of hardmetal surfaces for metallographic examination. For example, a detailed description is given in ISO 4499-1. Firstly, careful coarse grinding is carried out to remove sufficient material to ensure that the true structure is revealed. After grinding with fine diamond grit wheels, polishing is effected by using diamond paste or diamond powders of progressively finer grain size down to 1  $\mu\text{m}$  on rigidly supported laps of, for example, thin plastic, thin felt or paper.

## 8.2 Characterisation of porosity and carbon (graphite) defects

For porosity and carbon defects, the test-piece section shall be prepared as for metallographic examination and the surface to be examined shall be free from grinding and polishing marks. Care shall be taken to avoid tearing out of particles, which can lead to a misleading evaluation of porosity.

## 8.3 Characterisation of eta-phase

Etching is necessary to reveal eta-phase particles (see 9.4). Eta-phase is metal carbide (usually  $M_6C$  or  $M_{12}C$ , where M is a combination of Co and W, for example,  $Co_3W_3C$ ), that forms when the overall carbon content of the hardmetal is relatively low. Generally, it can grow in one of two morphologies, either as large rosettes or as small particles of a similar size to the other hard phases (WC or cubic carbides) present in the hardmetal (see 9.4). The presence of the eta-phase is usually determined after light etching in 10 % Murakami's reagent for a few seconds with immediate water flush following etching (see ISO 4499-1), which works well for identifying large eta-phase rosettes. When the eta-phase is present as smaller particles (see Figure 6), it is recommended to use a 5 % Murakami's solution for 20 min followed by washing the sample with water. In both cases, the surface should be dried carefully with acetone or alcohol without wiping.

# 9 Procedure

## 9.1 General

If the porosity or uncombined carbon is not uniform over the area of the test piece section being examined, the locations on the section to which the evaluation refers shall be identified, for example, as top, bottom, edge, rim (case), core, etc.

It should be noted that the figures given in this Clause are only representing approximately  $\frac{1}{7}$  of the field of view in the microscope.

## 9.2 Determination of porosity

Pore size is defined as the maximum dimension of the pore in the section. Special reference shall be made to the presence of cracks or slits.

**9.2.1** Pores up to 10  $\mu m$  shall be assessed by scanning the surface of the test-piece section at a magnification of either  $\times 100$  or  $\times 200$ . An area fully representative of the test-piece section shall be examined and compared with the range of photomicrographs shown in Figure 1 or Figure 2, according to the chosen magnification. The porosity level shall be reported by reference to the appropriate photomicrograph and designated as A02, A04, A06 or A08. If the level of A-type pores is less than 50 % of that shown in Figure 1 (A02) or Figure 2 (A02), it shall be designated as A00.

**9.2.2** Pores within the range 10  $\mu m$  to 25  $\mu m$  shall be assessed by scanning the surface of the test-piece section at a magnification of  $\times 100$ . An area fully representative of the test-piece section shall be examined and shall be compared with the range of photomicrographs shown in Figure 3. The porosity level shall be reported by reference to the appropriate photomicrograph and designated as B02, B04, B06 or B08.

If the number of B-pores appears to be less than or equal to that represented by B02, the number of B-pores in the representative area ( $\geq 0,25 \text{ cm}^2$ ) shall be counted. This number shall be divided by the area examined to obtain the number of B-pores/ $\text{cm}^2$ .

If this number is less than 70 pores/ $\text{cm}^2$ , it shall be designated as B00 - #, where # is the number of B-pores/ $\text{cm}^2$  so obtained. If the number is greater than or equal to 70 pores/ $\text{cm}^2$ , it shall be designated as B02.