


SVENSK STANDARD

SS-EN 413-2:2016

Fastställt/Approved: 2016-10-24
Publicerad/Published: 2016-10-24
Utgåva/Edition: 3
Språk/Language: engelska/English
ICS: 91.100.10

Murverk – Murcement – Del 2: Provning

Masonry cement – Part 2: Test methods



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 413-2:2016 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 413-2:2016.

Denna standard ersätter SS-EN 413-2:2005, utgåva 2.

The European Standard EN 413-2:2016 has the status of a Swedish Standard. This document contains the official English version of EN 413-2:2016.

This standard supersedes the Swedish Standard SS-EN 413-2:2005, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Cement och byggkalk, SIS/TK 185.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 413-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2016

ICS 91.100.10

Supersedes EN 413-2:2005

English Version

Masonry cement - Part 2: Test methods

Ciment à maçonner - Partie 2 : Méthodes d'essai

Putz- und Mauerbinder - Teil 2: Prüfverfahren

This European Standard was approved by CEN on 18 June 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope	6
2 Normative references.....	6
3 General requirements for testing.....	6
3.1 Laboratory	6
3.2 Manufacturing tolerances for test equipment.....	6
3.2.1 Dimensions.....	6
3.2.2 Mass.....	6
3.3 Tolerances for test equipment in use	6
3.4 Number of tests.....	7
4 Determination of setting time	7
4.1 General.....	7
4.2 Method A.....	7
4.3 Method B.....	7
4.3.1 Test principle.....	7
4.3.2 Initial setting time procedure.....	7
4.3.3 Report - initial setting time.....	8
4.3.4 Final setting time procedure.....	8
4.3.5 Report - final setting time.....	8
4.3.6 Repeatability and reproducibility.....	8
5 Preparation of standard mortar	8
5.1 Principle	8
5.2 Consistence of fresh mortar by plunger apparatus (reference method).....	8
5.2.1 Apparatus.....	8
5.2.2 Procedure.....	9
5.2.3 Reproducibility.....	9
5.3 Consistence of fresh mortar by flow table (alternative method)	9
5.3.1 Method	9
5.3.2 Apparatus.....	9
5.3.3 Calibration	9
5.3.4 Procedure.....	10
6 Determination of water retention.....	10
6.1 Principle	10
6.2 Preparation	10
6.3 Apparatus.....	12
6.4 Procedure.....	13
6.5 Repeatability and reproducibility.....	13
7 Determination of air content	14
7.1 General.....	14
7.2 Pressure method (reference method).....	14
7.2.1 Principle	14
7.2.2 Apparatus.....	14
7.2.3 Calibration	14

7.2.4	Procedure.....	15
7.2.5	Repeatability and reproducibility.....	15
7.3	Alcohol method (alternative method).....	16
7.3.1	Principle	16
7.3.2	Apparatus.....	16
7.3.3	Procedure.....	16
	Bibliography.....	18

European foreword

This document (EN 413-2:2016) has been prepared by Technical Committee CEN/TC 51 “Cement and building limes”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2017, and conflicting national standards shall be withdrawn at the latest by February 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 413-2:2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

EN 413, Masonry cement, consists of the following parts:

- Part 1: Composition, specifications and conformity criteria;
- Part 2: Test methods.

The main differences between this document and EN 413-2:2005 are:

- updating of normative references;
- revised guidance on the properties of gauzes used in the water retention test;
- revised repeatability and reproducibility limits for setting time (Method B), water retention and air content (these revisions are based on a round-robin test programme instituted following the introduction of a new class of Masonry cement MC 22,5 into EN 413-1).

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard includes additional test methods to those described in the EN 196 series, *Methods of testing cement*, that enable the performance of masonry cement to be assessed when used in mortar for bedding masonry units and for rendering and plastering.

1 Scope

This European Standard describes reference and alternative test methods to be used when testing masonry cements to assess their conformity to EN 413-1. It gives the tests on fresh mortar for consistence, water retention and air content.

In the event of a dispute, only the reference methods are used.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement - Part 1: Determination of strength*

EN 196-3:2005+A1:2008, *Methods of testing cement - Part 3: Determination of setting times and soundness*

EN 459-2:2010, *Building lime - Part 2: Test methods*

3 General requirements for testing

3.1 Laboratory

Unless specifically stated to the contrary, all the tests described in this document shall be carried out in a laboratory where the air temperature is maintained at (20 ± 2) °C and the relative humidity at not less than 50 %.

3.2 Manufacturing tolerances for test equipment

3.2.1 Dimensions

Figures indicating the specified requirements for apparatus used in the tests described in this document shall include essential dimensions for which manufacturing tolerances are given.

Unless otherwise stated, tolerance class m according to EN 22768-1 should be applied.

NOTE Other dimensions are given for guidance.

3.2.2 Mass

Specified masses shall have manufacturing tolerances within ± 1 % of the mass unless otherwise stated.

3.3 Tolerances for test equipment in use

Tolerances applying to apparatus, which has been subjected to wear in use shall not exceed twice the corresponding manufacturing tolerance unless alternative requirements are specified.

3.4 Number of tests

Where the test is one of a series subject to statistical control, determination of each property by a single test shall be the minimum required.

Where the test is not part of a series subject to statistical control, two tests shall be performed to determine each property.

4 Determination of setting time

4.1 General

The setting time is determined by observing the penetration of a needle into a cement paste of standard consistence until it reaches a specified value.

The setting time is determined in accordance with either method A (4.2) or method B (4.3).

Method B is the reference method.

4.2 Method A

The setting time is determined in accordance with EN 196-3.

NOTE Experience has shown that the method specified in EN 196-3, in which the specimens are tested under water, is not suitable for some masonry cements which have low clinker contents.

4.3 Method B

4.3.1 Test principle

The equipment used and the specimen preparation procedures are as described in EN 196-3 but with the additional requirement for a room or a humidity cabinet of adequate size and maintained at $(20 \pm 1)^\circ\text{C}$ and not less than 90 % relative humidity.

4.3.2 Initial setting time procedure

Calibrate the Vicat apparatus with the needle, attached in advance of the test, by lowering the needle to rest on the base-plate to be used and adjusting the pointer to read zero on the scale. Raise the needle to the stand-by position. Fill a Vicat mould in accordance with EN 196-3:2005+A1:2008, 5.2.2 with paste of standard consistence mixed in accordance with EN 196-3:2005+A1:2008, 5.2.1

Place the filled mould and base-plate in the room or humidity cabinet and after a suitable time, position the mould and base-plate under the needle of the Vicat apparatus. Lower the needle gently until it is in contact with the paste. Pause in that position for between 1 s and 2 s in order to avoid initial velocity or forced acceleration of the moving parts. Then release the moving parts quickly and allow the needle to penetrate vertically into the paste. Read the scale when penetration has ceased, or 30 s after the release of the needle, whichever is the earlier.

Record the scale reading, which indicates the distance between the end of the needle and the base-plate, together with the time from zero. Repeat the penetration on the same specimen at conveniently spaced positions, not less than 8 mm from the rim of the mould or 5 mm from each other and at least 10 mm from the last penetration position, at conveniently spaced intervals of time, e.g. at 10 min intervals. Between penetrations keep the specimen in a room or humidity cabinet. Clean the Vicat needle immediately after each penetration. Retain the specimen if determination of the final setting time is to be made.