

Teknisk specifikation

SIS-CEN/TS 16980-1:2016

Publicerad/Published: 2017-02-01
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 25.220.20

Fotokatalys – Provningsmetod med kontinuerligt flöde – Del 1: Bestämning av nedbrytning av kväveoxid (NO) i luft med fotokatalytiskt material

Photocatalysis – Continuous flow test methods – Part 1: Determination of the degradation of nitric oxide (NO) in the air by photocatalytic materials

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8024422>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Denna tekniska specifikation är inte en svensk standard. Detta dokument innehåller den engelska språkversionen av CEN/TS 16980-1:2016.

This Technical Specification is not a Swedish Standard. This document contains the English version of CEN/TS 16980-1:2016.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i detta dokument lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om nationell och internationell standard.

Information about the content of this document is available from the SIS, Swedish Standards Institute, telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about national and international standards.

Dokumentet är framtaget av kommittén för Nanoteknik, SIS/TK 516.

Har du synpunkter på innehållet i det här dokumentet, vill du delta i ett kommande revideringsarbete eller vara med och ta fram standarder inom området? Gå in på www.sis.se - där hittar du mer information.

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 16980-1

December 2016

ICS 25.220.20

English Version

**Photocatalysis - Continuous flow test methods - Part 1:
Determination of the degradation of nitric oxide (NO) in
the air by photocatalytic materials**

Photocatalyse - Méthodes d'essai en flux continu -
Partie 1 : Détermination de la dégradation du
monoxyde d'azote (NO) dans l'air par des matériaux
photocatalytiques

Photokatalyse - Prüfverfahren mit kontinuierlichem
Durchfluss - Teil 1: Bestimmung des Abbaus von
Stickstoffmonoxid (NO) aus der Luft durch
photokatalytische Werkstoffe

This Technical Specification (CEN/TS) was approved by CEN on 8 August 2016 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

SIS-CEN/TS 16980-1:2016 (E)

Contents	Page
European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms, definitions and abbreviations	5
3.1 Terms and definitions	5
3.2 Abbreviations	5
4 Principle	7
5 Interferences	7
6 Apparatus.....	7
7 Sample preparation.....	13
7.1 Precaution.....	13
7.2 Sample characteristics	13
7.3 Conditioning.....	13
8 Measurement of concentrations.....	14
8.1 General.....	14
8.2 Measurement of the initial concentration of nitrogen oxides before entering the photochemical reactor	14
8.3 Conversion without sample.....	14
8.4 Conversion in the dark and in the presence of sample	15
8.5 Conversion under illumination in the presence of sample.....	15
9 Calculation of photocatalytic degradation rate.....	17
9.1 The observed rate of photocatalytic degradation	17
9.2 Intrinsic rate of photocatalytic transformation.....	18
10 Acceptability ranges of main test parameters.....	18
11 Test report.....	19
Annex A (informative) Typical trend of NO, NO₂ and NO_x concentrations during a photocatalytic test	21
Annex B (informative) Example of test for the control of mass transfer conditions	22
Annex C (informative) Typical Ohmic response of the fan.....	23
Bibliography.....	24

European foreword

This document (CEN/TS 16980-1:2016) has been prepared by Technical Committee CEN/TC 386 “Photocatalysis”, the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document is part of the CEN/TS 16980 series that consists of the following parts:

- Part 1: *Determination of the degradation of nitric oxide (NO) in the air by photocatalytic materials*
- Part 2: [To be determined].

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom

SIS-CEN/TS 16980-1:2016 (E)

1 Scope

This standard describes a method for assessing the performance of photocatalytic inorganic materials contained in cement mortars and/or limes or ceramic-based matrices, paints or materials deposited as thin films or coatings on a variety of substrates for the photocatalytic abatement of nitric oxide in the gas phase. This method is not suitable for the assessment of samples to be applied with flow perpendicular to the surface or flow permeating the surface itself as polymeric and paper filters, honeycomb structures and suchlike.

The performance for the photocatalytic sample under test is evaluated by measuring the degradation rate of nitric oxide (NO) using the method described herein. The photocatalytic abatement rate is calculated from the observed rate by eliminating the effects of mass transfer. The intrinsic photocatalytic abatement rate is an intrinsic property of the material tested and makes it possible to distinguish the photocatalytic activities of various products with an absolute scale defined with physical and engineering meaning.

For the measurements and calculations described in this standard the concentration of nitrogen oxides (NO_x) is defined as the stoichiometric sum of nitric oxide (NO) and nitrogen dioxide (NO₂).

Safety statement

Persons using this document should be familiar with the normal laboratory practice, if applicable. This document cannot address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

Environmental statement

It is understood that some of the material permitted in this standard may have negative environmental impact. As technological advantages lead to better alternatives for these materials, they will be eliminated from this standard to the extent possible.

At the end of the test, the user of the standard will take care to carry out an appropriate disposal of the wastes, according to local regulation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CEN/TS 16599:2014, *Photocatalysis - Irradiation conditions for testing photocatalytic properties of semiconducting materials and the measurement of these conditions*

EN ISO 9169, *Air quality - Definition and determination of performance characteristics of an automatic measuring system (ISO 9169)*

ISO 7996, *Ambient air — Determination of the mass concentration of nitrogen oxides — Chemiluminescence method*

3 Terms, definitions and abbreviations

3.1 Terms and definitions

For the purposes of this document, the following terms, definitions and abbreviations apply.

3.1.1

concentration of nitrogen oxides

NO_x

stoichiometric sum of nitric oxide (NO) and nitrogen dioxide (NO₂)

Note 1 to entry: For grade 999 nitrogen or air: the purity of the gas should be equal at least to 99,9 %.

3.1.2

photocatalyst

Catalyst able to produce, upon absorption of light, chemical transformations of the reaction partners

Note 1 to entry: The excited state of the photocatalyst repeatedly interacts with the reaction partners forming reaction intermediates and regenerates itself after each cycle of such interactions.

3.1.3

photocatalytic materials

materials in which or on which the photocatalyst is added by coating, impregnation, mixing, etc

3.2 Abbreviations

CSTR	Continuous Stirred-Tank Reactor
C^{IN}	concentration at reactor inlet
$C^{OUT,DARK}$	concentration of NO and NO ₂ at reactor outlet under stable conditions in the dark (no illumination)
$C^{OUT,light}$	concentration at reactor outlet under stable conditions with illumination (lamp on)
C_{NO}^{IN}	concentration of NO at reactor inlet
$C_{NO_2}^{IN}$	concentration of NO ₂ at reactor inlet
$C_{NO}^{OUT,DARK}$	concentration of NO at reactor outlet under stable conditions in the dark (no illumination) without sample
$C_{NO_2}^{OUT,DARK}$	concentration of NO ₂ at reactor outlet under stable conditions in the dark (no illumination) without sample
$C_{NO,S}^{OUT,DARK}$	concentration of NO at reactor outlet under stable conditions in the dark (no illumination) in presence of sample
$C_{NO_2,S}^{OUT,DARK}$	concentration of NO ₂ at reactor outlet under stable conditions in the dark (no illumination) in presence of sample
$C_{NO}^{OUT,LIGHT}$	concentration of NO at reactor outlet under stable conditions with illumination (lamp on) without sample
$C_{NO,0}^{OUT,LIGHT}$	concentration of NO at reactor outlet under illumination of sample measured at fan speed at nominal voltage V_0

SIS-CEN/TS 16980-1:2016 (E)

$C_{NO_2,0}^{OUT,LIGHT}$	concentration NO_2 at reactor outlet under illumination of sample measured at fan speed nominal voltage V_0
F	Flow
$F_{v,i}$	fan flow at i^{th} potential
I	irradiance
LED	light emitting diodes
MM	molecular mass
P	pressure in atmosphere
PTFE	Polytetrafluoroethylene
R	ideal gas constant
RH	gas relative humidity at 25 °C inside the reactor
η_{NO}^{dark}	conversion of NO in the dark
$\eta_{NO_2}^{dark}$	conversion to NO_2 in the dark
$\eta_{NO,lamp}^{PHOTO}$	conversion of NO under illumination without sample
$\eta_{NO,i}^{total}$	conversion of NO measured with fan speed at i^{th} potential
$\eta_{NO_2,i}^{total}$	conversion to NO_2 measured with fan speed at i^{th} potential
$r_{NO,i}^{photo}$	NO abatement rate at each fan speed ($i = 0..n$)
$r_{NO_2,i}^{photo}$	NO_2 photocatalytic production rate at each fan speed ($i = 0..n$)
$r_{NO_x,i}^{photo}$	NO_x abatement rate correspond to NO abatement rate minus NO_2 photocatalytic production rate
$r_{NO}^{photoCAT}$	NO photocatalytic degradation rate intrinsic to the surface of the material, after removing the mass transfer limitations
$r_{NO_x}^{photoCAT}$	NO_x photocatalytic degradation rate intrinsic to the surface of the material, after removing the mass transfer limitations
UV-A	ultraviolet with wavelength (λ) situated between 315 nm and 400 nm (IUPAC)
V_0	fan nominal operating potential (in Volt)
V_{min}	fan minimum operating potential (in Volt) set by the manufacturer
S	Sample
T	temperature in Kelvin
t_{stab}	time to reach the stability of NO concentration
UV	UltraViolet
Vr	Reactor net volume

4 Principle

The method consists in measuring the photocatalytic abatement of nitric oxide (NO) by photocatalytic materials as specified in paragraph 1 using a Continuous Stirred-Tank Reactor (CSTR) with flow tangential to the sample. Information on the theory is reported in the specialized literature (Minero et al. 2013). The residual NO and NO_x concentration at the CSTR outlet is measured by a chemiluminescence analyser (ISO 7996).

The photocatalytic activity test is carried out using chromatographic grade air, also obtained by mixing pure gases, to which NO is added in such an amount as to simulate a high degree of air pollution. The NO concentration is set to $(0,50 \pm 0,05)$ ppmv.

5 Interferences

Any measurement interferences are reported in the technical specifications of the chemiluminescence analyser. As what is measured are all species that can be converted by reduction to NO, NO₂ concentration is here defined as $[NO_2] = [NO_x] - [NO]$. For interferences on chemiluminescence detection, see Winer et al. (1974).

6 Apparatus

The test apparatus shall consist of the following main components.

6.1 Gas mixture preparation system.

The system used for preparing the reaction mixture is shown in Figure 1.

The mass flow controllers, calibrated and traceable, shall ensure a maximum flow consistent with that needed for a correct test execution. To ensure the necessary accuracy, the flow shall not exceed 90 % of the rated full scale.

As an example, to obtain the gas mixture only gases of chromatographic grade or higher purity shall be used. Instead of dry air cylinders, two separate cylinders of pure N₂ and O₂ can be used at the inlet of mass-flow controllers, adjusted so as to produce a mixture consisting of 20,8 % of O₂ and 79,2 % of N₂. The NO concentration to flow #1 is set to $(0,50 \pm 0,05)$ ppmv.