

# SVENSK STANDARD

## SS-EN 12574-2:2017

Fastställt/Approved: 2017-02-09  
Publicerad/Published: 2017-02-13  
Utgåva/Edition: 3  
Språk/Language: engelska/English  
ICS: 13.030.40

---

### **Stationära avfallsbehållare – Del 2: Prestandakrav och provningsmetoder**

### **Stationary waste containers – Part 2: Performance requirements and test methods**

This preview is downloaded from [www.sis.se](http://www.sis.se). Buy the entire standard via <https://www.sis.se/std-8024970>

# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 12574-2:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 12574-2:2017.

Denna standard ersätter SS-EN 12574-2:2006, utgåva 2.

The European Standard EN 12574-2:2017 has the status of a Swedish Standard. This document contains the official English version of EN 12574-2:2017.

This standard supersedes the Swedish Standard SS-EN 12574-2:2006, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Utrustning för avfallshantering, SIS/TK 252.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

EN 12574-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2017

ICS 13.030.40

Supersedes EN 12574-2:2006

English Version

## Stationary waste containers - Part 2: Performance requirements and test methods

Conteneurs fixes à déchets - Partie 2 : Exigences de performance et méthodes d'essais

Stationäre Abfallsammelbehälter - Teil 2: Anforderungen an die Ausführung und Prüfverfahren

This European Standard was approved by CEN on 21 November 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**SS-EN 12574-2:2017 (E)**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
<b>1 Scope</b> .....	<b>4</b>
<b>2 Normative references</b> .....	<b>4</b>
<b>3 Terms and definitions</b> .....	<b>4</b>
<b>4 Tests</b> .....	<b>5</b>
<b>4.1 General</b> .....	<b>5</b>
<b>4.2 Control before the tests</b> .....	<b>5</b>
<b>4.2.1 Visual aspects</b> .....	<b>5</b>
<b>4.2.2 Correspondence with EN 12574-1:2017</b> .....	<b>5</b>
<b>4.2.3 Masses limit deviations</b> .....	<b>6</b>
<b>4.2.4 Colour</b> .....	<b>6</b>
<b>4.2.5 Marking</b> .....	<b>6</b>
<b>4.3 Control after the tests</b> .....	<b>6</b>
<b>4.4 Conditions of the tests</b> .....	<b>6</b>
<b>4.5 Test load</b> .....	<b>6</b>
<b>4.6 Tests on the containers</b> .....	<b>6</b>
<b>4.6.1 General</b> .....	<b>6</b>
<b>4.6.2 Impact test by ball drop</b> .....	<b>6</b>
<b>4.6.3 Impact on an inclined plane</b> .....	<b>8</b>
<b>4.7 Stability test</b> .....	<b>9</b>
<b>4.8 Dynamic tests</b> .....	<b>9</b>
<b>4.8.1 General</b> .....	<b>9</b>
<b>4.8.2 Pulling test</b> .....	<b>9</b>
<b>4.8.3 Immobilization test</b> .....	<b>10</b>
<b>4.9 Lifting-tilting tests</b> .....	<b>10</b>
<b>4.9.1 General</b> .....	<b>10</b>
<b>4.9.2 Lifting-tilting empty container</b> .....	<b>10</b>
<b>4.9.3 Lifting-tilting of the loaded container</b> .....	<b>10</b>
<b>4.10 Miscellaneous tests</b> .....	<b>11</b>
<b>4.10.1 Internal stress-cracking tests (for thermo plastics only)</b> .....	<b>11</b>
<b>4.10.2 Corrosion test</b> .....	<b>11</b>
<b>4.10.3 Weathering</b> .....	<b>11</b>
<b>4.10.4 Test method with child mannequin for containers with sliding mobile flap</b> .....	<b>12</b>
<b>4.10.5 Test for locked lid</b> .....	<b>13</b>
<b>4.10.6 Sequence of the tests</b> .....	<b>13</b>
<b>5 Tests report</b> .....	<b>14</b>
<b>Annex A (normative) Device for ball drop test</b> .....	<b>15</b>
<b>Annex B (informative) Apparatus for lateral impact test on inclined plane</b> .....	<b>16</b>
<b>Annex C (normative) Weathering tests</b> .....	<b>17</b>
<b>Annex D (informative) A-deviations</b> .....	<b>18</b>
<b>Bibliography</b> .....	<b>19</b>

## **European foreword**

This document (EN 12574-2:2017) has been prepared by Technical Committee CEN/TC 183 “Waste management”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12574-2:2006.

This European Standard is one part of the series of standards EN 12574 about “Stationary waste containers” comprising the following parts:

- *Part 1: Containers with a capacity up to 10 000 l with flat or dome lid(s), for trunnion, double trunnion or pocket lifting device — Dimensions and design;*
- Part 2: Performance requirements and test methods;
- Part 3: Safety and health requirements;

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **SS-EN 12574-2:2017 (E)**

### **1 Scope**

This part of EN 12574 specifies the test methods for stationary waste containers (in the text also called containers) according to EN 12574-1:2017. It also specifies the target requirements to be reached either during or after the tests.

### **2 Normative references**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1501-1, *Refuse collection vehicles and their associated lifting devices - General requirements and safety requirements - Part 1: Rear-end loaded refuse collection vehicles*

EN 1501-2, *Refuse collection vehicles and their associated lifting devices - General requirements and safety requirements - Part 2: Side loaded refuse collection vehicles*

EN 1501-3:2008, *Refuse collection vehicles and their associated lifting devices - General requirements and safety requirements - Part 3: Front loaded refuse collection vehicles*

EN 1501-5, *Refuse collection vehicles - General requirements and safety requirements - Part 5: Lifting devices for refuse collection vehicles*

EN 10346, *Continuously hot-dip coated steel flat products for cold forming - Technical delivery conditions*

EN 12574-1:2017, *Stationary waste containers - Part 1: Containers with a capacity up to 10 000 l with flat or dome lid(s), for trunnion, double trunnion or pocket lifting device - Dimensions and design*

EN ISO 105-B02, *Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02)*

EN ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461)*

EN ISO 4892-2, *Plastics - Methods of exposure to laboratory light sources - Part 2: Xenon-arc lamps (ISO 4892-2)*

EN ISO 8256, *Plastics - Determination of tensile-impact strength (ISO 8256)*

ISO 2081, *Metallic and other inorganic coatings - Electroplated coatings of zinc with supplementary treatments on iron or steel*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 12574-1:2017 apply.



## **4 Tests**

### **4.1 General**

The following tests refer to EN 12574-1:2017.

Before and after the tests a visual inspection of the container shall be done for the purpose of:

- a) checking that the container is not damaged and has no visual defect;
- b) checking that the manufacturing characteristics of the container to be tested are those specified in EN 12574-1:2017;
- c) comparing the condition of the container before and after the sequence of tests.

After completing the tests some deformation of the container is permissible, however, it shall remain entirely functional.

### **4.2 Control before the tests**

#### **4.2.1 Visual aspects**

Conformity of the container to EN 12574-1:2017, no damage, no cracks, bubbles, large flashes or sharp edges shall be present. No surface defects (unsmooth areas; trails in colour) perceivable from a distance of 1 m by a naked eye shall be visible.

#### **4.2.2 Correspondence with EN 12574-1:2017**

##### **4.2.2.1 Components**

Body, lid, wheels and other fittings shall be tested in line with the relevant container standard.

##### **4.2.2.2 Sizes and dimensions**

Dimensions of the containers and components shall correspond to EN 12574-1:2017.

##### **4.2.2.3 Capacities**

Capacities of the container and its parts shall correspond to EN 12574-1:2017.

- a) For the body, by tank method (see 4.2.2.4), up to 1 700 l, and by calculation for containers over 1 700 l;
- b) for the lid, if possible by tank method (see 4.2.2.4), if not by calculation;
- c) for the container, add the results obtained in a) and b) minus any duplicated capacities.

##### **4.2.2.4 Tank method**

The test equipment shall consist of a tank with sufficient capacity to receive the container to be tested.

The test procedure is as follows:

- a) place the empty container in a tank, the container shall not be inclined;
- b) simultaneously fill the tank and the container with water at a temperature of  $(15 \pm 5)$  °C;
- c) measure the quantity of water inside the container.

The result of measurement shall be  $\pm 1$  % of the stated capacity of the container.

## **SS-EN 12574-2:2017 (E)**

### **4.2.3 Masses limit deviations**

The limit deviations on the claimed container mass are  $\pm 5\%$  for all materials.

### **4.2.4 Colour**

The colour shall be defined and agreed upon between customer and supplier.

### **4.2.5 Marking**

The marking of the container shall correspond to EN 12574-1:2017, Clause 10.

## **4.3 Control after the tests**

In spite of variations in deflection and sizes, it shall be possible to lift and tilt the container loaded according to 4.5 with nominal load safely on a designated lifting device and to move the container on its wheels if any.

## **4.4 Conditions of the tests**

The tests shall be carried out at the following temperatures:

$$T_1 = (23 \pm 5) ^\circ\text{C}$$

$$T_2 = (-18^{0}_{-2}) ^\circ\text{C}.$$

The minimum duration of conditioning before testing shall be 12 h. If the test is carried out outside the conditioned room and if the duration of the test is more than 5 min, then for each 5 min period of testing the container shall be reconditioned for at least 15 min before continuing the test.

For special purposes a temperature lower than  $-18\text{ }^\circ\text{C}$  or higher than  $+23\text{ }^\circ\text{C}$  can be agreed; in this case it shall be indicated in the test report.

## **4.5 Test load**

For the calculation of test loads either of the two following density values shall be taken:

- $0,25\text{ kg/dm}^3$  for light waste (e.g. for plastics, plastic bottles, flasks, mixed waste);
- $0,40\text{ kg/dm}^3$  for heavy waste (e.g. for glass, paper, organic waste, cardboard).

The test load shall be the value of density as above multiplied by nominal volume and shall be HDPE granules in 25 kg bags having a specific mass of  $0,5\text{ kg/dm}^3$  but no more than 2 500 kg.

## **4.6 Tests on the containers**

### **4.6.1 General**

All tests shall be carried out on new containers, as per the sequence of tests in 4.10.4.

### **4.6.2 Impact test by ball drop**

The ball drop test is not compulsory for steel containers.

The ability of the sensitive points such as welds and corners of the container to resist under impacts at temperature  $T_2$  shall be tested.

The stationary containers shall stand on their wheels (if they are fitted) or on their supports.

Ball drop test shall be carried out using a 5 kg steel cylinder, diameter 65 mm, with hemispheric end radius of 32,5 mm. The steel cylinder is guided in a vertical pipe with a slot or with holes in order to allow the air to escape during the drop.

The following areas of containers shall be tested by impact test according to the conditions shown below:

- a) on the inside of the bottom:
  - 1) at least 3 points beginning at the injection point(s) (less than 20 mm from sprue point) and other potentially weak points (i.e. drain holes for instance);
  - 2) with a drop height of 1,5 m;
  - 3) with a frequency of 3 times per measuring point.
- b) at protrusions on the body (handle, top rim, etc.), junctions between lid and body, hinges at the lid and protruding areas on the lid:
  - 1) with a drop height of 0,8 m; and
  - 2) with a frequency of 2 impacts per measuring point.

After tests, no permanent deformations or ruptures capable of hampering designed use are allowed.

The device shall be according to Figure A.1.

A test of segments is allowed with segments of approximately a quarter of a square metre.

At least the following critical area shall be sawn from the container and shall be tested:

- positioning wheel suspensions (see area 1 in Figure 1): this area shall be cut out from the bottom at a height of approximately 500 mm;
- frontal receiver (see area 2 in Figure 1): both corner parts shall be tested. The area should be 300 mm × 300 mm;
- hinge area (see area 3 in Figure 1): both corner parts shall be tested. The area should be 300 mm × 300 mm;
- lid (see area 4 in Figure 1): an area from the hinges to the injection points shall be tested.