

SVENSK STANDARD

SS-EN 302-3:2017

Fastställt/Approved: 2017-09-13
Publicerad/Published: 2017-09-14
Utgåva/Edition: 4
Språk/Language: engelska/English
ICS: 83.180; 83.181

Lim för bärande träkonstruktioner – Provningsmetoder – Del 3: Tvärdraghållfasthet vid syrapåverkan under cykliskt varierad temperatur och fukt

Adhesives for load-bearing timber structures – Test methods – Part 3: Determination of the effect of acid damage to wood fibres by temperature and humidity cycling on the transverse tensile strength

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-8028463>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 302-3:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 302-3:2017.

Denna standard ersätter SS-EN 302-3:2013, utgåva 3.

The European Standard EN 302-3:2017 has the status of a Swedish Standard. This document contains the official version of EN 302-3:2017.

This standard supersedes the Swedish Standard SS-EN 302-3:2013, edition 3.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Lim och limningsteknik, SIS/TK 162.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 302-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2017

ICS 83.180

Supersedes EN 302-3:2013

English Version

Adhesives for load-bearing timber structures - Test methods - Part 3: Determination of the effect of acid damage to wood fibres by temperature and humidity cycling on the transverse tensile strength

Adhésifs pour structures portantes en bois - Méthodes d'essai - Partie 3: Détermination de l'influence de l'attaque d'acide des fibres de bois, résultant de traitements cycliques en température et humidité sur la résistance à la traction transversale

Klebstoffe für tragende Holzbauteile - Prüfverfahren - Teil 3: Bestimmung des Einflusses von Säureschädigung der Holzfasern durch Temperatur- und Feuchtezyklen auf die Querkzugfestigkeit

This European Standard was approved by CEN on 9 July 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

SS-EN 302-2:2017 (E)

Contents		Page
European foreword		3
Introduction		4
1	Scope	6
2	Normative references	6
3	Principle	6
4	Apparatus	6
5	Method	7
5.1	Selection of timber	7
5.2	Preparation of the bonded assemblies	7
5.3	Preparation of the test pieces	9
5.4	Number of test pieces	9
5.5	Climatic and cyclic storage conditions	9
5.6	Test procedure	10
6	Expression of results	10
7	Test report	11
Bibliography		12

European foreword

This document (EN 302-3:2017) has been prepared by Technical Committee CEN/TC 193 “Adhesives”, the secretariat of which is held by UNE.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2018, and conflicting national standards shall be withdrawn at the latest by March 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 302-3:2013.

Compared to EN 302-3:2013 the following modification has been made:

- a) EN 15416-2 is replaced by EN 302-8, *Adhesives for load-bearing timber structures — Test methods — Part 8: Static load test of multiple bond line specimens in compression shear*;
- b) specification of beech for test pieces for gap filling adhesives in 5.1;
- c) reparation of test pieces for gap filling adhesives added in 5.2;
- d) description of climate cycling test in 5.5 completed.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SS-EN 302-2:2017 (E)

Introduction

This document is one of a series dealing with adhesives for use with timber structures, and is published in support of EN 1995, *Eurocode 5: Design of timber structures*. The series consists of three classification and performance requirements for adhesives for load-bearing timber structures, phenolic and aminoplastic adhesives (EN 301), one component polyurethane adhesives (EN 15425) and emulsion polymerized isocyanate adhesives (EN 16254), and all together twelve test methods (EN 302-1, EN 302-2, EN 302-3, EN 302-4, EN 302-5, EN 302-6, EN 302-7 and EN 302-8, and EN 15416-1, EN 15416-3, EN 15416-4 and EN 15416-5).

These European Standards have the following titles.

EN 301, *Adhesives, phenolic and aminoplastic, for load-bearing timber structures — Classification and performance requirements*

EN 15425, *Adhesives — One component polyurethane (PUR) for load bearing timber structures — Classification and performance requirements*

EN 16254, *Adhesives — Emulsion polymerized isocyanate (EPI) for load-bearing timber structures — Classification and performance requirements*

EN 302, *Adhesives for load-bearing timber structures — Test methods*

- *Part 1: Determination of longitudinal tensile shear strength*
- *Part 2: Determination of resistance to delamination*
- *Part 3: Determination of the effect of acid damage to wood fibres by temperature and humidity cycling on the transverse tensile strength*
- *Part 4: Determination of the effects of wood shrinkage on the shear strength*
- *Part 5: Determination of maximum assembly time under referenced conditions*
- *Part 6: Determination of the minimum pressing time under referenced conditions*
- *Part 7: Determination of the working life under referenced conditions*
- *Part 8: Static load test of multiple bond line specimens in compression shear*

EN 15416, *Adhesives for load bearing timber structures other than phenolic and aminoplastic — Test methods*

- *Part 1: Long-term tension load test perpendicular to the bond line at varying climate conditions with specimens loaded perpendicular to the glue line (Glasshouse test)*
- *Part 3: Creep deformation test at cyclic climate conditions with specimens loaded in bending shear*
- *Part 4: Determination of open assembly time under referenced conditions*
- *Part 5: Determination of minimum pressing time under referenced conditions*

Safety statement

Persons using this document should be familiar with the normal laboratory practice, if applicable. This document cannot address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

Environmental statement

It is understood that some of the material permitted in this standard can have a negative environmental impact. As technological advantages lead to better alternatives for these materials, they will be eliminated from this standard to the greatest extent possible.

At the end of the test, it is recommended that the user of the standard take care to carry out an appropriate disposal of the wastes, according to local regulations.

SS-EN 302-2:2017 (E)

1 Scope

This European Standard specifies a method for determining the effect on bond strength of damage to wood fibres caused by the action of acids from the adhesive or primer used in the gluing process during climatic cycling.

It is suitable for the following applications:

- a) for assessing the compliance of adhesives with EN 301, EN 15425 and EN 16254;
- b) for assessing the suitability and quality of adhesives for load-bearing timber structures;
- c) for determining if the adhesive after bonding has a damaging influence on the strength of the wood due to chemical action.

This test is intended primarily to obtain performance data for the classification of adhesives for load-bearing timber structures according to their suitability for use in defined climatic environments. This test is carried out on Norway spruce (*Picea abies* L.) or Beech (*Fagus sylvatica* L.).

This method is not intended for use to provide numerical design data and does not necessarily represent the performance of the bonded member in service.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1245, *Adhesives - Determination of pH*

ISO 5893, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

3 Principle

A joint between wooden adherends is submitted to defined temperature and humidity cycles and then strained to failure by a transverse tensile load.

4 Apparatus

4.1 Testing machine, which shall be either:

- a) a constant rate of loading machine, capable of maintaining a rate of loading of (5 ± 1) kN/min; or
- b) a constant rate of traverse machine as described in ISO 5893.

Special mounts are required (see Figure 1). One or both mounts shall be attached to the straining heads by a coupling, which permits self-alignment of the mounts whilst the test pieces are being pulled.

4.2 Climatic cabinets, which are enclosures with air circulation capable of maintaining the test pieces under the following conditions:

- a) (10 ± 2) °C at approximately $(87,5 \pm 2,5)$ % relative humidity;
- b) (50 ± 2) °C at approximately $(87,5 \pm 2,5)$ % relative humidity;

c) (50 ± 2) °C with relative humidity lower than 20 %.

NOTE The velocity of the air circulation at a level of 0,5 m/s to 1,0 m/s has shown to be suitable.

4.3 Airtight glass enclosure, such as a desiccator with a lid is required, with the following dimensions:

- a) Volume 2 l to 10 l;
- b) Ratio of height to width between 1/1 and 2/1.

5 Method

5.1 Selection of timber

Carry out this test using Norway spruce (*Picea abies* L.) having a density of (450 ± 25) kg/m³ measured at 12 % moisture content.

Carry out the test using beech (*Fagus sylvatica* L.) having a density of (700 ± 50) kg/m³ measured at 12 % moisture content, for gap filling adhesives (GF).

Prepare one piece of wood, at least 60 mm × 60 mm in cross section and at least 1 600 mm in length or two pieces with a length of 800 mm that are free from knots, straight-grained and with growth rings not wider than 2 mm and at 30° to 60° to the surfaces of the specimen.

5.2 Preparation of the bonded assemblies

Cut the piece of wood lengthwise into two equal pieces of rectangular cross section and store them in standard climate [20/65] to constant mass. Constant mass is defined as the mass attained when the results of two successive weighings over an interval of 24 h differ by not more than 0,1 % of the mass of the specimen.

Condition the timber in standard atmosphere [20/65] ((20 ± 2) °C and (65 ± 5) % relative humidity) for at least 7 days prior to bonding, to achieve a moisture content of (12 ± 1) %.

Not more than 8 h before bonding, plane each surface to be bonded to the final thickness of 25 mm. Remove any dust carefully. Do not touch or soil the prepared surface.

For glue mixes, adhesive and hardener blended before application, the glue line thickness shall be 0,5 mm by using 0,5 mm thick spacers.

For gap filling adhesives (GF), the glue line thickness shall be 2,0 mm by using 2,0 mm thick spacers.

For separate application of adhesive and hardener, the glue line thickness shall be 0,1 mm by using 0,1 mm thick spacers.