

SVENSK STANDARD

SS-EN 13639:2017

Fastställt/Approved: 2017-10-10
Publicerad/Published: 2017-10-16
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 91.100.10

Bestämning av halten organiskt kol i kalksten

Determination of total organic carbon in limestone



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 13639:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 13639:2017.

Denna standard ersätter SS-EN 13639, utgåva 1 och SS-EN 13639/AC:2004, utgåva 1.

The European Standard EN 13639:2017 has the status of a Swedish Standard. This document contains the official version of EN 13639:2017.

This standard supersedes the Swedish Standard SS-EN 13639, edition 1 and SS-EN 13639/AC:2004, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Cement och byggkalk, SIS/TK 185.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 13639

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2017

ICS 91.100.10

Supersedes EN 13639:2002

English Version

Determination of total organic carbon in limestone

Determination du carbone organique total dans le
calcaireBestimmung des Gesamtgehalts an organischem
Kohlenstoff in Kalkstein

This European Standard was approved by CEN on 26 June 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

Contents

Page

European foreword.....	4
1 Scope.....	5
2 Normative references.....	5
3 General requirements for testing.....	5
3.1 Number of tests.....	5
3.2 General statistical terms	5
3.3 Expression of masses and results.....	6
3.4 Blank determinations.....	6
3.5 Sampling and sampling preparation.....	6
3.6 General test principles.....	6
4 Reagents	7
5 General apparatus	9
5.1 Balances.....	9
5.2 Laboratory ovens	9
5.3 Crucibles.....	10
6 Gravimetric method with wet oxidation (reference method)	10
6.1 Principle	10
6.2 Apparatus.....	10
6.3 Procedure.....	11
6.4 Calculation.....	12
7 Gravimetric method with furnace oxidation (alternative method No. 1)	12
7.1 Principle	12
7.2 Apparatus.....	12
7.3 Procedure.....	14
7.4 Calculation.....	14
8 Infrared detection method with furnace oxidation (low temperature) (alternative method No. 2)	15
8.1 Principle	15
8.2 Apparatus.....	15
8.3 Procedure.....	17
8.4 Calculation.....	18
9 Infrared detection or conductivity methods with furnace oxidation (high temperature): procedure A (alternative method No. 3)	19
9.1 Principle	19
9.2 Apparatus.....	19
9.3 Procedure.....	20
10 Infrared detection or conductivity methods with furnace oxidation (high temperature): procedure B (alternative method No. 4)	21
10.1 Principle	21
10.2 Apparatus.....	21
10.3 Procedure.....	21

11 Repeatability and reproducibility standard deviation, determination limit 22

12 Test report 22

Annex A (informative) Features of commercial HF (High Frequency) combustion/infrared carbon analyzers..... 23

A.1 Combustion 23

A.2 Infrared gas analyser 24

Annex B (informative) Assignment of reagents to methods 25

Bibliography 27

SS-EN 13639:2017 (E)

European foreword

This document (EN 13639:2017) has been prepared by Technical Committee CEN/TC 51 "Cement and building limes", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2018, and conflicting national standards shall be withdrawn at the latest by March 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13639:2002.

In comparison to EN 13639:2002, the following change has been made:

In Clause 10 a new alternative method, *Alternative method No. 4*, developed in Sweden, has been included.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies methods for the determination of the total organic carbon content (TOC) in limestone.

NOTE This method covers the determination of TOC in < 1 %.

The standard describes the reference method and alternative methods that can be considered to be equivalent.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 11464, *Soil quality — Pretreatment of samples for physico-chemical analysis*

3 General requirements for testing

3.1 Number of tests

Where the analysis is one of the series subject to statistical control, determination of the total organic carbon content by a single test shall be the minimum required.

Where the analysis is not part of a series subject to statistical control, the number of tests for determination of the total organic carbon content shall be two (see also 3.3).

In case of dispute, only the reference method is used.

In case of dispute, the number of tests for determination of the total organic carbon content shall be two (see also 3.3).

Any other method may be used provided it is calibrated, either against the reference method or against internationally accepted reference materials, in order to demonstrate its equivalence.

3.2 General statistical terms

Repeatability standard deviation - the standard deviation of test results obtained under repeatability conditions where independent test results are obtained with the same method on identical material tested in the same laboratory by the same operator using the same equipment within short intervals of time.

Reproducibility standard deviation - the standard deviation of test results obtained under reproducibility conditions where test results are obtained with the same method on identical material tested in different laboratories with different operators using different equipment.

NOTE Definitions are based on ISO 3534-1 [1].

The standard deviations of repeatability and reproducibility are expressed in absolute percent.

Determination limit (Formula (1)) - is the content where its relative uncertainty, which is assigned to a fixed probability level, and defined as the quotient of the half of a two-side prognosis interval and the content to be assigned to the determination limit, is equal to a pre-set value.

SS-EN 13639:2017 (E)

$$x_{DI} = k \times s_{xD} \times t_{f\alpha} \sqrt{\frac{1}{n} + \frac{1}{p} + \frac{(x_{DI} - \bar{x})^2}{Q_x}} \tag{1}$$

where:

- α is the probability level
- f is the variability (number of degrees of freedom)
- $\frac{1}{k} = \frac{\Delta x_{DI}}{x_{DI}}$ is the relative uncertainty
- $Q_x = \sum_{i=1}^n (x_i - \bar{x})^2$ is the number of calibration samples
- n number of test results
- p is the number of analyses of each calibration sample
- s_{xD} is the standard deviation of the procedure
- $t_{f\alpha}$ is the quantile of the t -distribution ($f = n - 2$)
- x_i is the analysed content assigned to a calibration sample
- \bar{x} is the arithmetic mean of the contents assigned to all calibration samples
- x_{DI} is the determination limit
- Δx_{DI} is half width of the two-side prognosis interval

NOTE This determination limit is based on DIN 32645 [2].

3.3 Expression of masses and results

Express masses in grams to an accuracy of $\pm 0,0005$ g.

Express the results as a percentage to at least two decimal places, if the difference between the individual test results exceeds two times the repeatability standard deviation given in Clause 10, the test shall be repeated.

3.4 Blank determinations

Carry out a blank determination without a sample following the same procedure and using the same amounts of reagents. Correct the results obtained for the analytical determination.

3.5 Sampling and sampling preparation

Depending on the size of the raw material, a sample of at least 1 kg up to 10 kg shall be taken by the procedure described in ISO 11464, dried, crushed, reduced and ground to form a representative laboratory sample for analysis. The laboratory sample shall pass a sieve of 90 μ m mesh size conforming to ISO 3310-1. The drying process shall be modified, if necessary, to accommodate samples known to contain high contents of volatile organic carbon.

3.6 General test principles

In general, all the methods consist of the following procedures:

- a) decarbonation of the original limestone sample;
- b) purification of the carrier gas, if it is not of high purified quality;

- c) oxidation of the organic carbon matter;
- d) purifying of the CO₂ produced by oxidation;
- e) measurement of the CO₂ content.

4 Reagents

4.1 General requirements

Application of this standard involves the use of hazardous substances.

There are national and European regulations and provisions on requirements for occupational health and safety.

Use only reagents of analytical quality. References to water mean distilled water, or water of equal purity.

Unless otherwise stated percent means percent by mass.

The concentrated liquid reagents used in this standard have the following densities (ρ) in grams per cubic centimetre at 20 °C:

ammonia solution	0,88 to 0,91
hydrochloric acid	1,18 to 1,19
hydrogen peroxide	1,11
nitric acid	1,40 to 1,42
phosphoric acid	1,71 to 1,75
sulfuric acid	1,84

The degree of dilution is always given as a volumetric sum, for example: dilute hydrochloric acid 1 + 2 means that 1 volume of concentrated hydrochloric acid is to be mixed with 2 volumes of water.

4.2 Ammonia solution (NH₃ × H₂O)

4.3 Calcium chloride, anhydrous (CaCl₂)

4.4 Calibration reagent, metal

For example iron with known carbon content.

4.5 Carbon dioxide in oxygen

Concentrations, 0,95 vol.% and 19 vol.%

4.6 Carrier gases

Air, oxygen, nitrogen or argon, free of carbon dioxide and hydrocarbons, depending on application.

4.7 Chromic acid

Dissolve 5 g of chromium trioxide (4.8) in 10 ml of water. Add sulfuric acid (4.13) with stirring, until the chromium trioxide, which initially precipitates, is just re-dissolved.