

SVENSK STANDARD


SS-EN 16755:2017



Fastställt/Approved: 2017-10-26
Publicerad/Published: 2017-10-30
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 13.220.40; 13.220.50; 71.100.50

Bruksklasser för brandskyddets beständighet inomhus och utomhus hos träbaserade produkter

Durability of reaction to fire performance – Classes of fire-retardant treated wood products in interior and exterior end use applications



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.



Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.


Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 16755:2017 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 16755:2017.

The European Standard EN 16755:2017 has the status of a Swedish Standard. This document contains the official version of EN 16755:2017.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Sågade och hyvlade trävaror, SIS/TK 182/AG 02.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 16755

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2017

ICS 13.220.40; 13.220.50; 71.100.50

English Version

Durability of reaction to fire performance - Classes of fire-retardant treated wood products in interior and exterior end use applications

Durabilité des performances de réaction au feu -
Classement des produits à base de bois ignifugés pour
utilisation finale en intérieur et en extérieur

Dauerhaftigkeit des Verhaltens bei Brandeinwirkung -
Klassen der mit Feuerschutzmitteln behandelten
Holzprodukte für Anwendungen im Innen- und
Außenbereich

This European Standard was approved by CEN on 2 July 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	6
4 Symbols and abbreviations	6
5 Requirements.....	6
5.1 Wood products and non-fire-retardant coating systems	6
5.2 Reaction to fire performance.....	7
5.2.1 Initial classification for reaction to fire	7
5.2.2 Reaction to fire performance before and after accelerated or natural weathering.....	7
5.3 Durability of reaction to fire performance	8
5.3.1 General.....	8
5.3.2 DRF Class INT1	8
5.3.3 DRF Class INT2	8
5.3.4 DRF Class EXT	9
5.3.5 Practise to use DRF classes.....	10
6 Classification report.....	11
Annex A (normative) Hygroscopic properties of fire-retardant treated wood products including those with fire-retardant coatings.....	12
A.1 General.....	12
A.2 Field of application.....	12
A.3 Sampling, sample handling and preparation.....	13
A.3.1 General procedure.....	13
A.3.2 Procedure for end use products	14
A.4 Test method	14
A.4.1 Principle	14
A.4.2 Equipment	14
A.4.3 Testing environment	14
Annex B (normative) Accelerated weathering of fire-retardant treated wood for fire testing.....	17
B.1 General.....	17
B.2 Field of application.....	17
B.3 Sampling, sample handling and preparation.....	17
B.4 Test method	18
B.4.1 Principle	18
B.4.2 Equipment	18
B.4.3 Testing environment	19
Annex C (informative) Example of classification report — Classification report: Durability classes of reaction to fire performance of fire-retardant wood products in interior and exterior end use applications according to EN 16755:2017	22
Bibliography.....	26

European foreword

This document (EN 16755:2017) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2018, and conflicting national standards shall be withdrawn at the latest by April 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SS-EN 16755:2017 (E)**Introduction**

Fire-retardant treatments may considerably improve the reaction to fire properties of wood products and these may result in wood products having the highest fire performance characteristics achievable with any combustible product. However, the reaction to fire performance may be reduced by exposure to wet and/or humid conditions [11] and the ability of the treated products to continue to perform even when exposed to these conditions needs to be demonstrated.

Two aspects of the reaction to fire durability of fire-retardant wood products need to be considered. One is the risk for high moisture content and migration of the fire-retardant chemicals within the wood product and salt crystallization on the product surface that may fall off and reduce the improved fire properties. These hygroscopic properties of the treated wood product can be evaluated by exposure to high relative humidity.

The other aspect is the risk for decreased fire performance due to loss of the fire-retardant chemicals by leaching in exterior applications, e.g. facade claddings. Maintained fire performance after weathering needs to be verified.

This standard is based on the Technical Specification CEN/TS 15912, on a Nordtest standard [20] and on experience from North America [10, 9].

1 Scope

This European Standard describes the characteristics for fire-retardant treated wood products.

NOTE 1 It is based on maintaining performance undiminished throughout the desired service life in the anticipated conditions of use.

The European Standard prescribes the classification requirements for the durability of the reaction to fire performance of fire-retardant treated wood products to be used in interior and exterior end use conditions.

This European Standard applies to wood which has been treated during a production process with fire retardant products applied either by a penetration process or by a superficial process, such as with a film forming or intumescent fire retardant coating. It covers fire-retardant treated products that are coated with an ordinary paint.

Mechanical properties and biological durability of fire-retardant treated wood products are not covered by this European Standard.

NOTE 2 This standard can be used for other manufactured wood products.

This standard covers wood products. It doesn't cover wood-based panels.

NOTE 3 Wood based panels for construction are described in EN 13986.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 927-3, *Paints and varnishes — Coating materials and coating systems for exterior wood — Part 3: Natural weathering test*

EN 927-6, *Paints and varnishes — Coating materials and coating systems for exterior wood — Part 6: Exposure of wood coatings to artificial weathering using fluorescent UV lamps and water*

EN 13238, *Reaction to fire tests for building products — Conditioning procedures and general rules for selection of substrates*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

ISO 5660-1, *Reaction-to-fire tests — Heat release, smoke production and mass loss rate — Part 1: Heat release rate (cone calorimeter method) and smoke production rate (dynamic measurement)*

SS-EN 16755:2017 (E)**3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

3.1 service classes**3.1.1 dry condition
DRF INT1**

moisture content in the materials corresponding to a temperature of 20 °C and the relative humidity of the surrounding air exceeding 65 % only for a few weeks per year

Note 1 to entry: In Eurocode EN 1995-1-1 as Service class 1.

**3.1.2 humid condition
DRF INT2**

moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air exceeding 85 % only for a few weeks per year

Note 1 to entry: In EN 1995-1-1 defined as Service class 2.

**3.2 ordinary paint
non-fire retardant paint****4 Symbols and abbreviations**

The symbols for DRF Classes INT1, INT2 and EXT are the following ones:



Figure 1 — Proposed symbols for classes

5 Requirements**5.1 Wood products and non-fire-retardant coating systems**

The treatment manufacturing process and application rate declared by the producer shall be declared by the manufacturer of the final product. Actual fire-retardant retention shall be expressed in kg/m³ of the final wood product, or in kg/m² for surface treated products. Values shall be given for products conditioned at (50 ± 5)% relative humidity at (23 ± 2) °C (as for fire testing) according to EN 13238.

For products in DRF Classes INT and EXT procedures for maintenance shall be provided by the manufacturers regarding:

- type of maintenance;
- interval of maintenance;

- time until to the first maintenance/recoating (if relevant);
- coating system to be used initially and at maintenance (if relevant).

Verification of DRF Class EXT obtained without a coating system (with an ordinary paint) is valid also for the same product coated, provided that the coating does not reduce the reaction to fire performance.

The maintained fire performance of a coated product (with an ordinary paint) may be verified by fire testing according to EN 13823 or ISO 5660-1.

Verification of DRF Class EXT is valid for thicker wood products than verified, but not for thinner.

5.2 Reaction to fire performance

5.2.1 Initial classification for reaction to fire

Classification testing for reaction to fire performance shall be performed. The products shall fulfil a specified fire performance according to a recognized reaction to fire standard. The recognized standards are for construction products EN 13501-1 and for maritime application the IMO Code FTP [12].

5.2.2 Reaction to fire performance before and after accelerated or natural weathering

5.2.2.1 General

Reaction to fire performance before and after weather exposure shall be performed according to 5.2.2.2.

The weather exposure shall be performed according to an accelerated procedure, see Annex B, or according to EN 927-6 or natural weathering according to EN 927-3. If there is a contestation, the reference test method is EN 927-3 with fire testing according to EN 13823 before and after weathering.

For the accelerated weathering, it is essential that the exposed samples are large enough to be fire tested. Thus, minimum width is 100 mm (minimum according to ISO 5660-1).

For the accelerated weathering, it is also essential that the exposed samples are large enough to fulfil the cutting requirements in 5.2.2.2.3 and Annex B.

For the natural weathering, it is essential that the exposed samples are large enough to be fire tested either by European standards or by small scale testing, see 5.2.2.2.2 and 5.2.2.2.3.

It is recommended that the natural weathering according to EN 927-3 is extended for at least one year as specified in EN 927-3, since experience shows that the fire performance may degrade during up to 10 years [21, 20].

For the natural weathering, exposure at 45° slope is recommended.

Natural weathering at relevant conditions for the specific end use is most desirable, but such data are usually not available. It is recommended that a set of the products going through an accelerated weathering procedure is also exposed to natural weathering, in order to gain experience on the relationship between accelerated and natural weathering.

Additional variations of the product, e.g. additional coating systems (with ordinary paints), could preferably be evaluated at the same time. Examples of weathering studies are given in [21, 20].

5.2.2.2 Testing for reaction to fire performance

5.2.2.2.1 General

The reaction to fire performance after weathering shall be tested according to one of the following two procedures: