


SVENSK STANDARD

SS-EN 15022-4:2011

Fastställt/Approved: 2011-11-14
Publicerad/Published: 2011-11-17
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 77.120.30

Koppar och kopparlegeringar – Bestämning av tennhalt – Del 4: Medel tennhalt – Flamatomär absorptionsspektrometrimetod (FAAS)

Copper and copper alloys – Determination of tin content – Part 4: Medium tin content – Flame atomic absorption spectrometric method (FAAS)



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 15022-4:2011 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 15022-4:2011.

Denna standard ersätter SIS-CEN/TS 15022-4:2006, utgåva 1.

The European Standard EN 15022-4:2011 has the status of a Swedish Standard. This document contains the official version of EN 15022-4:2011.

This standard supersedes the Swedish Standard SIS-CEN/TS 15022-4:2006, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Koppar, SIS/TK 132.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 15022-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2011

ICS 77.120.30

Supersedes CEN/TS 15022-4:2006

English Version

**Copper and copper alloys - Determination of tin content - Part 4:
Medium tin content - Flame atomic absorption spectrometric
method (FAAS)**

Cuivre et alliages de cuivre - Détermination de la teneur en étain - Partie 4: Étain en moyenne teneur - Méthode par spectrométrie d'absorption atomique dans la flamme (SAAF)

Kupfer und Kupferlegierungen - Bestimmung des Zinngehaltes - Teil 4: Mittlerer Zinngehalt - Flammenatomabsorptionsspektrometrisches Verfahren (FAAS)

This European Standard was approved by CEN on 24 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Reagents	4
5 Apparatus	5
6 Sampling	5
7 Procedure	5
7.1 Preparation of the test portion solution	5
7.1.1 Test portion	5
7.1.2 Test portion solution	5
7.2 Blank test.....	5
7.3 Check test.....	5
7.4 Establishment of the calibration curve	6
7.4.1 Preparation of the calibration solutions.....	6
7.4.2 Adjustment of the atomic absorption spectrometer.....	6
7.4.3 Spectrometric measurement of the calibration solutions	7
7.4.4 Calibration curve.....	7
7.5 Determination.....	7
7.5.1 General.....	7
7.5.2 Preliminary spectrometric measurement.....	7
7.5.3 Spectrometric measurements	7
8 Expression of results	8
8.1 Use of calibration curve	8
8.2 Use of bracketing method.....	8
9 Precision.....	8
10 Test report	9
Bibliography	11

Foreword

This document (EN 15022-4:2011) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2012, and conflicting national standards shall be withdrawn at the latest by May 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15022-4:2006.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 "Methods of analysis" to prepare the revision of the following document:

CEN/TS 15022-4:2006, *Copper and copper alloys — Determination of tin content — Part 4: Medium tin content — Flame atomic absorption spectrometry method (FAAS)*.

In comparison with the first edition of CEN/TS 15022-4:2006, the following significant technical changes were made:

- a) conversion into a European Standard;
- b) Clause 9 completely revised and the results of the precision test included.

This is one of four parts of the standard for the determination of tin content in copper and copper alloys. The other parts are:

- prEN 15022-1, *Copper and copper alloys — Determination of tin content — Part 1: Titrimetric method* (Part 1 will be the subject of a future work);
- CEN/TS 15022-2, *Copper and copper alloys — Determination of tin content — Part 2: Spectrophotometric method*;
- EN 15022-3, *Copper and copper alloys — Determination of tin content — Part 3: Low tin content — Flame atomic absorption spectrometry method (FAAS)*.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the tin content of copper and copper alloys in the form of unwrought, wrought and cast products.

The method is applicable to products having medium tin mass fractions between 0,2 % and 3,0 %.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

3 Principle

Dissolution of a test portion in hydrochloric acid and hydrogen peroxide followed, after suitable dilution, by aspiration into a nitrous oxide/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 286,3 nm line emitted by a tin hollow-cathode lamp.

4 Reagents

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Hydrochloric acid, HCl ($\rho = 1,19$ g/ml).

4.2 Hydrochloric acid solution, 7 + 3.

Add 700 ml of hydrochloric acid (4.1) to 300 ml of water.

4.3 Hydrogen peroxide, H₂O₂ 30 % (mass fraction) solution, free from tin base stabilizers.

Hydrogen peroxide may be stabilized by products containing some tin. It is therefore necessary to use exactly the same volume of hydrogen peroxide for the dissolution of the test sample as for the preparation of the corresponding blank test.

4.4 Tin stock solution, 1 g/l Sn.

Weigh ($1 \pm 0,001$) g of tin ($\text{Sn} \geq 99$ %) and transfer it into a 250 ml beaker. Dissolve it in 100 ml hydrochloric acid (4.1) and several drops of hydrogen peroxide (4.3) and cover with a watch glass. Heat gently until the metal is dissolved. Cool to room temperature and transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask. Dilute to the mark with water and mix.

1 ml of this solution contains 1 mg of Sn.