

# SVENSK STANDARD


## SS-EN 16124:2011

Fastställt/Approved: 2011-12-05  
Publicerad/Published: 2011-12-06  
Utgåva/Edition: 1  
Språk/Language: engelska/English  
ICS: 77.080.10

---

### **Gjutning – Låglegerade, ferritiska segjärn för högtemperaturtillämpningar**

### **Founding – Low-alloyed ferritic spheroidal graphite cast irons for elevated temperature applications**



# Standarder får världen att fungera

*SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.*

## Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

## Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

## Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

**Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på [www.sis.se](http://www.sis.se) eller ta kontakt med oss på tel 08-555 523 00.**



# Standards make the world go round

*SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.*

## Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.


## Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

## Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

**If you want to know more about SIS, or how standards can streamline your organisation, please visit [www.sis.se](http://www.sis.se) or contact us on phone +46 (0)8-555 523 00**



Europastandarden EN 16124:2011 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 16124:2011.

The European Standard EN 16124:2011 has the status of a Swedish Standard. This document contains the official version of EN 16124:2011.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

*Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.*

*Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.*

Denna standard är framtagen av kommittén för Gjutet järn och stål, SIS/TK 130.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på [www.sis.se](http://www.sis.se) - där hittar du mer information.



EUROPEAN STANDARD

**EN 16124**

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2011

---

ICS 77.080.10

English Version

## Founding - Low-alloyed ferritic spheroidal graphite cast irons for elevated temperature applications

Fonderie - Fontes ferritiques à graphite sphéroïdal faiblement alliées pour applications à haute température

Gießereiwesen - Niedriglegiertes ferritisches Gusseisen mit Kugelgraphit für Anwendungen bei höheren Temperaturen

This European Standard was approved by CEN on 15 October 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
Foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
3 Terms and definitions .....	5
4 Designation .....	6
5 Order information .....	6
6 Manufacture.....	6
7 Requirements .....	7
7.1 Chemical composition .....	7
7.2 Microstructure.....	7
7.3 Mechanical properties.....	8
8 Sampling.....	9
8.1 General.....	9
8.2 Cast samples for tensile testing.....	9
8.3 Samples cut from a casting .....	11
9 Test methods.....	15
9.1 Chemical analysis.....	15
9.2 Micrographic examination .....	15
9.3 Tensile test .....	15
9.4 Hardness test .....	16
9.5 Specific test.....	16
10 Retests .....	17
10.1 Need for retests.....	17
10.2 Test validity .....	17
10.3 Non-conforming test results.....	17
10.4 Heat treatment of samples and castings.....	17
11 Inspection documentation .....	17
Annex A (informative) Guidance values of mechanical properties for 3 special grades.....	18
Annex B (informative) Properties of low alloyed ferritic spheroidal graphite cast irons at elevated temperatures .....	19
Annex C (informative) Additional information on general mechanical and physical properties .....	33
Annex D (informative) Heat treatment .....	34
Annex E (informative) Nodularity.....	35
Annex F (normative) Sectioning procedure for cast samples.....	36
Bibliography .....	37

## Foreword

This document (EN 16124:2011) has been prepared by Technical Committee CEN/TC 190 "Foundry technology", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2012, and conflicting national standards shall be withdrawn at the latest by May 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 7 "Spheroidal graphite, silicon molybdenum and austempered ductile iron" to prepare EN 16124.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

This European Standard classifies low-alloyed ferritic spheroidal graphite cast irons, principally used for their heat and oxidation resistance properties.

NOTE Ferritic spheroidal graphite cast irons alloyed with silicon and molybdenum is also known as SiMo cast irons.

Due to the ferritic structure and the silicon and molybdenum content, these cast irons allow producing castings which are resistant to distortion and oxidation at high temperatures.

Nine grades of low-alloyed ferritic spheroidal graphite cast iron are defined by their silicon and molybdenum content.

Typical applications for the first three grades are medium to heavy castings like turbine housings and compressor parts. The other six grades are mainly applied for exhaust manifolds and turbocharger parts in automotive applications.

The mechanical properties of the material can be evaluated on machined test pieces prepared from cast samples or samples cut from a casting.

Additional information on technical properties for low-alloyed ferritic spheroidal graphite cast iron is given in Annex B and Annex C.



## 1 Scope

This European Standard defines the grades and the corresponding requirements for low-alloyed ferritic spheroidal graphite cast irons for elevated temperature applications.

These requirements are specified in terms of

- chemical composition: as given for each of the grades,
- graphite form and matrix structure: spheroidal graphite in a predominantly ferritic matrix,
- mechanical properties measured on machined test pieces prepared from cast samples.

This European Standard does not cover technical delivery conditions for iron castings, see EN 1559-1 [1] and EN 1559-3 [2].

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10204, *Metallic products — Types of inspection documents*

EN ISO 945-1:2008, *Microstructure of cast irons — Part 1: Graphite classification by visual analysis (ISO 945-1:2008)*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **low alloyed ferritic spheroidal graphite cast iron**

cast iron material with carbon mainly present in the form of spheroidal graphite particles, alloyed with silicon in order to produce a predominantly ferritic matrix and alloyed with molybdenum to improve mechanical properties at elevated temperatures

### 3.2

#### **graphite spheroidizing treatment**

operation that brings the liquid iron into contact with a substance to produce graphite in the predominantly spheroidal (nodular) form during solidification

NOTE This operation is often followed by a second one called inoculation.

### 3.3

#### **cast sample**

quantity of material cast to represent the cast material, including separately cast sample, side by side cast sample and cast-on sample

### 3.4

#### **separately cast sample**

sample cast in a separate sand mould under representative manufacturing conditions and material grade

- 3.5**  
**side-by-side cast sample**  
sample cast in the mould alongside the casting, with a joint running system
- 3.6**  
**cast-on sample**  
sample attached directly to the casting
- 3.7**  
**relevant wall thickness**  
wall thickness representative of the casting, defined for the determination of the size of the cast samples to which the mechanical properties apply

## 4 Designation

The material shall be designated either by symbol or by number as given in Table 1.

NOTE The designation system is in accordance with EN 1560 [3].

In the case of samples cut from the casting, the letter C is added at the end of the designation by symbol.

## 5 Order information

The following information shall be supplied by the purchaser:

- a) the number of this European Standard;
- b) the designation of the material;
- c) the relevant wall thickness of the casting;
- d) any special requirements.

All requirements shall be agreed between the manufacturer and the purchaser by the time of acceptance of the order, e.g. technical delivery conditions according to EN 1559-1 and EN 1559-3.

## 6 Manufacture

Unless otherwise specified by the purchaser, the method of manufacture of low-alloyed ferritic spheroidal graphite cast irons and any heat treatment required to obtain the specified mechanical properties and microstructure shall be left to the discretion of the manufacturer.

The manufacturer shall ensure that the requirements defined in this European Standard are met for the material grade specified in the order.

All agreements between the manufacturer and the purchaser shall be made by the time of acceptance of the order.

## 7 Requirements

### 7.1 Chemical composition

The silicon and molybdenum content of low-alloyed ferritic spheroidal graphite cast iron grades shall be in accordance with Table 1.

Unless otherwise agreed, the content of other elements shall be left to the discretion of the manufacturer.

If the presence of any element specified in Table 1 is required to be outside the limits indicated, or if any other alloying elements are required, their contents shall be agreed between the manufacturer and the purchaser and specified in the order.

**Table 1 — Chemical composition**

Material designation		Silicon % (mass fraction)	Molybdenum % (mass fraction)
Symbol	Number		
EN-GJS-SiMo25-5	5.3111	2,3 to 2,7	0,4 to 0,6
EN-GJS-SiMo30-7	5.3112	2,8 to 3,2	0,6 to 0,8
EN-GJS-SiMo35-5	5.3113	3,3 to 3,7	0,4 to 0,6
EN-GJS-SiMo40-6	5.3114	3,8 to 4,2	0,5 to 0,7
EN-GJS-SiMo40-10	5.3115		0,8 to 1,1
EN-GJS-SiMo45-6	5.3116	4,3 to 4,7	0,5 to 0,7
EN-GJS-SiMo45-10	5.3117		0,8 to 1,1
EN-GJS-SiMo50-6	5.3118	4,8 to 5,2	0,5 to 0,7
EN-GJS-SiMo50-10	5.3119		0,8 to 1,1

### 7.2 Microstructure

#### 7.2.1 Graphite structure

The graphite structure shall be mainly of form V and VI in accordance with EN ISO 945-1. A more precise definition may be agreed upon by the time of acceptance of the order.

NOTE Annex E gives more information on nodularity.

#### 7.2.2 Matrix structure

The matrix structure shall consist of minimum 85 % ferrite, the balance consisting of pearlite and carbides.

Carbides can be present to a maximum of 5 %.

Other limits may be agreed upon by the time of acceptance of the order.