


Teknisk specifikation

SIS-CEN/TS 15912:2012

Publicerad/Published: 2012-09-04
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 71.100.50

Bruksklasser för brandskyddets beständighet inomhus och utomhus hos träbaserade produkter

Durability of reaction to fire performances – Classes of fire-retardant treated wood-based product in interior and exterior end use applications



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.


Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Denna tekniska specifikation är inte en svensk standard. Detta dokument innehåller den engelska språkversionen av CEN/TS 15912:2012.

This Technical Specification is not a Swedish Standard. This document contains the English version of CEN/TS 15912:2012.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i detta dokument lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om nationell och internationell standard.

Information about the content of this document is available from the SIS, Swedish Standards Institute, telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about national and international standards.

Dokumentet är framtaget av kommittén för Trä, SIS/TK 182.

Har du synpunkter på innehållet i det här dokumentet, vill du delta i ett kommande revideringsarbete eller vara med och ta fram standarder inom området? Gå in på www.sis.se - där hittar du mer information.

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 15912

April 2012

ICS 71.100.50

English Version

Durability of reaction to fire performance - Classes of fire-retardant treated wood-based product in interior and exterior end use applications

Durabilité des performances de réaction au feu -
Classement des produits à base de bois ignifugés pour
utilisation finale en intérieur et en extérieur

Dauerhaftigkeit des Verhaltens bei Brandeinwirkung -
Klassen der mit Feuerschutzmitteln behandelten
Holzprodukte für Anwendungen im Innen- und
Außenbereich

This Technical Specification (CEN/TS) was approved by CEN on 14 February 2012 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Symbols	7
5 Requirements	7
5.1 Wood-based products and non-fire-retardant coating systems.....	7
5.2 Reaction to fire performance	8
5.2.1 Initial classification for reaction to fire.....	8
5.2.2 Reaction to fire performance before and after accelerated or natural weathering.....	8
5.3 Durability of reaction to fire performance	9
5.3.1 General.....	9
5.3.2 DRF Class ST	9
5.3.3 DRF Class INT1	9
5.3.4 DRF Class INT2	9
5.3.5 DRF Class EXT	9
6 Practices to use the DRF classification system	11
7 Classification report	11
Annex A (informative) Test methods.....	13
A.1 Hygroscopic properties of fire-retardant treated wood-based products including those with fire-retardant coatings	13
A.1.1 General.....	13
A.1.2 Field of application	13
A.1.3 Sampling, sample handling and preparation	14
A.1.4 Test method.....	15
A.2 Accelerated weathering of fire-retardant treated wood for fire testing.....	17
A.2.1 General.....	17
A.2.2 Field of application	18
A.2.3 Sampling, sample handling and preparation	18
A.2.4 Test method.....	19
A.3 Building materials and components in the vertical position: Exposure to accelerated climate strains.....	21
A.3.1 General.....	21
A.3.2 Field of application	21
A.3.3 Sampling.....	21
A.3.4 Test method.....	22
Annex B (informative) Example of classification report.....	26
B.1 Classification report: Durability classes of reaction to fire performance of fire-retardant wood-based products in interior and exterior end use applications according to CEN/TS 15912	26
B.1.1 Product	26
B.1.2 Product specification	26
B.1.3 Requirements	27
B.1.4 Evaluation documents	27
B.1.5 Durability of reaction to fire performance (DRF) Class	28
B.1.6 Applicability of DRF Class	28

B.1.7 Service life	29
Bibliography	30

Foreword

This document (CEN/TS 15912:2012) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Fire-retardant treatments may considerably improve the reaction to fire properties of wood and wood-based products and these may result in wood having the highest fire-resisting characteristics achievable with any combustible product. However, the reaction to fire performance may be reduced by exposure to wet and/or humid conditions [1] and the ability of treatments to continue to perform even when exposed to these conditions needs to be demonstrated.

Two aspects of fire durability of the fire-retardant treatment of wood-based products need to be considered. One is the risk for high moisture content and migration of the fire-retardant chemicals within the wood product and salt crystallisation on the product surface. These hygroscopic properties of the treated wood-based product can be evaluated by exposure to high relative humidity.

The other aspect is the risk for decreased fire performance due to loss of the fire-retardant chemicals by leaching in exterior applications, e.g. facade claddings. Maintained fire performance after weathering needs to be verified.

The Technical Specification is based on a Nordtest standard [15] and on experience from North America [7] [12].

1 Scope

This European Technical Specification describes the characteristics which fire-retardant treated wood products should exhibit so that their fire-retardant properties persist undiminished throughout the desired service life in the anticipated conditions of use.

The Technical Specification prescribes the classification requirements for the durability of the reaction to fire performance of fire-retardant treated wood-based products to be used in interior and exterior end use conditions. The products initially need to meet required reaction to fire classification. For interior and exterior use, limited hygroscopicity needs to be verified. In addition, products for exterior use needs to meet the minimum durability of reaction to fire performance requirements specific to the end use.

The requirements are applicable for fire-retardant treated (applied by penetrating and superficial processes or with film forming or intumescent fire-retardant coatings) solid wood and wood-based products and wood-based products in which the fire-retardant is incorporated during manufacture. The fire-retardant treated products may be coated with an ordinary paint.

Mechanical properties and biological durability of fire-retardant treated wood products are not covered by this European Technical Specification.

Paints, coatings and varnishes intended to improve the reaction to fire performance of a construction product when incorporated in the works, i.e. a building, are covered by ETAG 028 [19].

This Technical Specification may be used as a basis for an approval system.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 927-3, *Paints and varnishes — Coating materials and coating systems for exterior wood — Part 3: Natural weathering test*

EN 13238, *Reaction to fire tests for building products — Conditioning procedures and general rules for selection of substrates*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

durability of reaction to fire performance

DRF

four classes for the Durability of Reaction to Fire performance are defined:

- **DRF Class ST** for short term use (e.g. less than one year); no durability performance shall be verified;
- **DRF Class INT1** for permanent use in interior applications, service class 1 (e.g. wall and ceiling products);

- **DRF Class INT2** for permanent use in interior applications and certain protected exterior applications, service class 2 (e.g. wall and ceiling products);
- **DRF Class EXT** for permanent use in exterior applications, service class 3 (e.g. facade claddings, exterior conditions)

3.2 service classes

3.2.1 dry condition

moisture content in the materials corresponding to a temperature of 20 °C and the relative humidity of the surrounding air only exceeding 65 % for a few weeks per year

Note 1 to entry: In Eurocode EN 1995-1-1 as Service class 1.

3.2.2 humid condition

moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air only exceeding 85 % for a few weeks per year

Note 1 to entry: In EN 1995-1-1 defined as Service class 2.

3.3 ordinary paint non-fire retardant paint

4 Symbols

The symbols for DRF Classes ST, INT1, INT2 and EXT are the followings:




Figure 1 — Proposed symbols for classes

5 Requirements

5.1 Wood-based products and non-fire-retardant coating systems

The treatment manufacturing process and application rate declared by the producer shall be declared by the manufacturer of the final product. Remaining fire-retardant chemicals in terms of kg/m^3 of the final wood-based product, or in terms of kg/m^2 for surface treated products, shall be specified. Values shall be given for products conditioned at $(50 \pm 5) \%$ relative humidity at $(23 \pm 2) \text{ }^\circ\text{C}$ (as for fire testing).

For products in DRF Classes INT and EXT the following procedures shall be provided by the manufacturers:

- type of maintenance;
- interval of maintenance;
- time until to the first maintenance/recoating (if relevant);