

SVENSK STANDARD

SS-EN ISO 5755:2012



Fastställt/Approved: 2012-09-20
Publicerad/Published: 2012-09-25
Utgåva/Edition: 1
Språk/Language: engelska/English
ICS: 77.160

Sintermetall – Specifikationer (ISO 5755:2012)

Sintered metal materials – Specifications (ISO 5755:2012)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-87519>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN ISO 5755:2012 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 5755:2012.

The European Standard EN ISO 5755:2012 has the status of a Swedish Standard. This document contains the official version of EN ISO 5755:2012.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Pulvermetallurgi, SIS/TK 133.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN ISO 5755

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2012

ICS 77.160

English Version

Sintered metal materials - Specifications (ISO 5755:2012)

Matériaux métalliques frittés - Spécifications (ISO 5755:2012)

Sintermetalle - Anforderungen (ISO 5755:2012)

This European Standard was approved by CEN on 25 August 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Sampling	3
5 Test methods for normative properties	3
5.1 General	3
5.2 Chemical analysis	3
5.3 Open porosity	3
5.4 Mechanical properties.....	4
6 Test methods for informative properties	5
6.1 General	5
6.2 Density.....	5
6.3 Tensile strength.....	5
6.4 Tensile yield strength.....	5
6.5 Elongation	5
6.6 Young's modulus	5
6.7 Poisson's ratio.....	5
6.8 Impact energy	6
6.9 Compressive yield strength	6
6.10 Transverse rupture strength	6
6.11 Fatigue strength	6
6.12 Apparent hardness.....	7
6.13 Coefficient of linear expansion	7
7 Specifications	7
8 Designations	7
Annex A (normative) Designation system.....	33
Annex B (informative) Microstructures.....	36
Bibliography.....	39

Foreword

This document (EN ISO 5755:2012) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2013, and conflicting national standards shall be withdrawn at the latest by March 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 5755:2012 has been approved by CEN as a EN ISO 5755:2012 without any modification.

SS-EN ISO 5755:2012 (E)

Sintered metal materials — Specifications

1 Scope

This International Standard specifies the requirements for the chemical composition and the mechanical and physical properties of sintered metal materials used for bearings and structural parts.

When selecting powder metallurgical (PM) materials, it should be taken into account that the properties depend not only on the chemical composition and density, but also on the production methods. The properties of sintered materials giving satisfactory service in particular applications may not necessarily be the same as those of wrought or cast materials that might otherwise be used. Therefore, liaison with prospective suppliers is recommended.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 437, *Steel and cast iron — Determination of total carbon content — Combustion gravimetric method*

ISO 1099, *Metallic materials — Fatigue testing — Axial force-controlled method*

ISO 1143, *Metallic materials — Rotating bar bending fatigue testing*

ISO 2738, *Sintered metal materials, excluding hardmetals — Permeable sintered metal materials — Determination of density, oil content and open porosity*

ISO 2739, *Sintered metal bushings — Determination of radial crushing strength*

ISO 2740, *Sintered metal materials, excluding hardmetals — Tensile test pieces*

ISO 2795, *Plain bearings — Sintered bushes — Dimensions and tolerances*

ISO 3325, *Sintered metal materials, excluding hardmetals — Determination of transverse rupture strength*

ISO 3928, *Sintered metal materials, excluding hardmetals — Fatigue test pieces*

ISO 3954, *Powders for powder metallurgical purposes — Sampling*

ISO 4498, *Sintered metal materials, excluding hardmetals — Determination of apparent hardness and micro-hardness*

ISO 5754, *Sintered metal materials, excluding hardmetals — Unnotched impact test piece*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7625, *Sintered metal materials, excluding hardmetals — Preparation of samples for chemical analysis for determination of carbon content*

SS-EN ISO 5755:2012 (E)

ISO 14317, *Sintered metal materials, excluding hardmetals — Determination of compressive yield strength*

ASTM E228, *Standard Test Method for Linear Thermal Expansion of Solid Materials with a Push-Rod Dilatometer*

ASTM E1875, *Standard Test Method for Dynamic Young's Modulus, Shear Modulus, and Poisson's Ratio by Sonic Resonance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 tensile strength

R_m
ability of a test specimen to resist fracture when a pulling force is applied in a direction parallel to its longitudinal axis – expressed in MPa

NOTE It is equal to the maximum load divided by the original cross-sectional area.

3.2 tensile yield strength

$R_{p0,2}$
load at which the material exhibits a 0,2 % offset from proportionality on a stress-strain curve in tension, divided by the original cross-sectional area – expressed in MPa

3.3 Young's modulus

E
ratio of normal stress to corresponding strain for tensile or compressive stresses below the proportional limit of the material – expressed in GPa

3.4 Poisson's ratio

ν
absolute value of the ratio of transverse strain to the corresponding axial strain, resulting from uniformly distributed axial stress below the proportional limit of the material

3.5 impact energy

measurement of the energy absorbed when fracturing a specimen with a single blow – measured in Joules (J)

3.6 compressive yield strength

stress at which a material exhibits a specified permanent set – expressed in MPa

3.7 transverse rupture strength

stress, calculated from the bending strength formula, required to break a specimen of a given dimension – expressed in MPa

3.8 fatigue strength

maximum alternating stress that can be sustained for a specific number of cycles without failure, the stress being reversed with each cycle unless otherwise stated – expressed in MPa

3.9

radial crushing strength

radial stress required to fracture a hollow cylindrical part of specified dimensions – expressed in MPa

3.10

density

mass per unit volume of the material – expressed in g/cm³

3.11

apparent hardness

resistance of a powder metallurgical (PM) material to indentation, tested under specified conditions; for PM materials, it is a function of the density of the material

3.12

open porosity

oil content after full impregnation, divided by the volume of the test piece, and multiplied by 100 – expressed as a volume percentage

3.13

coefficient of linear expansion

change in length per unit length per degree change in temperature – expressed in 10⁻⁶ K⁻¹

4 Sampling

Sampling of powders to produce standard test pieces shall be carried out in accordance with ISO 3954.

5 Test methods for normative properties

5.1 General

The following test methods shall be used to determine the normative properties given in Tables 1 to 18.

5.2 Chemical analysis

The chemical composition table for each material lists the principal elements by minimum and maximum mass percentage before any additional process, such as oil impregnation, resin impregnation or steam treatment, has taken place. “Other elements” may include minor amounts of elements added for specific purposes and is reported as a maximum percentage.

Whenever possible, and always in cases of dispute, the methods of chemical analysis shall be those specified in the relevant International Standards. If no International Standard is available, the method may be agreed upon and specified at the time of enquiry and order.

Samples for the determination of total carbon content shall be prepared in accordance with ISO 7625. Determination of the total carbon content shall be in accordance with ISO 437.

5.3 Open porosity

The open porosity shall be determined in accordance with ISO 2738.