

SVENSK STANDARD

SS-EN 13602:2013



Fastställt/Approved: 2013-06-23
Publicerad/Published: 2013-06-24
Utgåva/Edition: 2
Språk/Language: engelska/English
ICS: 77.150.30

Koppar och kopparlegeringar – Dragen rundtråd av koppar för tillverkning av elektriska ledare

Copper and copper alloys – Drawn, round copper wire for the manufacture of electrical conductors



Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN 13602:2013 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN 13602:2013.

Denna standard ersätter SS-EN 13602, utgåva 1.

The European Standard EN 13602:2013 has the status of a Swedish Standard. This document contains the official version of EN 13602:2013.

This standard supersedes the Swedish Standard SS-EN 13602, edition 1.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Uppllysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna uppllysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Koppar, SIS/TK 132.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN 13602

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2013

ICS 77.150.30

Supersedes EN 13602:2002

English Version

Copper and copper alloys - Drawn, round copper wire for the manufacture of electrical conductors

Cuivre et alliages de cuivre - Fils ronds en cuivre étirés
pour la fabrication des conducteurs électriques

Kupfer und Kupferlegierungen - Gezogener Runddraht aus
Kupfer zur Herstellung elektrischer Leiter

This European Standard was approved by CEN on 25 April 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Designations	6
4.1 Material	6
4.2 Material condition	6
4.3 Product	7
5 Ordering information	8
6 Requirements	9
6.1 Composition	9
6.2 Mechanical properties	10
6.3 Electrical properties	10
6.4 Dimensions	10
6.5 Ductility	10
6.6 Surface condition	10
7 Sampling	11
7.1 General	11
7.2 Analysis	11
7.3 Mechanical, electrical and tin coating tests	11
8 Test methods	11
8.1 Analysis	11
8.2 Tensile test	11
8.3 Ductility test	12
8.4 Electrical resistivity test	12
8.5 Assessment of tin coatings	12
8.6 Retests	12
8.7 Rounding of results	12
9 Declaration of conformity and inspection documentation	13
9.1 Declaration of conformity	13
9.2 Inspection documentation	13
10 Marking, packaging, labelling	13
Annex A (informative) Characteristics of coppers for electrical purposes	20
A.1 General grouping of copper types	20
A.2 General characteristics	20
A.3 Particular characteristics	20
Bibliography	22
 Tables	
Table 1 — Composition of Cu-ETP1 (CW003A) and Cu-OF1 (CW007A)	14
Table 2 — Composition of Cu-ETP (CW004A), Cu-FRHC (CW005A) and Cu-OF (CW008A)	15
Table 3 — Mechanical properties of plain wire	16
Table 4 — Mechanical properties of tinned wire	17

Table 5 — Electrical properties (at 20 °C)	18
Table 6 — Tolerances on diameter	19
Table 7 — Requirements of coatings	19
Table 8 — Number of bends for annealed wire.....	19
Table 9 — Number of bends for hard drawn wire	19
Table A.1 — Particular characteristics of copper grades for electrical purposes.....	21

Foreword

This document (EN 13602:2013) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2013, and conflicting national standards shall be withdrawn at the latest by December 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13602:2002.

In comparison with EN 13602:2002, the following changes were made:

- Terms have been modified.
- Normative references have been updated.
- Editorial modifications have been made.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 4 "Extruded and drawn products, forgings and scrap" to prepare the following revision of the standard:

EN 13602:2002, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*.

The products specified in this European Standard are those which are especially suitable for electrical purposes, i.e. with specified electrical properties. Drawn round wire for general purposes is specified in EN 12166.

This is one of a series of European Standards for copper products for electrical purposes. Other copper products are specified as follows:

- EN 13599, *Copper and copper alloys — Copper plate, sheet and strip for electrical purposes*
- EN 13600, *Copper and copper alloys — Seamless copper tubes for electrical purposes*
- EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*
- EN 13604, *Copper and copper alloys — Semiconductor devices, electronic and vacuum products made from high conductivity copper*
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wire for electrical purposes*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the composition, property requirements including electrical properties, and dimensional tolerances for drawn round copper wire from 0,04 mm up to and including 5,0 mm for the manufacture of electrical conductors intended for the production of bare and insulated cables and flexible cords.

This standard covers plain or tinned, single or multilined, annealed or hard drawn wire. It does not include wire for enamelling (winding wire, magnet wire), for electronic application and for contact wire for electric traction.

The sampling procedures, the test methods for verification of conformity to the requirements of this standard and the delivery conditions are also specified.

NOTE Due to the thermal and/or mechanical treatment involved in cabling processes, the properties of conductors in the final cable or cord differ from those of the original wire supplied. Requirements for conductors taken from cable or cord are given in appropriate cable standards.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 610, *Tin and tin alloys — Ingot tin*

EN 1655, *Copper and copper alloys — Declarations of conformity*

EN 1976, *Copper and copper alloys — Cast unwrought copper products*

EN 10204, *Metallic products — Types of inspection documents*

EN 13603, *Copper and copper alloys — Test methods for assessing protective tin coatings on drawn round copper wire for electrical purposes*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

IEC 60468, *Method of measurement of resistivity of metallic materials*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

ISO 4739, *Wrought copper and copper alloy products — Selection and preparation of specimens and test pieces for mechanical testing*

ISO 7801, *Metallic materials — Wire — Reverse bend test*

ISO 7802, *Metallic materials — Wire — Wrapping test*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 wire

wound product of uniform cross-section along its whole length

Note 1 to entry: Rectangles may have round or sharp corners.

[SOURCE: EN 12166:2011, 3.1]

3.2

multiline wire

number of wires of the same nominal diameter and material condition wound at the same time on the same spool with the wires having a maximum of one twist per revolution of the spool

Note 1 to entry: Generally, the wires are drawn simultaneously on the same machine.

3.3

deviation from circular form

difference between the maximum and the minimum diameters measured at any one cross-section of a round product

[SOURCE: EN 12163:2011, 3.2]

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or by number (see Table 1 and Table 2).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1.

NOTE Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.

4.2 Material condition

For the purposes of this standard, the following designations, which are in accordance with the system given in EN 1173, apply for the material condition:

R... Material condition designated by the minimum value of tensile strength requirement for the product with mandatory tensile strength requirements;

A... Material condition designated by the minimum value of elongation requirement for the product with mandatory elongation requirements.

Exact conversion between the material conditions designated R... and A... is not possible.

Material condition is designated by only one of the above designations.

4.3 Product

The product designation provides a standardised pattern of designation from which a rapid and unequivocal description of a product can be conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant European Standard.

The product designation is no substitute for the full content of the standard.

The product designation for products to this standard shall consist of:

- a) denomination (wire);
- b) number of this European Standard (EN 13602);
- c) material designation, either symbol or number (see Table 1 and Table 2);
- d) material condition designation (see Table 3 and Table 4);
- e) surface condition: plain (P) or tinned (grade A, B or C, see Table 7);
- f) nominal dimensions:
 - 1) single wire (S): diameter;
 - 2) multiline wire (M): number of wires and diameter;
- g) form of delivery: coil (Y) or spool (Z).

The derivation of a product designation is shown in Example 1.

EXAMPLE 1 Plain single wire

Drawn round wire for electrical purposes conforming to this standard, in material designated either Cu-ETP1 or CW003A, in material condition A022, produced as a plain single wire, nominal diameter 0,4 mm, in coils, will be designated as follows:

Wire — EN 13602 — Cu-ETP1 — A022 — P — S0,4 — Y

or

Wire — EN 13602 — CW003A — A022 — P — S0,4 — Y

