

SVENSK STANDARD

SS-EN ISO 14113:2013

Fastställt/Approved: 2013-10-06
Publicerad/Published: 2013-10-08
Utgåva/Edition: 3
Språk/Language: engelska/English
ICS: 23.040.70; 25.160.30; 83.140.40

Svetsutrustning – Gassvetsning – Slangar av gummi och plast med anslutningar för industriella gaser vid tryck upp till 450 bar (45 MPa) (ISO 14113:2013)

Gas welding equipment – Rubber and plastics hose and hose assemblies for use with industrial gases up to 450 bar (45 MPa) (ISO 14113:2013)

This preview is downloaded from www.sis.se. Buy the entire standard via <https://www.sis.se/std-99609>

Standarder får världen att fungera

SIS (Swedish Standards Institute) är en fristående ideell förening med medlemmar från både privat och offentlig sektor. Vi är en del av det europeiska och globala nätverk som utarbetar internationella standarder. Standarder är dokumenterad kunskap utvecklad av framstående aktörer inom industri, näringsliv och samhälle och befrämjar handel över gränser, bidrar till att processer och produkter blir säkrare samt effektiviserar din verksamhet.

Delta och påverka

Som medlem i SIS har du möjlighet att påverka framtida standarder inom ditt område på nationell, europeisk och global nivå. Du får samtidigt tillgång till tidig information om utvecklingen inom din bransch.

Ta del av det färdiga arbetet

Vi erbjuder våra kunder allt som rör standarder och deras tillämpning. Hos oss kan du köpa alla publikationer du behöver – allt från enskilda standarder, tekniska rapporter och standardpaket till handböcker och onlinetjänster. Genom vår webbtjänst e-nav får du tillgång till ett lättnavigerat bibliotek där alla standarder som är aktuella för ditt företag finns tillgängliga. Standarder och handböcker är källor till kunskap. Vi säljer dem.

Utveckla din kompetens och lyckas bättre i ditt arbete

Hos SIS kan du gå öppna eller företagsinterna utbildningar kring innehåll och tillämpning av standarder. Genom vår närhet till den internationella utvecklingen och ISO får du rätt kunskap i rätt tid, direkt från källan. Med vår kunskap om standarders möjligheter hjälper vi våra kunder att skapa verklig nytta och lönsamhet i sina verksamheter.

Vill du veta mer om SIS eller hur standarder kan effektivisera din verksamhet är du välkommen in på www.sis.se eller ta kontakt med oss på tel 08-555 523 00.



Standards make the world go round

SIS (Swedish Standards Institute) is an independent non-profit organisation with members from both the private and public sectors. We are part of the European and global network that draws up international standards. Standards consist of documented knowledge developed by prominent actors within the industry, business world and society. They promote cross-border trade, they help to make processes and products safer and they streamline your organisation.

Take part and have influence

As a member of SIS you will have the possibility to participate in standardization activities on national, European and global level. The membership in SIS will give you the opportunity to influence future standards and gain access to early stage information about developments within your field.

Get to know the finished work

We offer our customers everything in connection with standards and their application. You can purchase all the publications you need from us - everything from individual standards, technical reports and standard packages through to manuals and online services. Our web service e-nav gives you access to an easy-to-navigate library where all standards that are relevant to your company are available. Standards and manuals are sources of knowledge. We sell them.

Increase understanding and improve perception

With SIS you can undergo either shared or in-house training in the content and application of standards. Thanks to our proximity to international development and ISO you receive the right knowledge at the right time, direct from the source. With our knowledge about the potential of standards, we assist our customers in creating tangible benefit and profitability in their organisations.

If you want to know more about SIS, or how standards can streamline your organisation, please visit www.sis.se or contact us on phone +46 (0)8-555 523 00



Europastandarden EN ISO 14113:2013 gäller som svensk standard. Detta dokument innehåller den officiella engelska versionen av EN ISO 14113:2013.

Denna standard ersätter SS-EN ISO 14113:2008, utgåva 2.

The European Standard EN ISO 14113:2013 has the status of a Swedish Standard. This document contains the official version of EN ISO 14113:2013.

This standard supersedes the Swedish Standard SS-EN ISO 14113:2008, edition 2.

© Copyright/Upphovsrätten till denna produkt tillhör SIS, Swedish Standards Institute, Stockholm, Sverige. Användningen av denna produkt regleras av slutanvändarlicensen som återfinns i denna produkt, se standardens sista sidor.

© Copyright SIS, Swedish Standards Institute, Stockholm, Sweden. All rights reserved. The use of this product is governed by the end-user licence for this product. You will find the licence in the end of this document.

Upplysningar om sakinnehållet i standarden lämnas av SIS, Swedish Standards Institute, telefon 08-555 520 00. Standarder kan beställas hos SIS Förlag AB som även lämnar allmänna upplysningar om svensk och utländsk standard.

Information about the content of the standard is available from the Swedish Standards Institute (SIS), telephone +46 8 555 520 00. Standards may be ordered from SIS Förlag AB, who can also provide general information about Swedish and foreign standards.

Denna standard är framtagen av kommittén för Svetsutrustning, SIS/TK 119.

Har du synpunkter på innehållet i den här standarden, vill du delta i ett kommande revideringsarbete eller vara med och ta fram andra standarder inom området? Gå in på www.sis.se - där hittar du mer information.

EUROPEAN STANDARD

EN ISO 14113

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2013

ICS 25.160.30; 83.140.40

Supersedes EN ISO 14113:2008

English Version

Gas welding equipment - Rubber and plastics hose and hose assemblies for use with industrial gases up to 450 bar (45 MPa) (ISO 14113:2013)

Matériel de soudage aux gaz - Tuyaux souples et flexibles en caoutchouc et en plastique pour des gaz industriels jusqu'à 450 bar (45 MPa) (ISO 14113:2013)

Gasschweißgeräte - Gummi- und Kunststoffschläuche und Schlauchleitungen für Industriegase bis zu einem Druck von 450 bar (45 MPa) (ISO 14113:2013)

This European Standard was approved by CEN on 3 September 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword		iv
1 Scope		1
2 Normative references		1
3 Terms and definitions		2
4 Construction		3
4.1 Hose		3
4.2 End fittings		3
4.3 Hose assemblies		3
5 Dimensions and tolerances		3
5.1 Bore size		3
5.2 Concentricity		3
5.3 Cut lengths and tolerances		4
5.4 Length of hoses assemblies		4
6 Physical properties of lining and cover — Type tests		4
6.1 General		4
6.2 Resistance to ignition requirement for oxygen hose lining		5
6.3 Resistance to acetone (acetylene hose only)		5
7 Performance requirements — Type tests		5
7.1 Pressure resistance requirements		5
7.2 Adhesion (rubber hoses only)		6
7.3 Flexibility		6
7.4 Low temperature flexibility		6
7.5 Ozone resistance (for hoses with an outer protective cover of rubber)		6
7.6 UV resistance (for hoses with plastics cover)		6
7.7 Permeability to gas		6
7.8 Electrical conductivity		6
7.9 End fitting integrity		6
8 Performance requirements — Production tests		7
8.1 Pressure tests for hose assemblies		7
8.2 Leak test		7
8.3 Cleaning for oxygen service		7
9 Marking		7
10 Packaging		8
11 Instructions		8
Annex A (normative) Acetylene decomposition test for hose assemblies used in high pressure acetylene installations		9
Annex B (normative) Oxygen pressure surge test		10
Annex C (normative) Oxygen system installation considerations		12
Bibliography		13

Foreword

This document (EN ISO 14113:2013) has been prepared by Technical Committee ISO/TC 44 “Welding and allied processes” in collaboration with Technical Committee CEN/TC 121 “Welding and allied processes” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14113:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 14113:2013 has been approved by CEN as EN ISO 14113:2013 without any modification.

Gas welding equipment — Rubber and plastics hose and hose assemblies for use with industrial gases up to 450 bar (45 MPa)

1 Scope

This International Standard specifies requirements for rubber and plastics hose and hose assemblies for use with compressed, liquefied, and dissolved gases up to a maximum working pressure of 450 bar (45 MPa), within the ambient temperature range of -20 °C to $+60\text{ °C}$.

This International Standard applies to hose assemblies used to connect industrial gas cylinders to manifolds or bundles prior to any pressure reduction stage.

This International Standard does not cover rubber or thermoplastic hoses for welding, cutting, and allied processes (see ISO 3821 and ISO 12170).

This International Standard does not apply to refrigerated liquefied gases or to liquefied petroleum gases (LPG).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 1307:2006, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1746:1998, *Rubber or plastics hoses and tubing — Bending tests*

ISO 1817, *Rubber, vulcanized — Determination of the effect of liquids*

ISO 4080:1991, *Rubber and plastic hoses and hose assemblies — Determination of permeability to gas*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 4672:1997, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*

ISO 7326:2006, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8031, *Rubber and plastics hoses and hose assemblies — Determination of electrical properties*

ISO 8033:2006, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 15296, *Gas welding equipment — Vocabulary — Terms used for gas welding equipment*

ISO 11114-3, *Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test in oxygen atmosphere*

ISO 30013:2011, *Rubber and plastics hoses — Methods of exposure to laboratory light sources — Determination of changes in colour, appearance and other physical properties*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions in ISO 15296 and the following apply.

3.1

autogenous ignition temperature

temperature at which ignition of a sample occurs when subjected to oxygen pressure and heating and in the absence of a source of ignition other than the applied temperature

Note 1 to entry: The autogenous ignition temperature depends on the sample preparation, test apparatus, and test procedure employed.

3.2

burst pressure

pressure at which rupture of the hose occurs when tested to the relevant standard

[SOURCE: ISO 8330:2007, definition 2.1.21]

3.3

distance piece

length of metallic tubing at the end of a hose or hose assembly that serves to contain and cool the highest temperature gas that is formed by the effect of adiabatic compression, e.g. by the rapid opening of a cylinder valve

3.4

end fitting

sub-assembly of components enabling the hose to be safely connected to other pressurized equipment

3.5

hose assembly

length of hose with suitably attached end fittings

3.6

maximum working pressure

pressure to which a hose is designed to be subjected during service, including expected momentary surges

Note 1 to entry: This definition is consistent with that for a gas cylinder in ISO 10286:2007, A.2.4 maximum permissible operating pressure (the highest pressure permitted to be developed during service). ISO 10286:2007 defines "working pressure" as the "settled pressure ... at a uniform ... temperature of 15 °C in a full gas cylinder".

Note 2 to entry: Due to the peculiar characteristics of the acetylene cylinder, there is no clearly defined maximum working pressure for acetylene service. Applicable requirements for acetylene service are given in relevant clauses.

3.7

proof pressure

pressure applied during a non-destructive test and held for a specified period of time to prove the integrity of the construction

Note 1 to entry: It is expressed in bars.

[SOURCE: ISO 8330:2007, definition 2.1.104]

4 Construction

4.1 Hose

The hose should consist of either

- a rubber or plastics lining,
- reinforcement consisting of one or more layers, and
- an outer protective cover of permeable material or perforated rubber or plastics,

for flammable gas service, the hose shall also incorporate bonding wires to provide the electrical conductivity (see [7.8](#));

or

- a rubber or plastics lining, and
- reinforcement consisting of one or more layers of stainless steel wire braid and/or other corrosion and abrasion resistant material, which is also designed to act as an outer protective cover and provide electrical conductivity (see [7.8](#)).

4.2 End fittings

Fittings shall be of permanent, swage, or crimp design.

The fitting design shall enable the hose assembly to attain its burst pressure without fitting pullout or separation from the hose.

End fittings shall be manufactured from materials that are compatible with the gases and the environment to which they will be subjected, e.g. according to ISO 9539.

4.3 Hose assemblies

Assemblies shall consist of a length of hose and permanently attached end fittings. Field-attachable or reusable-type fittings shall not be used. Distance pieces, when used as heat sinks as part of hose assemblies for oxygen service (see [7.1.3](#)), shall not be readily detachable by the user.

For maximum working pressures in excess of 40 bar (4 MPa), hoses assembled should be provided with a suitable restraining cable or device, properly fitted to an anchor point to restrain the hose in the event of a hose assembly failure.

5 Dimensions and tolerances

5.1 Bore size

The bore of the hoses shall be in accordance with the nominal bore sizes and permitted ranges given in [Table 1](#), except that the effective maximum bore of hoses for acetylene shall not exceed 25 mm.

NOTE In some countries, local regulations can restrict bores of acetylene hoses to less than 25 mm.

5.2 Concentricity

The internal diameter and concentricity of the hose, measured according to ISO 4671, shall be in accordance with the values given in [Table 1](#).